

INDEX

- ALLOY LISTING 50
ALLOY SPECIFICATIONS 52
ALLOYED CAST IRON 40, 41
ALUMINUM IN STAINLESS STEEL 19
ALUMINUM IN STEEL 2, 6
ANTIMONY IN STEEL 5
ARSENIC IN STEEL 5
- BISMUTH STEEL 5, 8
BORON IN STEEL 2
- CALCIUM IN STAINLESS STEEL 19
CALCIUM IN STEEL 6
CARBON STEEL 2, 3, 4, 44
CARBON STEEL SPECIFICATIONS 52
CAST IRON
32, 33, 34, 35, 37, 38, 39, 40, 41, 42, 43, 49
CAST IRON WITH MAGNESIUM 34, 35, 36
COBALT IN STAINLESS STEEL 21
COPPER IN STAINLESS STEEL 20
Cr-Mo STEEL 6, 7
- DUCTILE IRON 33
- EPMA SETS 6
- GRAY IRON 33
- HIGH ALLOY STEEL 31, 32, 48
HIGH ALLOY STEEL SPECIFICATIONS 55
HIGH CHROMIUM CAST IRON 40, 41
- IRON 2
- LEADED STEEL 8
LOW ALLOY STEEL
5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 45, 46
LOW ALLOY STEEL SPECIFICATIONS 53
LOW ALLOY STEEL WITH 0.13 % < C < 0.3 % 13, 14
LOW ALLOY STEEL WITH C < 0.13 % 15
LOW ALLOY STEEL WITH C > 0.3% 11, 12
LOW ALLOY STEEL WITH EXTENSIVE ANALYSIS
13, 44
- MANGANESE STAINLESS STEEL 22
MANGANESE STEEL 8
MARAGING STEEL 21
- NICKEL BINARY 22
NITROGEN IN STEEL 6
NODULAR IRON 33
- PHOSPHORUS IN STAINLESS STEEL 23
- RESULFURIZED STAINLESS STEEL 23
RESULFURIZED STEEL 9, 44
RESULFURIZED STEEL SPECIFICATIONS 52
- SELENIUM IN STAINLESS STEEL 23
SET 2, 6, 8, 9, 16, 30, 32
Si-Mo CAST IRON 33
SILICON STEEL 10, 46
SOLUBLE ALUMINUM 2
SOLUBLE BORON 2
STAINLESS STEEL
19, 20, 21, 22, 23, 24, 25, 26, 27, 28, 29, 30, 31, 47, 48
STAINLESS STEEL SPECIFICATIONS 55
STAINLESS STEEL WITH C < 0.05 % 28, 29
STAINLESS STEEL WITH C > 0.05% 26, 27
STAINLESS STEEL WITH NI < 5.0 % 24, 25
SULFUR IN STAINLESS STEEL 23
- TOOL STEEL 16, 17, 18, 45, 46
TOOL STEEL SPECIFICATIONS 54
TUNGSTEN IN STAINLESS STEEL 21
- WHITE IRON 36
- XRF 2, 6, 8, 9, 16, 30, 32

PURE IRON

= class, where 1 = CRM and 2 = RM

* Provisional Analysis

17025

T = total

Table with 15 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Mo, Al, Co, N, O. Rows include SRM 1265a, BS 50F, CZ LA-0A, CZ LA-0B, IARM 27G, BS LC-7B, BS LC-7A, BS 50G, TL 1669, BS 50D, ECRM 098-1D, and ECRM 097-2D.

Table with 11 columns: Number, As, B, Mg, Nb, Pb, Sn, Ti, V, W, Units. Rows include SRM 1265a, BS 50F, CZ LA-0A, CZ LA-0B, IARM 27G, BS LC-7B, BS LC-7A, BS 50G, TL 1669, BS 50D, ECRM 098-1D, and ECRM 097-2D.

** TL-1669 also contains in ppm Ca: 1.7, Sb: 4.9, Zn: 2.7

RM CARBON STEEL XRF SET

Part Number: BS CS-10 AVAILABLE INDIVIDUALLY 17025 ~7 mm discs

Table with 17 columns: Grade, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Mo, Al, As, Co, N, Sn, V. Rows include Pure Iron 1018, 1020, 1026, 1035, 1040, 1045, 1095, 1522 (LF2), and 1345.

CRM CARBON STEEL SET

AVAILABLE IN SET/6 ONLY

38 mm Ø x 30 mm

Table with 15 columns: Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Al.Sol, Ti, Ti.Sol, V. Rows include NCS HS11719-5, NCS HS11719-1, NCS HS11719-3, NCS HS11719-4, NCS HS11719-2, and NCS HS11719-6.

CRM SOLUBLE ALUMINUM AND SOLUBLE BORON STEEL SET

available in set/6 only as grouped .T = total .S = soluble

37 mm Ø x 30 mm

Table with 15 columns: Number, Al.T, Al.S, B.T, B.S, C, Mn, P, S, Si, Cu, Ni, Cr, Co, Mo. Rows include NCS HS93703-1a, NCS HS93703-2, NCS HS93703-3, NCS HS93703-4, NCS HS93703-5, and NCS HS93703-6.

Table with 12 columns: Number, As, Bi, Ca, Nb, Pb, Sb, Sn, Ti, V, W, Zr. Rows include NCS HS93703-1a, NCS HS93703-2, NCS HS93703-3, NCS HS93703-4, NCS HS93703-5, and NCS HS93703-6.

ARSENIC AND ANTIMONY IN STEEL

= Class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	As	Sb	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Sn	Ti
2	CZ CM-2B	0.12	0.020	0.247	0.894	0.082	0.0114	1.95	0.99	1.20	1.53	0.046	.	0.45	0.33	0.091	0.342
1	12X 12749X	0.081	.	0.176	1.41	0.023	0.066	0.48	0.253	0.47	0.453	0.202	.	0.426	0.195	0.018	0.0178
1	IMZ 120	0.065	0.031	0.60	0.40	(0.049)	0.026	0.34	0.10	0.085	0.20	0.033	.	.	.	0.008	.
1	12X 15266V	0.0640	.	0.455	1.240	0.0344	0.0258	0.674	0.226	1.317	3.49	0.526	.	0.286	0.298	0.0082	.
1	12X 350C	0.057	.	0.159	0.758	0.0296	0.040	0.467	0.196	0.160	0.335	0.290	.	0.030	0.147	0.0382	0.076
1	IRSID 1656	0.055	.	0.477	0.730	0.027	0.013	0.277	.	(0.048)	(0.017)	(0.002)	.	.	(0.007)	.	.
1	12X 354B	0.023	.	0.252	5.03	0.0478	0.0105	0.200	0.0679	0.082	0.0487	0.0150	.	0.0237	0.0328	0.0154	0.0248
1	BS 1762	0.025	(0.02)	0.363	2.04	0.032	0.037	0.38	0.133	1.16	0.929	0.049	.	0.064	0.347	0.079	0.096
1	ECRM 055-2D	0.0187	0.00376	0.5199	0.687	0.0102	0.0205	0.3094	0.2089	0.3121	0.3217	.	.	0.0257	0.0960	0.0162	0.00104
1	12X 357D	0.0127	0.018	0.312	0.219	0.0101	0.066	0.211	0.203	0.188	0.21	0.138	.	0.198	0.025	0.0145	0.074
1	IMZ 68	0.0057	0.0020	0.102	0.346	0.028	0.015	0.13	0.166	0.049	0.33	.	.	0.008	.	0.0066	0.0033
1	BS 1030	0.0055	0.0024	0.331	0.682	0.0101	0.0299	0.261	0.269	0.078	0.124	0.0014	.	0.0069	0.0182	0.0114	0.0005
1	VS UG90	0.0044	0.0011	0.34	0.286	0.0079	0.012	0.221	0.200	0.265	0.261	0.037	0.032	.	0.046	.	0.039
1	VS UG89	0.0043	0.0011	0.92	0.76	0.0085	0.01	0.385	0.373	0.51	0.420	0.01	0.007	.	0.044	.	0.012
1	VS UG92	0.0027	0.0005	0.69	0.79	0.05	0.0029	1.98	0.111	0.155	0.200	0.091	0.08	.	0.119	.	0.022
1	IRSID 1670	0.0018	.	0.0011	0.3981	0.0128	0.0075	0.0046	0.0134	0.0142	0.0174	0.0479	.	0.0018	0.0009	0.0017	0.0078
1	VS UG88	0.0007	0.0003	0.62	1.26	0.0026	0.0043	1.22	0.171	0.52	0.474	0.01	0.009	.	0.104	.	0.107
1	SS 458/2	.	0.089	0.198	0.479	0.0281	0.0314	0.504	.	.	.	0.055	0.053	0.198	.	.	.
1	SS 457/2	.	0.050	0.307	0.327	0.0098	0.0448	0.105	.	.	.	0.088	0.084	0.0217	.	.	.
1	SS 56	.	0.005	.	0.32	.	.	.	0.36	.	.	0.005	.	0.023	.	.	.

Number	B	Bi	Ca*	Ce*	Mg*	N	Nb	O*	Pb	Se	Ta	V	W	Zn	Zr	Units
CZ CM-2B	0.0010	0.0062	(0.58)	.	0.087	.	.	0.109	0.22	.	0.013	~39 mm Ø x ~25 mm
12X 12749X	0.016	.	.	0.068	0.036	.	.	~40 mm Ø x ~15 mm
IMZ 120	0.0115	.	.	0.077	40 mm Ø x 40 mm
12X 15266V	1.438	.	.	.	0.116	0.106	.	.	.	~40 mm Ø x ~15 mm
12X 350C	0.0115	0.260	.	.	~40 mm Ø x ~15 mm
IRSID 1656	(0.002)	.	.	.	40 mm Ø x 35 mm
12X 354B	0.0027	0.0802	0.0204	0.0248	.	.	~40 mm Ø x ~15 mm
BS 1762	0.0048	.	(20)	.	(3)	0.017	0.074	64	(0.011)	Fe:93.9	(0.03)	0.193	0.029	(0.01)	(0.01)	37 mm Ø x 25 mm 17025
ECRM 055-2D	0.01069	0.00245	0.0166	.	.	38 mm Ø x 25 or 30 mm
12X 357D	0.0036	0.0024	.	.	.	0.011	.	0.040	0.0057	.	.	0.127	0.0213	.	0.0049	~40 mm Ø x ~15 mm
IMZ 68	0.0086	0.046	.	.	.	38 mm Ø x 20 mm
BS 1030	0.0003	.	12	.	(2)	0.0107	(0.0004)	50	0.0005	.	(0.001)	0.031	0.0012	last	(0.0002)	38 mm Ø x ~7 mm 17025
VS UG90	0.015	~47 mm Ø x ~30 mm
VS UG89	0.017	0.0043	.	0.0003	.	.	0.021	.	.	.	~47 mm Ø x ~30 mm
VS UG92	0.016	0.034	.	0.00017	.	.	0.024	.	.	.	~47 mm Ø x ~30 mm
IRSID 1670	0.0007	.	.	(2)	.	0.0016	(0.0003)	(0.0005)	.	.	.	37 mm Ø x 30 mm
VS UG88	0.020	0.059	.	0.00015	.	.	0.117	.	.	.	~47 mm Ø x ~30 mm
SS 458/2	0.0069	0.0510	.	0.0140	.	.	.	0.105	.	.	(0.064)	38 mm Ø x 19 mm
SS 457/2	0.0046	0.0174	.	0.0098	.	.	.	0.153	.	.	0.025	38 mm Ø x 19 mm
SS 56	0.001	0.014	.	.	.	0.057	.	.	.	38 mm Ø x 19 mm last

RM

BISMUTH STEEL

Number	Bi	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	N
BS 4140A	0.105	0.40	0.84	0.021	0.076	0.21	0.15	0.15	0.97	0.016	0.005	0.010	0.16	0.0098
BS 53MOD	0.102	1.01	0.36	0.011	0.012	0.26	0.070	0.072	1.37	0.019	0.004	0.007	0.024	0.0086
BS 4150MOD	0.070	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.012	0.005	0.012	0.21	0.0087

Number	Ca	O	Pb	Sn	Ti	V	Units
BS 4140A	(0.0003)	(0.0025)	(0.001)	0.011	(0.003)	0.004	38 mm Ø x ~7 or ~10 mm last
BS 53MOD	(0.001)	(0.002)	0.0005	0.008	.	0.005	38 mm Ø x ~12 to 19 mm last
BS 4150MOD	0.0010	(0.003)	0.0010	0.013	(0.002)	0.008	38 mm Ø x ~7 mm last

CALCIUM IN STEEL

= Class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg

#	Number	Ca	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	V
1	BS HiCal-1	0.0140	0.271	1.00	(0.007)	0.0007	1.29	0.152	3.28	1.55	0.070	.	0.0024	0.379	.	0.0027
1	SS 115	0.0058	0.6224	0.682	0.0123	0.00093	0.2078	.	0.0196	0.0198	0.0527	.	.	.	0.0067	.
1	SS 116	0.0036	0.617	0.6756	0.0092	0.00176	0.201	.	0.0155	0.0141	0.0587	.	.	.	0.0069	.
1	BS 1020	0.0022	0.210	0.568	0.0058	0.0249	0.250	0.184	0.059	0.109	0.0006	.	0.0070	0.018	0.0109	0.0363
2	HRT FE2009-N	0.0020	0.12	0.55	0.010	0.003	0.32	0.08	0.25	2.56	0.030	.	.	1.02	.	0.015
2	BS 4150MOD	0.0010	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.012	.	0.012	0.21	0.0087	0.008
1	BS 4130	0.0007	0.303	0.541	0.0105	0.0113	0.245	0.221	0.088	0.924	0.0242	.	0.0065	0.168	0.0072	0.0037
2	BS 4942	0.0006	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	(0.004)	.	0.010	0.54	0.0080	0.28
1	BS PP20	0.0003	0.382	1.41	0.018	0.0070	0.262	0.119	1.00	1.94	0.0132	.	0.0145	0.212	0.0080	0.066
1	IMZ 111	0.0003	0.106	0.31	0.010	0.039	0.55	0.036	0.23	0.072	0.017	0.007	.	0.084	0.0133	0.022
2	TL 1669	0.00017	0.00226	0.0955	0.0137	0.0100	0.0093	0.0217	0.0160	0.0246	0.03553 (tot)	.	0.0019	0.0011	0.0024	(0.0006)

Number	As	B	Bi	Nb	O	Pb	Sb	Sn	Ti	W	Zr	Other
BS HiCal-1	0.0022	(0.0001)	.	(0.002)	.	(0.0005)	.	(0.0002)	0.0037	(0.0009)	(0.0008)	~38 mm Ø x ~30 mm 17025
SS 115	0.0027	.	.	38 mm Ø x 19 mm
SS 116	0.00012	.	.	0.00171	.	.	44 mm Ø x 19 mm
BS 1020	0.0074	(0.0001)	.	(0.0003)	0.0046	(0.0002)	(0.0018)	0.0090	(0.0005)	(0.0004)	(0.0005)	44 mm Ø x ~7 or 19+ mm 17025
HRT FE2009-N	Zn: 0.004	40 mm Ø x 40 mm
BS 4150MOD	0.005	.	0.070	.	(0.003)	0.0010	.	0.013	(0.002)	.	.	38 mm Ø x ~7 or 19 mm last
BS 4130	0.0048	(0.0002)	.	0.0015	0.0015	(0.00003)	(0.0021)	0.0099	0.0009	0.0011	(0.0002)	38 mm Ø x ~17 or 19 mm last
BS 4942	0.005	.	.	.	(0.0021)	.	.	0.014	.	.	.	38 mm Ø x ~7 mm last
BS PP20	0.0049	0.00011	.	0.0048	(0.0010)	.	0.0013	0.0069	0.0007	0.0058	.	38 mm Ø x ~7 or 19+ mm 17025
IMZ 111	40 mm Ø x 40 mm
TL 1669	0.0017	0.00038	.	0.00046	.	0.00013	0.00049	0.0071	0.0504	.	(0.00021)	38 mm Ø x 25 mm Zn: 2.7*

CRM AL, Ca, AND N IN LOW ALLOY STEEL

Number	Al	Ca	N	Units
IMZ 133	.	.	0.0360	40 mm Ø x 40 mm
IMZ 131	0.0043	.	0.0333	40 mm Ø x 40 mm
IMZ 135	0.0274	0.0008	0.0238	40 mm Ø x 40 mm
IMZ 169	0.075	.	0.0193	40 mm Ø x 40 mm
IMZ 141	0.0071	.	0.0154	40 mm Ø x 40 mm
IMZ 130	0.0046	0.0024	0.0153	40 mm Ø x 40 mm
IMZ 139	(0.029)	0.0031	0.0113	40 mm Ø x 40 mm
IMZ 132	0.0021	0.0002	0.0097	40 mm Ø x 40 mm
IMZ 137	0.0017	0.00025	0.0083	40 mm Ø x 40 mm
IMZ 140	0.0307	0.0015	0.0083	40 mm Ø x 40 mm
IMZ 138	0.0022	.	0.0063	40 mm Ø x 40 mm
IMZ 134	0.0124	0.0005	.	40 mm Ø x 40 mm
IMZ 136	0.0034	0.00031	.	40 mm Ø x 40 mm

C-Mo and Cr-Mo STEEL XRF SET

= class, where 1 = CRM ISO **17025** and 2 = RM, Set Part Number: BS MOLY-5 AVAILABLE INDIVIDUALLY ~7 mm discs

#	Grade	Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	N	Sn	V
2	C-.5Mo	4419	BS 3952	0.208	0.546	0.011	0.021	0.264	0.202	0.112	0.105	0.519	0.048	.	(0.0005)	.	.
1	1.25Cr-.5Mo	F-11	BS 45B	0.140	0.502	0.0068	0.017	0.583	0.101	0.136	1.14	0.60	0.030	0.0090	0.0066	0.0069	0.0083
1	2.25Cr-1Mo	F-22	BS 46B	0.126	0.472	0.0087	0.0187	0.219	0.128	0.081	2.28	1.00	0.020	0.0074	0.0100	0.0073	0.0073
2	5Cr-.5Mo	F-5	BS 47A	0.130	0.44	0.017	0.015	0.27	0.11	0.12	4.22	0.47	0.015	0.011	0.018	0.008	0.016
1	9Cr-1Mo	F-9	BS 48B	0.110	0.365	0.0228	0.0068	0.75	0.070	0.165	8.78	0.949	0.0157	0.0165	0.0088	0.0049	0.033

CRM EPMA SETS

available in sets only, as grouped 4x10x15mm

Number	Cr	Number	Ni
NMIJ 1001-a	5.00	NMIJ 1006-a	5.04
NMIJ 1002-a	14.96	NMIJ 1007-a	10.05
NMIJ 1003-a	19.87	NMIJ 1008-a	20.02
NMIJ 1004-a	29.84	NMIJ 1009-a	39.92
NMIJ 1005-a	39.69	NMIJ 1010-a	60.07

RESULFURIZED STEEL

= Class, where 1 = CRM and 2 = RM OES regularly requires extension of preburn time to analyze correctly

Main chemical composition table for Resulfurized Steel, including elements S, C, Mn, P, Si, Cu, Ni, Cr, Al, Co, Mo, N, Sn, Ti, V and second row elements As, B, Bi, Ca, Nb, O, Pb, Sb, W, Zn, Zr. Includes various grades like IMZ 123, BS 66K, etc.

RM RESULFURIZED STEEL XRF SET Part Number: BS RESUL-4 AVAILABLE INDIVIDUALLY -7 mm discs

XRF Set table with columns: Grade, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Mo, Al, Co, N, Sn, V, As. Lists grades 1117, 1140 + P, 1141, 1215.

SILICON STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Mo	N	Sn	Ti
2	CZ SST-4A	4.73	0.062	0.376	0.031	0.020	0.111	0.082	0.105	0.514	.	0.019	0.0058	0.025	0.035
2	CZ SST-3A	3.27	0.035	0.221	0.007	0.0093	0.096	0.061	0.043	0.009	.	0.036	0.0088	0.015	0.009
1	SRM 1218	(3.2)	0.0029	0.014	(0.002)	0.0011	0.003	(0.002)	0.006	0.005	.	(0.003)	.	.	(0.004)
1	SRM 1135	3.19	0.027	0.094	0.006	0.026	0.056	0.050	0.022	0.0028	.	0.014	.	0.004	.
2	CZ SST-2A	3.07	0.083	0.160	0.026	0.0089	0.205	0.066	0.138	0.010	.	0.054	0.0078	0.055	0.016
1	SRM 1134	2.889	0.0261	0.2751	0.0276	0.0095	0.0707	0.0375	0.0198	(0.329)	.	0.0087	.	0.0034	.
2	CZ SST-1A	2.57	0.072	0.062	0.041	0.0043	0.654	0.155	0.209	0.061	.	(0.002)	0.0059	0.110	0.004
1	12X 15251U	2.05	1.017	0.910	0.0253	0.0215	0.1194	0.896	0.612	0.1085	.	0.205	0.0031	0.0108	.
1	VS UG92	1.98	0.69	0.79	0.05	0.0029	0.111	0.155	0.200	0.091	0.08	0.119	0.016	.	0.022
1	KUT T4/1	1.97	0.17	0.23	0.012	0.041	0.16	0.077	0.24	(<0.005)
1	12X 15259Q	1.81	0.603	0.401	0.0401	0.0704	0.200	4.02	0.512	0.1488	.	0.407	0.0151	0.053	.
1	ECRM 196-2D	1.808	0.0060	0.364	0.00369	0.00065	0.0057	0.0401	0.0282	0.2167	.	0.0142	0.00178	0.00047	0.00253
1	VS UG4/5	1.80	0.56	1.26	(0.008)	(0.006)	0.098	0.68	0.17	0.010	.	0.087	.	.	0.17
2	CZ LA-2E	1.725	0.081	0.111	0.060	0.044	0.577	2.015	0.149	0.357	.	0.652	0.0071	0.087	0.343
1	ECRM 186-1D	1.72	0.610	0.870	0.022	0.035	0.281	0.190	0.218	0.014	.	0.048	.	.	.
1	12X 44220A	1.662	0.417	0.874	0.0050	0.0009	0.031	1.89	0.846	0.029	.	0.401	0.0030	0.0019	.
1	VS UG111	1.64	0.52	0.625	0.0028	0.0035	0.065	0.036	0.058	0.049	.	0.039	.	.	0.025
1	VS UG1/9	1.63	0.63	0.84	0.030	0.017	0.020	0.105	0.046	0.027	.	0.135	(0.002)	(0.002)	0.069
1	IARM 340A	1.63	0.414	0.755	0.011	0.001	0.103	1.80	0.84	0.062	.	0.39	0.0020	0.005	0.0098
1	IARM 342A	1.63	0.257	1.37	0.006	0.0051	0.110	1.76	0.38	0.019	.	0.42	0.0102	0.021	0.0028
1	VS UG4/10	1.61	0.695	0.834	0.031	0.0060	0.050	0.156	0.130	0.064	.	0.089	0.0192	.	0.0044
1	KUT B1/1	1.58	0.97	0.205	0.017	0.032	0.14	3.96	1.66
1	VS UG1/10	1.51	0.51	0.659	0.0053	0.0042	0.096	0.190	0.067	0.015	.	0.051	0.0164	0.0030	0.016
1	KUT A11/1	(1.46)	0.043	0.21	0.011	0.0137	0.047	0.04	0.02	0.02	.	1.20	.	0.002	0.17
2	CZ CM-14C	1.352	0.586	1.723	0.0169	0.0266	0.365	1.141	1.316	0.226	.	0.432	0.0092	0.048	0.420
1	VS UG4/6	1.25	0.59	1.23	(0.003)	0.0008	0.169	0.47	0.400	0.032	.	0.083	(<0.0005)	0.017	0.131
1	VS UG87	1.25	0.59	1.18	0.026	0.022	0.030	0.50	0.260	0.024	0.02	0.044	0.010	.	0.103
1	VS UG1/5	1.23	0.62	0.79	(0.02)	(0.03)	(0.01)	0.048	0.069	0.022	.	0.061	.	.	0.045
1	VS UG88	1.22	0.62	1.26	0.0026	0.0043	0.171	0.52	0.474	0.01	0.009	0.104	0.020	.	0.107
1	DSZU C046	1.21	0.785	0.257	0.025	0.0153	0.211	1.47	2.67	0.47	.	0.69	0.0099	0.0033	0.115
1	KUT A12	1.19	0.031	0.31	0.014	0.082	0.18	2.43	1.25	0.18	.	0.47	.	.	0.05
1	12X 15258P	1.01	0.392	1.23	0.067	0.032	0.109	0.497	0.631	0.087	.	0.361	.	0.071	0.100
1	SS 603/2	0.97	0.79	0.236	0.020	0.056	(0.05)	(0.03)	(0.04)	0.076	.	(0.004)	.	.	.
2	CZ CM-23A	0.934	0.917	0.803	0.0609	0.0348	0.234	0.230	3.064	0.323	.	0.816	0.0149	0.059	0.154
1	SS 113	0.931	0.837	1.207	0.0595	0.0294	0.179	0.0784	1.248	0.0151	.	0.056	0.0109	0.0067	0.0390
1	SS 604/2	0.75	0.199	1.91	0.016	0.072	(0.07)	(0.09)	(0.06)	0.008	.	(0.02)	.	.	.
2	CZ CM-25A	0.656	0.097	0.781	0.0036	0.0051	0.0040	0.0214	0.0248	0.0030	.	.	0.0061	.	.
#	Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Mo	N	Sn	Ti
Number	As	B	Ca	Co	Nb	O	Pb	Sb	Ta	V	W	Zr	Units		
CZ SST-4A	0.004	0.0006	.	0.012	.	.	0.008	(0.003)	.	0.031	0.026	(0.003)	-37 mm Ø x 25 mm		
CZ SST-3A	(0.003)	0.0019	.	0.038	.	Zn:0.011	0.013	.	.	0.041	0.016	.	-37 mm Ø x 25 mm		
SRM 1218	.	.	.	(0.002)	(<0.001)	.	(0.002)	32 mm Ø x 19 mm		
SRM 1135	<0.01	.	.	31 mm Ø x 19 mm		
CZ SST-2A	.	0.0089	.	0.022	.	Zn:0.011	0.015	0.008	.	0.024	0.019	0.017	-37 mm Ø x 25 mm		
SRM 1134	31 mm Ø x 19 mm		
CZ SST-1A	(0.002)	0.0003	.	0.005	.	(0.002)	(0.002)	.	.	0.006	.	.	-37 mm Ø x 25 mm		
12X 15251U	.	.	.	0.228	0.266	0.391	0.0393	.	-40 mm Ø x -15 mm		
VS UG92	0.0027	.	.	.	0.034	.	0.00017	0.0005	.	0.024	.	.	-47 mm Ø x -30 mm		
KUT T4/1	30-35 mm Ø x 39 mm last		
12X 15259Q	.	.	.	0.141	0.249	0.139	0.49	.	-40 mm Ø x -15 mm last		
ECRM 196-2D	0.00033	0.00014	0.00071	0.0138	Mg:0.00075	0.00368	.	Zn:0.00019	38 mm Ø x 25 mm		
VS UG4/5	.	.	.	0.053	0.054	0.14	.	-45 mm Ø x -28 mm		
CZ LA-2E	0.083	0.0043	.	0.268	0.111	.	0.068	0.033	.	0.310	0.307	.	-37 mm Ø x 25 mm		
ECRM 186-1D	38 mm Ø x 25 or 30 mm		
12X 44220A	0.0026	0.0764	.	.	-38 mm Ø x -15 mm		
VS UG111	0.058	0.056	.	-45 mm Ø x -28 mm		
VS UG1/9	(0.001)	(0.0003)	.	.	0.124	.	(0.002)	.	.	0.024	0.063	.	-45 mm Ø x -28 mm		
IARM 340A	(0.004)	0.0004	(0.0004)	0.006	0.015	(0.001)	(0.001)	0.0021	.	0.064	(0.005)	(0.002)	31 mm Ø x 2 mm		
IARM 342A	(0.006)	0.0004	(0.0001)	0.008	(0.002)	0.0006	0.0008	0.0021	.	0.023	(0.005)	(0.002)	31 mm Ø x 2 or 18 mm		
VS UG4/10	0.030	0.0239	0.006	.	-45 mm Ø x -28 mm		
KUT B1/1	0.001	30-35 mm Ø x 39 mm		
VS UG1/10	0.091	0.042	0.074	.	-45 mm Ø x -28 mm		
KUT A11/1	0.16	0.46	.	.	30-35 mm Ø x 39 mm		
CZ CM-14C	0.0165	0.0249	.	0.0306	0.248	.	0.0090	0.0170	.	0.325	0.0238	0.037	37 mm Ø x 25 mm		
VS UG4/6	(0.001)	.	.	(0.004)	(0.03)	.	(0.005)	(<0.0005)	.	0.051	0.111	.	-45 mm Ø x -28 mm		
VS UG87	0.116	0.00008	0.0012	.	0.0038	.	.	-47 mm Ø x -30 mm		
VS UG1/5	0.0007	.	.	.	0.078	0.070	(0.01)	.	-45 mm Ø x -28 mm		
VS UG88	0.0007	.	.	.	0.059	.	0.00015	0.0003	.	0.117	.	.	-47 mm Ø x -30 mm		
DSZU C046	0.0020	(0.0004)	0.0007	0.006	(0.005)	0.72	0.47	.	40 mm Ø x 25 mm		
KUT A12	0.007	.	.	0.012	(0.03)	.	.	0.013	.	0.042	.	.	30-35 mm Ø x 39 mm		
12X 15258P	.	0.0100	.	0.310	0.133	.	.	.	(0.002)	0.378	0.125	.	-40 mm Ø x -15 mm		
SS 603/2	.	.	.	(0.01)	(0.001)	.	(<0.005)	44 mm Ø x 19 mm		
CZ CM-23A	0.0146	0.0129	0.0004	0.510	0.628	Zn:0.0250	0.0034	0.137	(0.051)	0.157	0.104	0.137	37 mm Ø x 25 mm		
SS 113	0.0020	0.0066	.	0.0415	0.0487	0.201	0.012	0.0029	44 mm Ø x 19 mm		
SS 604/2	.	.	.	(0.01)	(0.001)	.	(<0.005)	44 mm Ø x 19 mm		
CZ CM-25A	0.0161	0.0048	.	37 mm Ø x 25 mm		
Number	As	B	Ca	Co	Nb	O	Pb	Sb	Ta	V	W	Zr	Units		

LOW ALLOY STEEL WITH C > 0.3%						CONTINUED ON THE NEXT PAGE					# = Class, where 1=CRM, 2=RM, 3=RM no uncertainties					
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti
1	VS UG0/9	1.33	0.208	0.0040	0.0045	0.170	0.307	0.36	0.55	0.139	(0.001)		0.024	0.0022	0.041	0.029
1	VS UG0/10	1.321	0.268	0.0090	0.0044	0.244	0.265	0.353	0.596	0.101			0.052	0.0120	0.0033	0.017
1	VS UG0/5	1.32	(0.2)	(0.01)	(0.007)	(0.2)	0.265	0.351	0.60	0.108			(0.05)		(0.01)	(0.01)
1	SS 402/2	1.311	0.288	0.0161	0.0138	0.111	0.302	0.808	0.652	0.161			0.140	0.0069		
1	IMZ 65/2	1.19	0.27	0.013	0.007	0.13	0.059	0.067	0.079	0.030						
1	DSZU C049	1.17	0.237	0.0166	0.0147	0.227	0.069	0.044	0.131	(0.005)		(0.003)	(0.002)	(0.007)		(0.003)
1	KUT A18	1.16	(1.99)	0.014	0.007	0.15	0.066	0.125	0.90	(0.02)					0.035	0.011
1	VS UG0/11	1.16	0.196	0.0054	0.0078	0.233	0.134	0.114	0.163	0.009		0.0109	0.011	0.005		0.0041
3	CZ CM-5B	1.09	1.28	0.021	0.012	0.39	0.13	0.23	2.07	0.083		0.022	0.10	0.0135	0.06	0.05
1	14X 72305A	1.085	0.349	0.0128	0.0028	0.206	0.149	0.089	0.425	0.0049			0.0231	0.0068		
2	CZ CM-5C	1.04	1.17	0.029	0.021	0.54	0.151	0.42	2.45	0.063		0.022	0.132	0.014	0.014	0.031
1	VS UG9/9	1.04	0.310	0.0053	0.021	0.319	0.163	0.242	0.310	0.073	(0.003)		0.308	0.0027	0.0046	0.130
1	IMZ 172	1.03	0.71	0.018	0.047	0.21	0.128	0.12	4.47	0.062		0.012	0.96	0.0192		(0.002)
1	IARM 49E	1.03	0.364	(0.006)	(0.002)	0.248	0.076	0.043	1.43	0.024		(0.006)	0.017	(0.003)	(0.003)	0.0060
1	12X 52986A	1.023	0.372	0.0049	0.0011	0.246	0.077	0.0411	1.418	0.0258	(0.002)		0.0169	(0.002)		
2	BS 53G	1.02	0.35	0.014	0.015	0.23	0.160	0.090	1.53	0.019			0.008	0.034	0.0084	(0.002)
1	NILAB 100LA D	1.002	0.333	0.012	0.018	0.27	0.019	0.027	1.517	0.005			0.007	0.012	0.0046	0.007
1	IARM 324A	0.99	1.01	0.009	0.028	0.163	0.22	0.081	0.42	0.002			0.007	0.022	0.0082	0.014
2	BS A485-1	0.98	1.10	0.019	0.004	0.62	0.16	0.13	1.07	0.017		0.010	0.029	0.0060		0.003
1	KUT B15	0.98	0.69	0.030	0.031	0.80	0.14	0.15	3.70	0.13		0.21	1.20			(0.32)
1	VS UG75	0.98	0.286	0.0127	0.0089	0.248	0.111	0.201	1.43	(0.03)			(0.01)		(0.01)	(0.001)
2	CZ LA-4C	0.95	1.63	0.021	0.012	0.07	0.056	0.045	1.78	0.048		(0.006)	0.008	0.012	0.053	(0.002)
1	VS UG9/11	0.94	0.895	0.027	0.0085	0.312	0.163	0.354	0.985	(0.04)			0.094	0.0119		0.010
1	12X 19965A	0.936	0.600	0.0196	0.0081	0.247	0.148	0.141	1.713	0.0256			0.210	0.0087		
1	SS 401/2	0.935	1.19	0.026	0.0078	0.60	0.101	0.019	0.138	0.074		0.0042	0.49	0.0159		
1	IMZ 119	0.93	1.15	0.018	0.006	0.16	0.042	0.049	0.062	0.010	0.007			0.0086		(0.0007)
1	VS UG89	0.92	0.76	0.0085	0.01	0.385	0.373	0.51	0.420	0.01	0.007		0.044	0.017	0.0043	0.012
1	VS UG21/6	0.83	0.74	(0.02)	(0.02)	0.312	0.346	0.47	0.50							
2	IARM 172A	0.78	0.010	0.007	0.004	1.29	0.40	0.025	3.52	0.39		0.006	0.014	0.0004	0.004	0.003
1	SS 403/2	0.750	1.677	0.055	0.0381	0.209	0.221	0.223	0.463	0.0485			0.088	(0.010)		
1	IMZ 64/2	0.75	0.47	0.012	(0.005)	0.22	0.12	0.081	0.090	0.020						
1	VS UG8/11	0.728	1.97	0.036	0.0019	0.31	0.160	0.291	1.74	(0.01)			0.622	0.0138		
1	ECRM 059-2D	0.721	0.495	0.0046	0.0084	0.188	0.0074	0.0198	0.0090	0.00045	0.00020		0.0018	0.0051		
2	CZ CM-4B	0.72	0.50	0.023	0.012	0.80	0.40	1.40	2.23	0.025		0.115	0.33	0.013	0.071	0.12
1	SS 404/2	0.696	0.532	0.0479	0.0228	1.121	0.427	0.393	0.774	0.017			0.307	0.0089		
1	IMZ 118	0.69	1.72	0.026	(0.049)	0.30	0.18	0.19	0.14	(0.014)	(0.004)		0.058	0.0120		
1	IMZ 116	0.64	0.94	0.025	0.035	0.25	0.33	0.022	0.72	0.025	0.012		0.074	0.0130		(0.0008)
1	VS UG1/11	0.61	0.667	0.0098	0.011	1.74	0.155	0.080	0.108	0.032		0.0195	0.0067	0.0100		0.0047
1	VS UG96	0.60	0.52	0.0046	0.0029	0.290	0.256	0.396	0.399	0.031			0.0042			0.0025
1	VS UG119	0.55	0.70	0.012	(0.02)	1.63	0.207	0.142	0.195	0.039			0.0113	0.0047		0.0030
1	12X 10550	0.549	0.685	0.0184	0.0055	0.281	0.0290	0.0247	0.338	0.0325			0.0086	0.0051		
1	12X 61500A	0.530	0.912	0.0104	0.0102	0.240	0.157	0.0976	1.023	(0.007)	0.0067		0.0195			
2	CZ CM-6A	0.52	0.37	0.016	0.058	0.27	0.05	0.19	0.37	0.02		0.03	0.04	0.009	0.028	0.03
2	CZ BO-2B	0.515	0.745	0.0093	0.0016	0.309	0.100	0.057	0.212	0.0196		0.0055	0.006	0.004		0.0017
1	12X LA3C	0.500	1.693	0.0274	0.0442	0.163	0.213	0.280	0.375	0.0410		0.0475	0.303	0.0039		
1	IARM 34C	0.50	0.739	0.0090	0.0011	0.30	0.078	0.085	0.914	0.068		0.005	0.022	0.0030	0.004	0.0045
1	BS 494I	0.490	0.79	0.012	0.017	0.27	0.106	0.074	0.96	0.024		0.008	0.039	0.0076		
1	BS 43A	0.49	0.82	0.0074	0.025	0.252	0.18	0.24	0.92	(0.003)		0.008	0.059	0.0072	(0.0017)	(0.002)
1	IMZ 117	0.49	0.77	0.038	0.015	0.34	0.41	0.29	0.94	0.023	0.013		0.024	0.0154	0.041	(0.0014)
1	BS 1144	0.483	1.55	0.022	0.243	0.262	0.462	0.097	0.193	(0.002)		0.011	0.017	0.0093	(0.004)	0.002
1	IPT 503	0.456	0.682	0.027	0.027	0.218	0.129	0.063	0.160	0.018		0.006	0.020	0.0082		0.0011
1	SRM C1173	0.453	0.174	0.031	0.092	1.38	0.204	4.04	2.63				1.46			0.037
1	12X 41450A	0.446	1.011	0.0093	0.0031	0.261	0.1318	0.187	1.194	0.0220			0.340	0.0080		
1	VS UG5/11	0.445	0.64	0.010	0.0037	0.29	0.146	0.140	0.912			0.0195	0.269	0.00119		
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti
2	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.033		0.006	0.007	0.0056	(<0.002)	(0.002)
1	12X LA3B	0.439	1.176	0.0215	0.0379	0.16	0.173	0.300	0.357	0.0300		0.0300	0.302	0.0080		
1	NM PC-4	0.43	0.80	0.043	0.045	0.34			0.26							
1	IARM 30H	0.425	0.937	0.015	0.022	0.253	0.131	0.063	0.97	0.020		0.0071	0.199	0.0081	(0.003)	(0.0024)
1	IARM 305B	0.425	0.58	0.011	0.014	0.349	0.214	0.156	1.63	0.92		0.007	0.32	0.0044	0.002	0.0044
1	IARM 252D	0.423	0.842	0.0075	0.0128	0.256	0.270	0.424	0.468	0.024		0.0078	0.204	0.0068	0.0013	0.0012
1	BS 4340A	0.423	0.766	0.0062	(0.0008)	0.253	0.128	1.80	0.879	0.031		0.0111	0.259	0.0102	(0.002)	(0.0011)
1	SRM 1173	0.423	0.19	0.033	0.092	1.28	0.204	4.06	2.70				1.50			
2	HRT FE2015-N	0.42	0.83	0.007	0.028	0.24	0.15	0.32	1.03	0.023			0.21	0.0057		
1	BS 4340	0.418	0.695	0.0119	0.0187	0.279	0.149	1.79	0.807	0.028		0.0068	0.231	0.0080	(0.001)	0.0014
1	IARM 252C	0.416	0.92	0.025	0.008	0.248	0.109	0.505	0.501	0.017		0.008	0.205	0.0083	0.002	0.001
2	BS 4942	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	(0.004)		0.010	0.54	0.0080		
1	IARM 252E	0.413	0.87	(0.009)	(0.012)	0.257	0.164	0.407	0.486	0.028		0.0093	0.204	0.0064		0.0010
2	BS 1962	0.41	0.94	0.007	0.011	0.242	0.224	0.16	1.05	0.018		0.008	0.229	0.0095		0.004
1	VS UG116	0.41	0.59	0.012	0.027</											

Number	LOW ALLOY STEEL WITH C > 0.3%						CONTINUED FROM THE PREVIOUS PAGE						Units	
	As	B	Ca	Fe	Mg	O	Pb	Sb	Sn	Ta	V	W		Zr
VS UG0/9	.	(0.0002)	(0.002)	.	(0.0008)	.	0.0087	0.074	.	~45 mm Ø x ~28 mm
VS UG0/10	0.0043	.	0.0037	(0.006)	.	~45 mm Ø x ~28 mm
VS UG0/5	(0.01)	(0.01)	.	~45 mm Ø x ~28 mm
SS 402/2	0.194	.	.	38 mm Ø x 19 mm
IMZ 65/2	40 mm Ø x 40 mm
DSZU C049	(0.004)	(0.0002)	(0.003)	(0.004)	.	(0.003)	.	.	40 mm Ø x 25 mm
KUT A18	0.003	(0.011)	0.005	0.016	.	0.10	.	.	30-35mm Ø x 38 mm
VS UG0/11	0.0051	.	0.0035	0.0032	.	~45 mm Ø x ~28 mm
CZ CM-5B	0.018	0.002	0.01	0.006	0.012	.	0.06	0.03	0.09	~37 mm Ø x 25 mm
14X 72305A	0.0101	.	0.0045	.	.	~40 mm Ø x ~15 mm
CZ CM-5C	0.020	0.0012	(0.0006)	0.018	.	0.106	0.034	(0.07)	~39 mm Ø x 25 mm
VS UG9/9	.	(0.0002)	(0.001)	.	0.215	1.60	.	~45 mm Ø x ~28 mm
IMZ 172	0.010	.	0.20	0.011	.	40 mm Ø x 40 mm
IARM 49E	0.0029	(0.002)	.	.	0.0065	.	0.066	.	.	31 mm Ø x 2 or 18 mm
12X 52986A	0.0063	.	0.0615	.	.	~38 mm Ø x ~15 mm
BS 53G	0.004	(0.0001)	(0.0001)	.	.	0.001	.	.	0.007	.	0.006	(0.13)	last	44 mm Ø x ~17 or 19 mm
NILAB 100LA D	0.004	0.004	.	.	34 mm Ø x 20 mm
IARM 324A	0.006	0.0004	0.0009	.	.	0.003	.	(0.002)	0.011	.	0.0017	(0.003)	(0.001)	31 mm Ø x 2 mm
BS A485-1	0.006	(0.0008)	.	.	0.011	.	0.003	.	.	39 mm Ø x ~7 or 19+ mm
KUT B15	(0.33)	.	.	30-35mm Ø x 39 mm
VS UG75	(0.006)	(0.02)	.	~40 mm Ø x ~26 mm
CZ LA-4C	(0.003)	0.0005	(0.006)	.	(0.010)	0.008	.	~37 mm Ø x 25 mm
VS UG9/11	0.0064	.	0.048	1.27	.	~45 mm Ø x ~28 mm
12X 19965A	0.0070	.	0.0087	.	Zn:0.0008	~41 mm Ø x ~15 mm
SS 401/2	0.496	.	.	38 mm Ø x 19 mm
IMZ 119	.	(0.0002)	0.006	.	.	40 mm Ø x 40 mm
VS UG89	0.0043	0.0003	0.0011	.	.	0.021	.	.	~47 mm Ø x ~30 mm
VS UG21/6	~45 mm Ø x ~28 mm
IARM 172A	(0.005)	0.0003	.	.	.	0.0006	(<0.01)	.	0.003	.	0.003	0.038	.	31 mm Ø x 2 mm
SS 403/2	0.341	.	.	38 mm Ø x 19 mm
IMZ 64/2	40 mm Ø x 40 mm
VS UG8/11	0.0058	.	0.181	0.70	.	~45 mm Ø x ~28 mm
ECRM 059-2D	38 mm Ø x 25 or 30 mm
CZ CM-4B	0.015	0.017	0.022	0.052	0.028	.	0.18	0.116	Zn:0.007	~39 mm Ø x 25 mm
SS 404/2	0.107	.	.	38 mm Ø x 19 mm
IMZ 118	.	(0.0002)	0.22	.	0.059	.	.	40 mm Ø x 40 mm
IMZ 116	0.076	.	.	40 mm Ø x 40 mm
VS UG1/11	0.0035	~45 mm Ø x ~28 mm
VS UG96	0.0030	.	.	~40 mm Ø x ~28 mm
VS UG119	~45 mm Ø x ~25 mm
12X 10550	0.0059	0.0018	.	.	.	Zn:(0.0016)	~40 mm Ø x ~15 mm
12X 61500A	0.0114	.	0.110	.	Zn: 0.0055	~38 mm Ø x ~15 mm
CZ CM-6A	0.025	0.015	0.017	0.03	0.017	.	0.05	0.04	0.04	~39 mm Ø x 25 mm
CZ BO-2B	0.0057	.	(0.0008)	0.0062	.	(0.001)	(0.005)	.	~37 mm Ø x ~25 mm
12X LA3C	0.0301	Zn:(0.004)	(0.004)	.	.	.	0.157	.	0.0197	~40 mm Ø x ~15 mm
IARM 34C	0.0024	0.0003	(0.0004)	.	.	0.0008	(0.0003)	(0.001)	0.0058	.	0.206	(0.003)	(0.001)	31 mm Ø x 2 or 18 mm
BS 4941	(0.004)	.	(0.0002)	.	.	0.0017	.	.	0.006	.	0.164	.	.	41 mm Ø x ~7 or 19+ mm
BS 43A	(0.005)	(0.0002)	(0.0006)	[96.8]	(0.0001)	(0.003)	.	(0.002)	0.011	.	0.145	(0.005)	(0.001)	41 mm Ø x ~7 or 19+ mm
IMZ 117	.	(0.0002)	0.087	.	.	40 mm Ø x 40 mm
BS 1144	0.009	0.0016	(0.001)	.	0.0113	.	0.0039	(0.003)	last	38 mm Ø x ~16 mm 17025
IPT 503	0.008	35 mm Ø x 20 mm
SRM C1173	0.42	.	.	32 mm Ø x 19 mm
12X 41450A	0.0053	0.0090	.	0.0385	.	.	~38 mm Ø ~15 mm
VS UG5/11	0.0047	.	0.148	0.049	.	~45 mm Ø x ~28 mm
Number	As	B	Ca	Fe	Mg	O	Pb	Sb	Sn	Ta	V	W	Zr	Units
BS XCCV	0.002	(0.0018)	(<0.0006)	(0.0003)	(0.0004)	.	(<0.003)	.	(<0.0002)	36 mm Ø x ~7 or 19+ mm
12X LA3B	.	0.0015	0.0149	.	.	Zn:0.0098	0.157	.	(0.027)	~40 mm Ø x ~15 mm
NM PC-4	40 mm Ø x 20 mm last
IARM 30H	0.0046	(0.0007)	(0.0009)	.	(0.001)	(0.0016)	(0.0005)	0.0013	0.008	.	(0.0040)	(0.007)	(0.002)	31 mm Ø X 2 mm
IARM 305B	(0.006)	0.0006	0.0007	.	(0.002)	0.0006	(0.0003)	(0.004)	0.011	.	0.004	(0.004)	0.0011	31 mm Ø X 2 or 18 mm
IARM 252D	0.0053	(0.0002)	(0.001)	.	(0.0002)	(0.0013)	(0.0004)	0.0024	0.012	.	0.0022	(0.004)	(0.0013)	31 mm Ø x 2 mm
BS 4340A	0.0059	(0.0002)	(0.0002)	95.4	0.0004	0.0007	(0.0003)	(0.0018)	0.0081	.	0.0024	0.0005	0.0016	38 mm Ø x ~7 or 19+ mm 17025
SRM 1173	0.42	.	.	32 mm Ø x 19 mm
HRT FE2015-N	0.06	.	.	35 mm Ø x 20 mm
BS 4340	0.0043	(0.0002)	0.0005	95.5	(0.0002)	0.0012	(0.0002)	(0.0013)	0.0063	.	0.0033	0.0012	0.0005	38 mm Ø x ~7 mm 17025 last
IARM 252C	0.004	(0.0001)	(0.0003)	.	.	(0.002)	0.001	<0.005	0.007	.	0.005	<0.005	<0.002	31 mm Ø x 2 mm
BS 4942	0.005	.	0.0006	.	.	(0.0021)	.	.	0.014	.	0.28	.	.	38 mm Ø x ~7 mm last
IARM 252E	0.0046	0.0075	.	(0.0028)	.	.	31 mm Ø X 2 or 18 mm
BS 1962	0.007	.	<u>25(pre-17025)</u>	.	(0.0001)	.	(0.001)	.	0.010	.	0.004	.	.	41 mm Ø x ~7 mm last
VS UG116	~45 mm Ø x ~25 mm
IARM 252F	(0.006)	0.006	.	(0.003)	(0.003)	.	31 mm Ø X 2 or 18 mm
IARM 30J	(0.002)	0.0109	.	0.0045	(0.005)	.	31 mm Ø X 2 mm
SS 114	0.0025	0.0008	0.041	.	0.0086	.	0.0051	44 mm Ø x 19 mm
IMZ 55/1A	.	0.0018	0.017	.	0.107	.	.	38 mm Ø x 20 mm
IARM 31G	(0.004)	0.0004	0.0077	.	0.0036	(0.004)	(0.0012)	31 mm Ø X 2 mm
IMZ 63/2	40 mm Ø x 40 mm
SS 225/2	38 mm Ø x 19 mm
IPT 504	36 mm Ø x 20 mm
12X 826M40A	0.0056	0.0085	~38 mm Ø x ~15 mm
BS 4942A	0.0031	(0.0001)	0.0012	96.8	0.0004	0.0020	(0.0007)	(0.001)	0.0044	.	0.280	(0.0009)	(0.001)	38 mm Ø x ~7 or 19+ mm 17025
VS RC20/1	0.70	0.89	.	~45 mm Ø x ~28 mm
VS UG79	(0.02)	(0.01)	.	~40 mm Ø x ~26 mm
IRSID 1731	44 mm Ø x 30 mm
DSZU C045	0.0052	(0.0004)	0.0005	0.0050	.	0.004	(0.011)	.	40 mm Ø x 25 mm last
VS UG3/10	0.0057	.	0.0053	0.006	.	~45 mm Ø x ~28 mm
12X 605M36A	0.0102	.	0.0033	0.0101	~38 mm Ø x ~15 mm
12X 12700A	0.0060	0.0014	0.0033	.	Zn:0.0120	~50 mm Ø x ~20 mm
IMZ 115	(0.063)	.	.	40 mm Ø x 40 mm
IRSID 1750	0.0188	(0.0002)	(0.0002)	.	(<0.0002)	.	(<0.001)	0.0031	0.0137	(<0.0010)	0.114	(0.004)	(0.0002)	38 mm Ø x 25 mm
IMZ 114A	0.0035	0.0019	0.021	0.018	0.014	.	0.096	(0.007)	Zn:(0.006)	38 mm Ø x 20 mm
12X 352E	0.029	0.109	(0.018)	0.0251	0.275	.	~40 mm Ø x ~15 mm
VS UG7/10	0.0006	.	0.234	0.34	.	~45 mm Ø x ~28 mm
IMZ 174	0.010	.	0.98	0.021	.	40 mm Ø x 40 mm
DSZU C05a	(0.005)	0.010	(0.003)	(0.0005)	0.010	.	0.20	0.27	.	40 mm Ø x 25 mm
12X 349E	0.0107	0.115					

LOW ALLOY STEEL WITH 0.13 % < C < 0.3 % - CONTINUED ON THE NEXT PAGE

#=Class, where 1=CRM and 2=RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Sn	V
1	IARM 330A	0.299	1.00	(0.005)	(0.001)	0.273	0.074	1.80	0.90	0.045	.	(0.003)	0.0063	0.404	0.0024	0.0039	0.071
1	12X 16604A	0.299	0.444	0.0064	0.0018	0.239	0.131	1.892	1.912	0.0111	.	.	0.0366	0.334	0.0046	0.0060	0.0069
1	SRM 1269	0.298	1.35	0.012	0.0061	0.189	0.095	0.108	0.201	0.016	.	.	.	0.036	.	.	0.004
1	ECRM 086-1D	0.297	0.879	0.024	0.037	0.206	0.320	0.168	0.150	.	.	0.023	.	.	.	0.026	.
2	CZ CM-3A	0.295	0.37	0.016	0.0013	0.27	0.16	1.82	1.87	0.05	.	0.005	0.012	0.33	0.007	0.007	0.007
1	VS UG9/10	0.294	0.616	.	(0.003)	0.235	0.169	0.144	0.170	0.280	.	.	.	0.282	0.015	0.0017	1.25
1	VS RG27/1	0.290	0.74	0.044	0.0043	0.28	0.208	0.142	1.83	1.07	.	.	0.025	0.191	.	.	0.072
1	IMZ 178	0.29	0.65	0.016	0.003	0.28	0.140	2.09	1.26	0.051	.	.	0.015	0.20	0.0160	0.011	0.011
1	SRM 1225	0.274	0.48	0.007	0.014	0.221	.	0.018	0.91	0.166	.	.	0.004
1	BS HiCal-1	0.271	1.00	(0.007)	0.0007	1.29	0.152	3.28	1.55	0.070	.	0.0022	0.0024	0.379	.	(0.0002)	0.0027
1	IARM 380A	0.268	1.24	0.021	0.025	0.181	0.265	0.114	0.192	0.0029	.	(0.007)	(0.010)	0.059	(0.012)	0.0117	0.0475
2	RM Fe 2/4	0.26	0.61	0.039	0.016	0.30	0.30	0.68	0.70	(0.001)	.	0.04	0.29	0.47	0.020	0.04	0.46
2	BS 69B	0.258	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.017	.	.	0.035	0.39	0.0057	0.006	(0.002)
1	12X 12750U	0.258	0.510	0.0078	0.0053	0.599	0.106	0.786	0.792	0.253	.	.	0.581	0.088	.	0.110	0.102
1	12X 32550A	0.257	1.350	0.0061	0.0054	1.59	0.108	1.750	0.377	0.0178	.	0.0054	.	0.417	0.0101	0.0206	0.0222
1	BS 6418	0.255	1.41	(0.010)	0.0041	1.54	0.109	1.74	0.34	0.029	.	(0.004)	0.010	0.42	0.007	(0.006)	(0.003)
1	IARM 380B	0.243	1.27	0.016	0.027	0.238	0.307	0.182	0.153	(0.0021)	.	0.0058	0.014	0.055	(0.013)	0.0132	0.049
2	HRT FE2018-N	0.24	0.74	0.012	(0.003)	0.29	0.06	0.43	1.46	0.017	.	.	.	0.75	.	0.0066	0.30
1	IMZ 113	0.24	0.50	0.022	0.025	0.10	0.11	0.13	1.25	0.007	0.004	.	.	0.050	0.0154	.	0.039
1	12X 722M24A	0.236	0.510	0.0135	0.0199	0.262	0.200	0.208	3.094	0.0187	.	0.0075	.	0.497	.	0.0116	0.0080
1	VS UG6/5	0.232	0.39	(0.006)	(0.008)	0.51	0.257	(0.2)	1.85	(0.4)	.	.	.	(0.2)	.	.	0.34
2	DSZU C043A	0.222	2.14	0.060	0.064	0.131	0.51	2.93	0.49	0.066	.	(0.001)	.	0.146	(0.009)	0.0023	0.25
1	IARM 229B	0.220	0.858	0.0073	0.0106	0.329	0.0153	0.030	0.017	0.025	.	(0.002)	0.0116	0.495	0.0072	0.0012	0.0059
1	ECRM 197-1D	0.219	0.792	0.0073	0.0232	0.275	0.152	0.148	0.451	0.0313	.	0.0083	0.0135	0.402	0.0114	0.0097	.
2	BS 3961	0.215	0.565	0.016	0.022	0.236	0.133	1.67	0.510	0.022	.	.	(0.010)	0.27	0.0079	(0.008)	(0.002)
1	DSZU C048	0.212	0.467	0.0102	0.0059	0.273	0.262	0.105	0.175	0.0293	.	0.0085	0.015	0.016	(0.011)	0.016	.
1	12X 86200-21	0.211	0.811	0.0128	0.0224	0.237	0.199	0.551	0.507	0.0241	.	0.0045	0.0072	0.190	0.0082	0.0094	0.0039
2	TL 1001	0.2108	0.8645	0.0141	0.0236	0.2141	0.1902	0.5378	0.5290	0.0191	.	(0.0051)	(0.0070)	0.1987	0.0102	0.0090	.
1	IPT 502	0.210	0.823	0.018	0.026	0.198	0.121	0.408	0.485	0.024	.	.	0.0083	0.155	0.0069	.	.
1	BS 8620G *	0.21	0.80	0.009	0.02	0.26	0.19	0.58	0.57	0.027	.	0.005	0.008	0.21	0.008	0.009	0.002
1	VS UG4/11	0.21	0.59	0.024	0.0069	0.285	0.074	0.173	1.21	0.032	.	.	0.0108	0.87	0.020	.	0.78
1	IARM 33D	0.209	0.593	0.009	0.023	0.207	0.072	1.78	0.139	0.026	.	0.0035	0.008	0.229	0.0053	0.005	0.002
1	BS 3952	0.208	0.543	0.011	0.021	0.263	0.201	0.111	0.104	0.048	.	<0.005	(0.003)	0.525	0.0006	(0.0009)	0.0014
1	ECRM 187-2D	0.2038	1.257	0.0066	(0.0300)	0.2111	0.1288	0.1755	1.132	0.0223	.	0.0057	0.0112	0.0623	0.0105	0.0237	0.0122
1	BS 4820A	0.203	0.64	0.008	0.014	0.185	0.212	3.28	0.116	0.029	.	0.006	0.008	0.203	0.0076	0.0097	0.0010

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Sn	V
1	12X 12747V	0.201	1.240	0.0648	0.0275	0.298	0.232	0.494	0.58	0.0271	.	0.0075	0.211	0.606	0.025	0.144	0.0272
1	VS RG31/1	0.200	0.191	0.0039	0.0058	0.28	0.39	2.12	1.28	0.30	.	.	0.273	0.30	.	.	0.200
1	KUT B3	0.20	0.14	(0.012)	0.025	0.53	0.25	.	5.94	1.16
1	VS UG5/5	(0.2)	0.52	(0.005)	(0.03)	0.145	0.37	0.42	1.42	0.19	.	.	.	0.44	.	.	0.29
1	IARM 155F	0.199	0.617	0.008	(0.013)	0.223	0.219	3.36	0.144	0.0356	.	(0.006)	0.012	0.244	(0.005)	0.0084	0.0015
1	IMZ 112B ##	0.195	0.43	0.022	0.016	0.27	0.055	0.046	0.034	(0.03)	.	.	.	0.043	0.010	0.15	0.045
1	VS UG8/10	0.192	1.81	0.0064	(0.005)	0.61	0.198	0.348	0.729	0.082	.	.	.	0.030	0.0185	0.0052	.
1	VS UG114	0.190	1.65	0.010	0.0074	0.59	0.173	0.345	1.03	0.146	.	.	.	0.016	.	.	0.0031
1	IMZ 162	0.19	1.31	0.021	0.014	0.59	0.077	1.64	0.91	(0.040)	.	.	.	0.52	.	.	0.045
1	VS UG113	0.189	1.55	0.0087	0.0070	0.59	0.185	0.186	1.12	0.263	.	.	.	0.010	.	.	0.0040
2	BS 4620	0.189	0.57	0.006	0.018	0.25	0.216	1.75	0.072	0.032	.	0.0084	0.012	0.24	0.0078	0.013	(0.0008)
1	BS 51F	0.188	0.519	0.016	0.017	0.24	0.231	1.68	0.156	0.022	.	(0.005)	0.0086	0.224	0.0061	0.008	0.0030
1	ECRM 192-1D	0.1875	1.377	0.0029	0.0010	0.219	0.0453	0.755	0.0717	0.0306	0.0285	.	0.0055	0.482	0.0118	.	.
1	VS UG112	0.186	1.63	0.0065	0.0050	0.60	0.157	0.185	0.98	0.026	.	.	.	0.021	.	.	0.014
2	BS LF3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.017	.	0.006	0.056	0.056	0.0054	0.006	(0.002)
2	HRT FE2012-N	0.18	0.70	0.010	0.008	0.31	0.14	0.13	0.25	0.030	.	.	.	0.26	.	.	.
1	ECRM 087-1D	0.174	0.671	0.010	0.046	0.263	0.171	0.118	0.078	.	.	0.024	0.015	0.021	.	0.017	.
1	12X 15180A	0.170	1.196	0.0110	0.0022	0.212	0.141	0.1030	0.118	0.018	.	0.0117	.	0.0231	0.0051	0.0115	.
1	ECRM 194-2D	0.1694	1.282	0.0137	0.00049	0.2974	0.0313	0.3316	0.760	0.0669	.	0.00208	0.00328	0.402	0.00319	.	0.00161
1	BS 3962	0.168	0.58	0.008	0.018	0.244	0.148	1.83	0.137	0.024	.	0.0053	0.0072	0.22	0.007	0.007	(0.0016)
1	VS UG7/11	0.164	0.293	0.0045	0.0062	0.39	0.468	2.09	1.31	0.276	.	.	0.291	0.298	0.014	.	0.208
2	BS XCCT	0.158	0.52	0.005	0.011	0.28	0.027	1.27	0.65	0.006	.	0.004	0.017	0.020	0.0076	(0.002)	0.031
1	IMZ 176A	0.15	0.75	0.018	0.003	0.35	0.103	3.62	0.41	(0.058)	.	.	(0.010)	0.027	0.0129	0.009	(0.061)
2	BS 15A	0.142	1.12	0.016	0.008	0.058	0.030	0.029	0.044	0.041	.	0.003	0.005	0.008	.	0.002	0.012
1	ECRM 193-1D	0.14	0.97	0.007	0.009	0.40	0.60	1.18	0.18	0.025	.	0.0062	0.007	0.35	0.0108	.	(0.002)
1	12X 15252R	0.137	0.321	0.044	0.044	0.097	0.153	2.03	0.96	0.035	.	.	0.153	0.247	0.020	0.047	0.298
2	BS 47A	0.130	0.44	0.017	0.015	0.27	0.11	0.12	4.22	0.015	.	.	0.011	0.47	0.018	0.008	0.016

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Sn	V
---	--------	---	----	---	---	----	----	----	----	----	-----	----	----	----	---	----	---

CRM LOW ALLOY STEEL WITH EXTENSIVE ANALYSIS analysis listed in mass % 31-34 mm ø x 19 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	Nb	Pb	Sn	Ta	Ti	V	W	Zr	
SRM 1264a	0.87	0.25	0.010	0.025	0.067	0.25	0.14	0.06	(0.008)	0.010	0.15	0.49	0.15	0.0022	(0.008)	0.11	0.24	0.10	0.10	0.069	
continued	analysis listed in mass %										analysis listed in mg/kg										
Number	B	Bi	Fe.diff	Ge	Sb	Te	Zn	Ag	Au	Ca	Ce	H	Hf	La	Mg	N	Nd	O	Pd	Se	Sr
SRM 1264a	(0.011)	(0.0009)	[96.7]	(0.003)	0.034	0.00018	(0.001)	(0.2)	1	0.4	2	(<5)	(13)	0.7	1.5	(32)	0.7	(10)	(0.3)	(2.1)	(5)

LOW ALLOY STEEL WITH 0.13 % < C < 0.3 %

CONTINUED FROM THE PREVIOUS PAGE

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
IARM 330A	0.0003	0.0010	.	.	(0.003)	(0.0009)	(0.0004)	(0.001)	.	0.006	(0.004)	.	0.0015	31 mm Ø x 2 mm
12X 16604A	-40 mm Ø x -15 mm
SRM 1269	0.005	32 mm Ø x 19 mm
ECRM 086-1D	38 mm Ø x 25 or 30 mm
CZ CM-3A	0.0002	.	.	.	0.006	0.006	0.015	.	.	-39 mm Ø x 25 mm
VS UG9/10	0.163	1.34	.	.	-45 mm Ø x -28 mm
VS RG27/1	0.110	0.170	.	.	-45 mm Ø x -28 mm
IMZ 178	0.105	0.017	.	.	40 mm Ø x 40 mm
SRM 1225	32 mm Ø x 19 mm
BS HiCal-1	(0.0001)	0.0140 [91.9]	(0.0003)	(0.002)	.	.	(0.0005)	.	.	0.0037	(0.0009)	.	(0.0008)	-38 mm Ø x -30 mm 17025
IARM 380A	(0.0020)	(0.009)	.	.	31 mm Ø x 2 or 18 mm
RM Fe 2/4	(0.0027)	<0.001	.	.	(0.011)	.	<0.02	<0.03	.	(0.0065)	0.19	.	<0.02	40 mm Ø x 40 mm
BS 69B	(0.002)	.	.	.	38 mm Ø x -7 or 19+ mm
12X 12750U	0.111	0.159	0.100	.	.	-40 mm Ø x -15 mm
12X 32550A	-38 mm Ø x -15 mm
BS 6418	0.0004	0.0002 [94.1]	0.0004	0.0022	0.0011	<0.005	(0.003)	<0.05	.	0.0036	<0.05	17025	<0.005	57 mm Ø x -7 or 19+ mm
IARM 380B	(0.0016)	0.0011	(0.003)	.	.	31 mm Ø x 2 or 18 mm
HRT FE2018-N	(0.0003)	36 mm Ø x 20 mm
IMZ 113	40 mm Ø x 40 mm
12X 722M24A	0.0028	.	-38 mm Ø x -15 mm
VS UG6/5	(0.01)	(0.01)	0.16	.	.	-45 mm Ø x -28 mm
DSZU C043A	(0.001)	0.0004	.	.	0.006	0.041	0.092	.	.	40 mm Ø x 25 mm
IARM 229B	(0.0006)	(0.0003)	.	.	(0.0019)	(0.0017)	(0.0005)	(0.0006)	(0.003)	0.0019	(0.003)	.	(0.0008)	31 mm Ø x 2 mm
ECRM 197-1D	0.0016	.	.	.	38 mm Ø x 25 mm
BS 3961	(<0.003)	44 mm Ø x -7 or 19+ mm
DSZU C048	.	(0.0017)	40 mm Ø x 25 mm
12X 86200-21	0.0014	.	.	0.0024	.	.	(0.003)	(0.0014)	.	38 mm Ø x 19 mm
TL 1001	(0.0134)	.	.	.	40 mm Ø x 20 mm
IPT 502	0.0016	.	.	.	36 mm Ø x 20 mm
BS 8620G *	<0.005	0.002 [97.1]	<0.005	0.002	0.004	<0.005	0.002	.	.	<0.005	0.003	.	<0.005	38 mm Ø x -7 or 19+ mm
VS UG4/11	0.071	0.034	0.0092	.	.	-45 mm Ø x -28 mm
IARM 33D	0.0002	(0.0003)	.	.	0.002	0.0013	<0.001	(0.002)	.	0.003	<0.005	.	<0.002	31 mm Ø x 2 or 18 mm
BS 3952	0.0003	<0.005	98.0	(0.00008)	<0.005	.	(0.0009)	0.0034	(0.003)	(0.002)	<0.005	17025	<0.005	39 mm Ø x -7 or 19+ mm
ECRM 187-2D	0.00048	0.0016	.	.	.	39 mm Ø x 28 mm
BS 4820A	0.0002	0.0003	.	0.0003	(0.002)	0.0011	(0.0002)	0.0024	.	0.0012	(0.002)	17025	.	38 mm Ø x -7 or 19+ mm

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
12X 12747V	0.099	0.0276	.	.	-40 mm Ø x -15 mm
VS RG31/1	0.21	0.39	.	.	-45 mm Ø x -28 mm
KUT B3	1.19	.	.	30-35mm Ø x 39 mm
VS UG5/5	(0.01)	(0.003)	0.38	.	.	-45 mm Ø x -28 mm
IARM 155F	0.0016	(0.003)	.	.	.	0.0020	(0.004)	.	.	31 mm Ø x 2 or 18 mm
IMZ 112B ## BACKORDERED	0.013	0.010	.	.	.	40 mm Ø x 40 mm
VS UG8/10	(0.003)	0.0034	.	.	.	-45 mm Ø x -28 mm
VS UG114	0.006	.	.	0.065	-45 mm Ø x -25 mm
IMZ 162	0.12	.	.	.	40 mm Ø x 40 mm
VS UG113	0.006	0.007	.	0.169	-45 mm Ø x -25 mm
BS 4620	0.00006	0.0001	.	0.0001	0.0001	0.0009	0.0002	0.0024	.	0.0026	0.0009	0.0002	.	38 mm Ø x -7 or 19+ mm
BS 51F	(0.0002)	(0.0005)[96.7]	.	(0.0001)	(0.0007)	(0.002)	(0.0008)	(0.003)	(0.005)	0.0012	(0.0024)	17025	(0.0009)	38 mm Ø x -7 or 19+ mm
ECRM 192-1D	-35 mm Ø x -30 mm
VS UG112	0.0028	0.005	.	0.0047	-45 mm Ø x -25 mm
BS LF3	0.0001	(0.0001)	.	.	.	0.004	38 mm Ø x -7 or 19+ mm
HRT FE2012-N	40 mm Ø x 20 mm
ECRM 087-1D	0.0046	38 mm Ø x 25 or 30 mm
12X 15180A	0.0016	.	-40 mm Ø x -20 mm
ECRM 194-2D	0.00155	.	.	.	0.0290	0.00322	.	.	.	39 mm Ø x 28 mm
BS 3962	<0.005	(0.00010)[96.6]	(0.00015)	(0.0014)	(0.002)	<0.005	(0.003)	<0.05	.	(0.002)	(0.004)	17025	(0.0011)	37 mm Ø x -7 or 19+ mm
VS UG7/11	0.20	0.385	.	.	-45 mm Ø x -28 mm
BS XCCT	(0.001)	(0.005)	(<0.001)	(0.0004)	.	(0.002)	.	.	(<0.002)	36 mm Ø x -7 or 19+ mm
IMZ 176A	(0.015)	.	.	40 mm Ø x 40 mm
BS 15A	(0.0002)	(0.0005)	.	.	0.041	.	(0.0003)	(0.003)	.	0.008	(0.004)	.	0.022	32 mm Ø x 17 mm last
ECRM 193-1D	0.0232	(0.0013)	.	.	.	40 mm Ø x 35 mm
12X 15252R	0.067	(0.0007)	(0.0013)	.	.	-40 mm Ø x -15 mm
BS 47A	0.002	(0.003)	.	.	.	0.003	.	.	.	38 mm Ø x -7 or 19+ mm

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
--------	---	----	----	----	----	---	----	----	----	----	---	----	----	-------

LOW ALLOY STEEL WITH C < 0.13 %

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Sn	V
1	IMZ 76	0.129	1.37	0.022	0.011	0.24	0.057	0.33	0.12	0.011	.	.	0.101	.	.	(0.006)
1	VS UG86	0.129	0.217	(0.005)	(0.007)	(0.3)	0.62	1.94	1.52	.	.	.	0.311	.	.	0.327
1	12X 15256Q	0.123	0.492	0.0125	0.0163	0.190	0.0550	5.33	0.362	0.1300	.	0.493	0.0740	0.0056	0.107	0.619
1	12X 93106A	0.122	0.605	0.0071	0.0103	0.206	0.199	3.255	1.107	0.0246	.	.	0.0879	0.0098	0.0094	0.0029
2	BS 47B	0.122	0.39	0.014	0.022	0.22	0.12	0.105	4.78	0.018	.	.	0.45	0.023	0.006	0.004
1	VS UG115	0.115	0.43	0.0084	0.012	0.227	0.173	1.63	0.81	0.024	.	.	0.0126	0.013	.	.
1	IMZ 75A	0.112	0.394	0.080	0.016	0.618	0.428	0.041	0.401	0.009	.	0.0037	0.018	0.0024	0.023	0.013
1	SRM 1138a	0.11	0.35	0.035	0.056	0.25	0.09	0.10	0.13	.	.	.	0.05	.	.	0.02
1	IPT 500	0.106	0.844	0.016	0.0048	0.282	0.270	0.018	0.612	0.046	.	0.0046	0.0013	0.0092	0.002	0.003
1	12X LALB	0.104	1.262	0.0090	0.060	0.777	0.0572	0.210	1.026	0.0104	.	0.0144	0.068	0.0144	.	0.448
2	BS 58E	0.100	0.63	0.009	0.002	0.29	0.154	3.22	1.40	0.029	.	0.013	0.110	0.0033	0.003	0.006
1	IMZ 175	0.099	0.25	0.016	0.0040	0.22	0.130	3.12	0.515	0.043	.	(0.013)	0.025	0.0099	0.011	0.014
2	BS 58C	0.098	0.57	0.011	0.014	0.29	0.14	3.20	1.29	(0.055)	.	.	0.11	.	(0.012)	.
1	IMZ 73	0.097	0.68	0.019	0.013	0.12	0.17	0.13	0.079	0.010	.	.	0.013	.	.	0.022
1	VS UG6/11	0.091	0.691	0.028	0.022	0.96	0.449	0.640	0.759	0.0107	.	0.0392	0.0082	0.0083	.	0.0075
1	KUT T3/2	0.09	0.60	0.058	0.033	0.66	0.10	0.11	0.40
1	IARM 268B	0.087	0.58	0.011	0.035	0.21	0.31	0.127	0.094	0.002	.	0.003	0.033	0.0015	0.010	0.047
1	IMZ 204	0.085	0.36	0.014	0.008	0.40	0.075	0.034	0.111	4.21	.	.	(0.007)	(0.0052)	.	.
1	SRM 1226	0.085	0.274	0.0022	0.0044	0.231	0.125	5.42	0.467	0.054	.	0.029	0.446	.	(0.003)	0.0018
1	DSZU C050	0.082	1.21	0.040	0.065	0.287	0.304	0.118	0.075	(0.008)	.	.	0.48	.	(0.004)	0.007
1	NCS HS20745	0.068	0.813	0.1	0.024	0.33	0.297	0.022
1	VS UG117	0.064	1.41	0.012	0.021	0.60	0.214	0.072	0.129	0.018	.	.	(0.005)	0.0085	.	.
1	SRM 1271	0.064	0.73	0.005	0.0013	0.334	1.48	3.34	0.552	0.020	.	.	0.543	.	.	0.003
1	SRM C1285	0.058	0.332	0.072	0.020	0.36	0.37	1.17	0.80	.	.	0.036	0.164	.	0.035	0.150
2	CZ CM-7A	0.05	1.17	0.011	0.016	0.56	0.09	0.05	0.10	0.13	.	0.007	0.015	0.01	0.008	0.012
1	SS 421	(0.049)	(0.11)	(0.012)	(0.027)	(0.07)	(0.028)	.	.	(<0.02)
1	VS UG82	0.046	1.83	(0.003)	(0.004)	0.334	0.056	0.201	0.59	.	.	.	0.93	.	.	0.56
1	VS UG97	0.041	0.59	0.0036	0.0025	0.194	0.0040	0.0048	0.0080	0.51	.	.	0.019	.	.	(0.001)
2	IARM 168A	0.003	0.12	0.030	0.064	0.46	0.009	2.32	0.004	0.19	.	0.003	0.69	0.0002	0.003	0.004
1	ECRM 064-2D	0.0026	0.1641	.	.	0.0065	0.0077	0.0115	.	.	.	0.0027	0.00077	0.0026	0.00051	0.00015

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Sn	V
	Number	As	B	Ca	Ce	Fe	Nb	O	Pb	Sb	Ti	W	Zr	Units		
	IMZ 76	.	(0.001)	.	.	.	0.068	.	.	.	(0.003)	.	.	40 mm Ø x 40 mm		
	VS UG86	~40 mm Ø x ~28 mm		
	12X 15256Q	0.0509	0.101	.	~40 mm Ø x ~15 mm		
	12X 93106A	0.0050	~38 mm Ø x ~15 mm		
	BS 47B	0.004	(0.004)	38 mm Ø x ~7 or 19+mm		
	VS UG115	0.0014	.	.	~45 mm Ø x ~25 mm		
	IMZ 75A	.	0.0021	.	.	.	0.024	.	.	.	0.023	.	.	38 mm Ø x 20 mm		
	SRM 1138a	32 mm Ø x 13 mm		
	IPT 500	0.0020	0.008	.	.	.	0.0014	.	.	34 mm Ø x 18 mm		
	12X LALB	0.0212	~40 mm Ø x ~15 mm		
	BS 58E	0.003	(0.0002)	(0.0002)	.	.	.	0.0008	.	.	(0.002)	.	.	38 mm Ø x ~7 or 19+mm		
	IMZ 175	(0.019)	.	40 mm Ø x 40 mm		
	BS 58C	no uncertainties	.	39 mm Ø x ~17 mm last		
	IMZ 73	(0.01)	.	.	.	(0.002)	.	(0.0025)	40 mm Ø x 40 mm		
	VS UG6/11	~45 mm Ø x ~28 mm		
	KUT T3/2	(<0.01)	.	.	30-35mm Ø x 39 mm		
	IARM 268B	<0.005	0.0011	.	.	.	0.006	(0.015)	<0.003	.	<0.001	0.01	<0.001	31 mm Ø x 2 mm		
	IMZ 204	0.035	.	.	36 mm Ø x 20 mm		
	SRM 1226	(0.005)	.	(0.0001)	.	0.0021	(0.005)	(0.010)	32 mm Ø x 19 mm		
	DSZU C050	(0.002)	(0.002)	(0.002)	.	.	40 mm Ø x 25 mm		
	NCS HS20745	.	.	.	0.014	.	.	La: 0.0076	35 mm Ø x 40 mm		
	VS UG117	0.018	.	.	~45 mm Ø x ~25 mm		
	SRM 1271	0.025	32 mm Ø x 19 mm		
	SRM C1285	.	.	.	0.021	32 mm Ø x 19 mm		
	CZ CM-7A	0.005	0.0003	.	.	.	0.004	.	(0.0014)	(0.0003)	0.14	0.01	0.042	~39 mm Ø x 25 mm		
	SS 421	0.52	.	38 mm Ø x 19 mm		
	VS UG82	~40 mm Ø x ~28 mm		
	VS UG97	0.154	.	.	~40 mm Ø x ~28 mm		
	IARM 168A	(0.003)	0.0004	.	.	.	0.003	0.0008	(<0.01)	.	0.004	0.52	.	31 mm Ø x 2 mm		
	ECRM 064-2D	0.0036	0.0146	.	0.00018	38 mm Ø x 25 or 30 mm		

LOW ALLOY STEEL XRF SET

Part Number: BS LAS-24 Set of 24 samples, each 35 - 45 mm ø x 7 mm discs CRM, 17025 others are RM

Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	Sn	V
300M	BS 4340M	0.414	0.74	0.004	<0.001	1.65	0.134	1.78	0.78	0.35	0.076	0.007	.	0.013	0.0020	0.009	0.056
1345	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.007	0.033	0.0023	.	0.006	0.0056	(0.0004)	(<0.003)
3115	BS XCCT	0.158	0.52	0.005	0.011	0.28	0.027	1.27	0.65	0.020	0.006	0.004	.	0.017	0.0076	(0.002)	0.031
4130	BS 3932	0.321	0.54	0.016	0.018	0.33	0.200	0.19	1.00	0.229	0.020	0.004	0.0043	0.011	0.0070	0.012	0.005
4140	BS 1962	0.41	0.94	0.007	0.011	0.242	0.224	0.16	1.05	0.229	0.018	0.007	.	0.008	0.0095	0.010	0.004
4150 + S	BS 42	0.516	1.24	0.021	0.073	0.235	0.252	0.183	0.67	0.190	0.020	(0.004)	.	0.012	0.0080	0.012	0.003
4330	BS 4330MOD	0.316	0.92	0.0052	0.0010	0.269	0.105	1.83	0.848	0.478	0.031	0.0038	(0.001)	0.034	0.0031	0.0062	0.083
4340	BS 4340	0.418	0.695	0.0119	0.0187	0.279	0.149	1.79	0.807	0.231	0.028	0.0043	0.0005	0.0068	0.0080	0.0063	0.0033
4615	BS 51E	0.15	0.59	0.010	0.021	0.28	0.22	1.75	0.14	0.21	0.028	.	.	0.035	0.0086	0.010	(0.0011)
4620	BS 4620	0.189	0.57	0.006	0.018	0.25	0.216	1.75	0.072	0.24	0.032	(0.0084)	(0.0001)	0.012	0.0078	0.013	(0.0008)
4820	BS 4820	0.188	0.57	0.010	0.025	0.25	0.11	3.29	0.12	0.21	0.020	0.005	0.0046	0.008	0.0079	(0.008)	(0.002)
6150	BS 43A	0.49	0.82	0.0074	0.025	0.252	0.18	0.24	0.92	0.059	(0.003)	(0.005)	(0.0006)	0.008	0.0072	0.011	0.145
8620	BS 1931	0.194	0.84	0.007	0.018	0.235	0.116	0.42	0.50	0.168	0.021	0.007	(0.0008)	0.012	0.0079	0.007	0.002
8822	BS 8822	0.228	0.92	0.011	0.025	0.26	0.17	0.47	0.52	0.34	0.022	0.007	(0.0004)	0.019	0.0085	0.011	0.003
8740	BS 67B	0.40	0.94	0.007	0.020	0.23	0.19	0.53	0.51	0.22	0.024	.	.	0.011	0.0078	0.009	(0.002)
9310	BS 58D	0.127	0.45	0.010	0.005	0.32	0.156	3.02	1.35	0.14	0.042	.	.	0.009	0.0147	0.012	0.005
9325	BS 9325	0.25	0.91	0.008	0.007	0.32	0.13	3.29	1.48	0.31	0.030	(0.004)	0.0049	0.010	0.0089	0.009	0.004
P-20	BS 55E	0.307	0.72	0.014	0.024	0.60	0.032	0.053	1.66	0.40	(0.004)	.	.	(0.005)	0.0096	0.002	0.019
AMS 6418	BS 69B	0.2258	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.39	0.024	.	.	0.035	0.0057	0.006	(0.002)
A193	BS 4942	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	0.54	(0.004)	0.005	0.0006	0.010	0.0080	0.014	0.28
A485-1	BS A485-1	0.98	1.10	0.019	0.004	0.62	0.16	0.13	1.07	0.029	0.017	0.006	.	0.010	0.0060	0.011	0.003
E52100	BS 53E	1.08	0.37	0.007	0.012	0.24	0.11	0.26	1.45	0.10	0.003	.	.	0.011	0.0086	0.005	0.004
Nitriding	BS 68C	0.38	0.60	0.018	0.008	0.305	0.178	0.166	1.77	0.36	1.06	(0.004)	(0.0002)	0.011	0.0045	0.008	0.007
LF 3	BS LF 3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.056	0.017	0.006	(0.0001)	0.056	0.0054	0.006	(0.002)

Alloy Number C Mn P S Si Cu Ni Cr Mo Al As Ca Co N Sn V
 ## this item sold out, most BS are available as XRF

CRM SOLUBLE ELEMENTS IN LOW ALLOY STEEL SET

available in set/7 only -S = Soluble, -T = Total 38 mm ø x 30 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al-S	Al-T	B-S	B-T	Mo
NCS HS11717a-1	0.0023	0.018	0.012	0.0027	0.0054	0.0036	0.011	0.023	0.0069	0.0078	0.0002	0.0004	0.0053
NCS HS11717a-2	0.0028	0.104	0.014	0.011	0.077	0.049	0.045	0.042	0.024	0.026	0.0011	0.0012	0.304
NCS HS11717a-3	0.032	0.303	0.018	0.067	1.55	0.403	0.563	0.236	0.295	0.298	0.0018	0.0020	0.034
NCS HS11717a-4	0.096	0.669	0.012	(0.050)	1.09	0.316	0.400	0.102	0.214	0.216	0.0085	0.0096	0.144
NCS HS11717a-5	0.243	1.04	0.030	0.042	0.769	0.248	0.393	0.106	0.101	0.104	0.0071	0.0074	0.105
NCS HS11717a-6	0.387	1.47	0.038	0.030	0.436	0.167	0.206	0.409	0.050	0.051	0.0047	0.0049	0.071
NCS HS11717a-7	0.498	2.10	0.050	0.022	0.176	0.075	0.107	0.612	0.022	0.024	0.0031	0.0033	0.196

Number	As	Bi	Co	N	Nb	Pb	Sb	Sn	Ti	V
NCS HS11717a-1	0.0034	(<0.00001)	0.0015	0.0016	(<0.0005)	(<0.0001)	0.00041	0.00020	0.0002	(0.0001)
NCS HS11717a-2	0.011	(<0.00001)	0.058	0.0017	0.031	(<0.0001)	0.00031	0.00073	0.020	0.011
NCS HS11717a-3	0.019	(<0.00001)	0.099	0.0032	0.079	(<0.0001)	0.00041	0.016	0.049	0.052
NCS HS11717a-4	0.073	(0.00001)	0.146	0.0031	0.223	(<0.0001)	0.00044	0.049	0.202	0.098
NCS HS11717a-5	0.071	(0.00001)	0.296	0.0048	0.318	(<0.0001)	0.00052	0.099	0.178	0.257
NCS HS11717a-6	0.045	(0.00001)	0.248	0.0049	0.106	(<0.0001)	0.00048	0.151	0.124	0.201
NCS HS11717a-7	0.034	(0.00001)	0.198	0.0063	0.153	(<0.0001)	0.00050	0.197	0.088	0.147

RM TOOL STEEL XRF SET

Part Number: BS TS-18 AVAILABLE INDIVIDUALLY 17025 ~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N
A-2	BS 36C	0.96	0.46	0.023	0.027	0.31	0.18	0.19	5.01	0.99	.	(0.04)	0.11	0.03	.
A-10	BS A-10	1.41	1.75	0.016	0.022	1.15	0.16	1.82	0.24	1.53	0.006	<0.005	(0.004)	(0.010)	.
D-2	BS 37D	1.54	0.28	0.021	0.015	0.29	0.063	0.21	11.07	1.09	.	0.16	0.80	0.07	0.016
H-10	BS 49	0.36	0.33	0.014	0.015	0.92	0.072	0.20	3.51	2.41	0.004	0.31	0.62	2.00	0.0186
H-11	BS TH11	0.423	0.31	0.016	0.005	0.88	0.041	0.11	5.04	1.27	.	(0.01)	0.46	(0.008)	.
H-12	BS TH12	0.372	0.40	0.020	0.005	0.92	0.064	0.16	5.02	1.41	.	1.06	0.62	0.07	.
H-13	BS 34D	0.395	0.38	0.017	0.005	1.06	0.049	0.10	5.15	1.24	.	0.10	0.94	0.031	.
L-6	BS 39B	0.67	0.62	0.009	0.019	0.214	0.163	1.45	0.79	0.17	(0.011)	.	(0.01)	(0.02)	.
M-1	BS TM1	0.86	0.23	0.007	0.012	0.46	0.054	0.057	3.72	8.4	.	1.7	1.05	0.45	.
M-2	BS 32C	0.84	0.29	(0.018)	0.0010	0.29	0.13	0.35	3.98	4.85	(0.02)	6.3	2.03	0.31	.
O-1	BS 35D	0.879	1.13	0.021	0.024	0.22	0.141	0.132	0.495	0.035	(0.005)	0.46	0.181	0.012	.
O-6	BS 41	1.41	0.89	0.013	0.011	1.02	0.038	0.15	0.22	0.23	(0.007)	0.035	0.046	.	.
S-1	BS 33E	0.49	0.29	0.022	0.005	0.20	0.038	0.08	1.25	0.045	.	2.75	0.19	0.006	.
S-5	BS 38C	0.60	0.81	0.011	0.012	2.08	0.26	0.24	0.28	0.41	0.015	0.004	0.214	0.036	0.0081
S-7	BS TS7	0.529	0.70	0.016	0.010	0.27	0.05	0.10	3.18	1.34	.	0.19	0.35	0.043	.
T-1	BS 30D	0.745	0.348	0.029	0.0010	0.301	0.116	0.191	3.93	0.342	0.0123	17.73	1.077	0.101	0.0168
	BS 10V	2.46	0.52	0.019	0.079	0.89	0.076	0.08	5.41	1.30	<0.002	0.013	9.50	0.009	0.064
HP9-4-30	BS 9-4-30	0.30	0.22	0.008	<0.001	0.06	0.09	7.25	1.00	1.00	0.004	0.01	0.085	4.40	0.0015

TOOL STEEL

CONTINUED ON THE NEXT PAGE

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

Table with 17 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Co, Mo, N, Ti, V, W, Al. Rows include various tool steel grades like BS PM15, BS 10V, DSZU C070, BS A-11, etc.

Table with 17 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Co, Mo, N, Ti, V, W, Al. Rows include various tool steel grades like IARM 40B, BS 39B, DSZU C078, etc.

ALUMINUM IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	Al	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	Ti	V
1	IMZ 158	1.56	0.24	25.51	0.091	1.34	0.015	0.007	2.23	0.097	.	0.025	.	.	0.12	0.078
1	13X PH17700A	1.172	6.98	16.88	0.0732	0.496	0.0181	0.0008	0.551	0.146	0.0464	0.340	0.0192	0.0201	0.051	0.0390
1	BS 192	1.17	7.11	16.44	0.074	0.835	0.025	0.0005	0.387	0.412	0.104	0.430	0.0290	0.168	0.076	0.124
2	CT X92834	1.14	8.32	12.57	0.035	0.044	0.003	0.003	0.019	0.030	0.030	2.20	.	0.001	0.019	<0.004
1	IARMPe177PH-18	1.09	7.11	17.08	0.080	0.730	0.020	(0.0005)	0.51	0.36	0.048	0.350	0.0153	0.009	0.083	0.062
1	13X PH13800A	1.075	8.04	12.53	0.0386	0.0332	0.0064	0.0030	0.081	0.0449	0.0220	2.10	0.0041	.	0.0122	0.0188
1	IARM 21D	1.03	8.29	12.69	0.032	0.052	0.008	(0.0014)	0.039	0.017	0.078	2.23	0.0037	(0.0005)	0.016	0.017
2	BS 184A	1.00	8.34	12.66	0.035	0.06	0.007	0.001	0.080	0.041	0.036	2.20	0.0045	(0.0006)	0.051	0.014
1	BS 192A	0.98	7.01	16.44	0.066	0.768	0.021	<0.002	0.300	0.334	0.114	0.28	0.029	0.208	0.083	0.077
1	IARM 152C	0.94	7.30	16.99	0.072	0.74	0.024	0.0006	0.263	0.316	0.113	0.36	0.0172	0.012	0.098	0.072

Number	As	B	Ca	O	Sn	Ta	W	Zr	Units
IMZ 158	40 mm Ø x 40 mm
13X PH17700A	.	0.0033	.	.	0.0055	.	0.009	.	-38 mm Ø x -15 mm
BS 192	(0.005)	(0.0003)	0.0007	0.0014	0.008	(0.001)	0.05	.	38 mm Ø x ~7 or 19+ mm 25(pre-17025)
CT X92834	.	0.0009	.	.	0.002	.	.	<0.001	30-35 mm Ø x x ~19 mm last of stock
IARMPe177PH-18	.	(0.0017)	.	.	(0.006)	.	(0.011)	.	31 mm Ø x 2 or 18 mm
13X PH13800A	0.0051	.	.	.	-38 mm Ø x ~15 mm
IARM 21D	(0.012)	.	31 mm Ø x 2 or 18 mm
BS 184A	.	(0.0004)	(0.0003)	(0.0003)	(0.002)	.	0.032	.	38 mm Ø x ~7 or 19+ mm
BS 192A	(0.0035)	(0.0003)	(0.0006)	(0.0006)	0.008	.	0.048	.	38 mm Ø x ~7 or 19+ mm 25(pre-17025)
IARM 152C	(0.004)	0.0029	(0.0005)	(0.001)	0.007	(0.005)	0.026	.	31 mm Ø x 2 mm

CALCIUM IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	Ca	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	V	W
1	BS Ca304-4	0.0075	8.77	18.26	0.096	0.783	0.0205	0.0070	0.887	0.143	(0.007)	0.0041	0.061	0.063	0.0686	0.0056
1	13X 14923A	0.0044	0.452	11.26	0.205	0.501	0.0197	0.0031	0.330	0.0563	0.0207	0.819	0.0321	0.005	0.295	.
1	ECRM 379-1D	0.0033	30.83	26.79	0.0121	1.804	0.0166	0.0006	0.393	0.984	0.0390	3.290	0.0550	(0.0028)	0.0663	(0.0091)
2	BS 193	0.0020	1.82	18.48	0.104	12.11	0.018	0.002	0.66	0.088	0.028	0.21	0.37	0.014	0.107	(0.007)
2	BS SS4952	0.0019	0.23	13.15	0.347	0.41	0.016	0.003	0.66	0.045	0.030	0.049	0.027	0.004	0.089	(0.007)
2	BS 82E	0.0014	12.49	22.38	0.062	1.61	0.027	0.001	0.58	0.26	0.12	0.31	0.072	0.062	0.064	0.041
1	BS 9942	0.0014	13.55	18.21	0.021	1.84	0.025	0.006	0.49	0.305	0.086	3.30	0.071	0.005	0.072	0.032
1	BS 9842	0.0010	20.02	24.19	0.059	1.50	0.025	0.0016	0.99	0.147	0.237	0.111	0.037	0.026	0.075	0.011
1	ECRM 272-1D	0.00090	0.2445	11.927	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.0145	0.0030	0.0508	0.0028	0.0167	.
2	BS 94C	0.0008	0.43	25.90	0.057	0.45	0.024	0.002	0.62	0.056	0.042	0.20	0.065	0.032	0.12	(0.03)
2	BS 87F	0.0007	10.12	17.30	0.055	1.64	0.024	0.025	0.67	0.28	0.17	0.29	0.037	0.57	0.13	0.050

Number	Al	As	B	O	Pb	Sb	Sn	Ti	Zn	Units
BS Ca304-4	0.017	0.0063	0.0031	0.013	0.0008	(0.0002)	0.0024	0.0046	Zr:0.0036	~38 mm Ø x ~38mm Fe: 70.7 17025
13X 14923A	0.003	0.004	.	.	~40 mm Ø x ~15 mm
ECRM 379-1D	(0.00246)	(0.0018)	0.00190	(0.0027)	(0.000038)	0.00057	0.0021	(0.0014)	.	38 or 45 mm Ø x 25 mm
BS 193	(0.003)	.	0.0007	(0.004)	.	.	0.004	0.003	.	32 mm Ø x ~7 or 19+ mm
BS SS4952	0.003	0.002	(0.0004)	0.005	.	.	0.004	0.002	.	38 mm Ø x ~7 or 19+ mm
BS 82E	0.006	.	0.0024	.	.	.	0.006	0.003	.	38 mm Ø x ~7 to 19 mm
BS 9942	0.004	(0.004)	0.0014	(0.0023)	.	.	0.006	(0.002)	.	44 mm Ø x ~7 or 19+ mm
BS 9842	0.014	(0.002)	0.0025	(0.0044)	.	.	0.005	0.003	.	38 mm Ø x ~7 or 19+ mm 25(pre-17025)
ECRM 272-1D	0.0046	0.0116	0.0018	.	.	0.0007	.	0.00096	0.0031	38 mm Ø x 25 or 30 mm
BS 94C	0.004	.	(0.0005)	0.0061	.	.	0.006	.	.	44 mm Ø x ~7 or 19+ mm
BS 87F	0.004	0.005	(0.0006)	0.005	.	.	0.004	0.004	.	41 mm Ø x ~7 or 19+ mm

COPPER IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

#	Number	Cu	Ni	Cr	C	Mn	P	S	Si	Co	Mo	N	Nb	Ti	V	W
1	13X PH 3N	5.83	3.03	16.0	0.110	0.39	0.0136	0.019	1.25	0.306	0.74	0.111	0.45	0.0193	0.246	.
1	13X PH 4P	5.53	4.07	15.5	0.033	0.69	0.021	0.019	0.64	0.50	0.255	0.082	0.355	0.075	0.55	.
1	13X PH 2M	4.03	3.56	16.80	0.0598	1.184	0.0201	0.0419	0.502	0.0927	1.009	0.052	0.143	0.049	0.1028	.
2	BS 9621	3.42	4.61	14.93	0.035	0.31	0.017	0.0011	0.468	0.029	0.063	0.013	0.27	(0.001)	0.096	(0.01)
2	BS 185A	3.41	4.43	14.46	0.033	0.49	0.022	0.002	0.38	0.026	0.30	0.027	0.32	(0.001)	0.048	(0.014)
1	BS 17-4PHB	3.35	4.52	15.60	0.042	0.559	0.022	0.023	0.43	0.040	0.110	0.047	0.315	0.0045	0.061	(0.02)
2	BS 9622	3.34	4.34	14.34	0.032	0.63	0.019	0.004	0.42	0.040	0.27	0.028	0.33	(0.001)	0.074	(0.020)
2	BS 17-4PHA	3.30	4.69	15.40	0.018	0.85	0.023	0.022	0.40	0.072	0.34	0.022	0.204	.	0.043	.
2	CT 20 Cb-3	3.28	33.55	19.63	0.034	0.19	0.017	0.003	0.38	0.035	2.25	.	0.86	.	0.053	.
2	CT 630	3.25	4.20	15.94	0.036	0.39	0.018	0.013	0.63	0.11	0.11	0.028	0.36	.	0.022	.
1	BS 17-4PHC	3.23	4.24	15.40	0.033	0.81	0.022	0.027	0.399	0.077	0.45	0.027	0.258	(0.001)	0.090	0.121
2	BS 187A	3.10	33.06	19.75	0.022	0.52	0.017	0.0025	0.26	0.32	2.06	0.0157	0.57	(0.002)	0.10	(0.02)
1	ECRM 273-1D	3.046	4.85	14.747	0.0336	0.785	0.0131	0.004	0.378	0.0391	0.2462	0.0444	0.221	.	0.0512	.
1	VS LG64	2.88	28.3	24.7	0.049	0.75	0.017	0.0032	0.76	.	2.89	.	0.048	0.64	0.094	0.013
1	SRM C2400	2.63	4.07	17.06	0.036	0.71	0.013	0.003	0.61	0.10	0.23	.	0.15	.	0.092	.
2	CT 455	2.32	8.22	11.37	0.012	0.074	0.010	0.005	0.13	.	0.027	0.002	0.28	1.18	.	.
2	BS SS1962	2.22	8.32	11.42	0.008	0.06	0.006	0.0025	0.06	(0.015)	0.008	0.0025	0.27	1.11	0.071	(<0.02)
1	13X 45500A	2.20	8.36	11.39	0.0041	0.0263	0.0049	0.0020	0.059	0.0152	0.0185	0.0030	0.250	1.187	0.0689	.
1	IARM 16C	2.08	8.23	11.34	0.003	0.024	0.007	0.0046	0.03	0.017	0.009	0.0030	0.248	1.16	0.070	0.008
1	SS 475	1.94	5.66	14.14	0.050	0.89	0.037	0.008	0.21	0.22	1.59	.	0.22	.	.	.
1	BS 9812	1.65	6.61	14.82	0.031	0.485	0.018	0.004	0.43	0.110	0.76	0.0195	0.645	(0.005)	0.088	0.025
1	BS 9811	1.63	6.55	14.87	0.027	0.380	0.016	0.0010	0.36	0.055	0.744	0.0196	0.62	(0.003)	0.086	0.013
1	IARM 318B	1.63	5.71	15.9	0.050	1.02	0.022	0.0006	0.41	0.100	1.57	0.032	0.086	0.014	0.115	0.087
1	13X PH2S143A	1.61	5.20	13.45	0.044	0.544	0.0205	0.0022	0.478	0.0475	1.325	0.024	0.222	.	0.087	0.019
1	BS 179B	1.56	6.17	25.9	0.0161	0.890	0.0243	0.0002	0.371	0.0394	3.34	0.239	0.008	(0.0008)	0.079	0.053
1	IARM 15C	1.54	6.35	14.39	0.032	0.760	0.019	0.0018	0.26	0.024	0.722	0.0148	0.63	(0.002)	0.041	(0.020)
1	13X NSA 7B	1.53	6.37	25.69	0.013	0.864	0.0160	0.0005	0.278	0.047	3.28	0.232	(0.009)	.	0.080	0.133
1	BS 179C	1.53	6.10	25.9	0.0164	0.878	0.0236	0.0003	0.373	0.0386	3.34	0.236	0.009	(0.0005)	0.080	0.056
1	BS 450	1.51	6.24	14.4	0.029	0.596	0.016	0.0013	0.323	0.028	0.671	0.022	0.59	<0.008	0.051	0.016
2	CT 450	1.49	6.36	15.20	0.036	0.39	0.014	0.006	0.29	0.16	0.80	0.028	0.67	.	0.043	.
1	ECRM 295-1D	1.481	24.40	19.51	0.0166	1.758	0.0167	0.0004	0.418	0.0450	3.996	0.0615	.	.	0.0453	.
1	IARM 239B	1.48	5.78	25.9	0.013	0.86	0.025	0.0005	0.39	0.048	3.42	0.25	0.024	0.002	0.099	0.106
2	HRT FE2004-H	1.33	24.25	19.08	0.021	1.83	0.021	0.004	0.47	0.046	4.17	.	0.046	0.005	0.042	.
1	13X PH 7F	0.77	5.41	13.16	0.118	1.487	0.028	0.0057	1.402	0.049	2.52	0.044	0.241	0.0196	0.043	.

Number	Al	Ag	As	B	Ca	Cd	Fe	Mg	O	Pb	Sb	Sn	Ta	Units
13X PH 3N	0.050	.	.	0.0042	~40 mm Ø x ~15 mm
13X PH 4P	0.029	.	.	0.0031	~40 mm Ø x ~15 mm
13X PH 2M	0.0419	.	.	0.0047	~40 mm Ø x ~15 mm
BS 9621	0.003	.	.	0.0004	(0.0001)	0.003	(0.002)	38 mm Ø x ~7 or 19+ mm
BS 185A	0.002	.	.	0.0017	(0.0002)	.	.	.	(0.0021)	.	.	0.007	(0.002)	38 mm Ø x ~7 or 19+ mm
BS 17-4PHB	0.034	.	(0.003)	0.0036	(0.0004)	17025	[74.8]	(0.0002)	(0.002)	(0.001)	(0.002)	0.012	(0.002)	41 mm Ø x ~7 or 19+ mm
BS 9622	0.002	.	.	0.0004	0.006	.	38 mm Ø x ~7 or 19+ mm
BS 17-4PHA	.	.	.	0.0016	(0.002)	38 mm Ø x ~7 or 19+ mm
CT 20 Cb-3	.	0.0019	.	0.0023	0.002	.	0.003	.	30-35 mm Ø x ~19 mm
CT 630	.	0.0004	.	0.0018	0.001	.	0.007	.	30-35 mm Ø x ~16 mm
BS 17-4PHC	0.0023	.	0.0043	0.0026	0.0007	17025	74.8	.	0.010	(0.0001)	.	0.0100	.	44 mm Ø x ~7 or 19+ mm
BS 187A	(0.009)	.	.	0.0022	0.0029	last of stock	.	0.003	<0.002	41 mm Ø x ~7 mm
ECRM 273-1D	.	.	0.0030	0.0021	.	40 mm Ø x 20 mm
VS LG64	0.189	~47 mm Ø x ~30 mm
SRM C2400	32 mm Ø x 19 mm
CT 455	.	0.0002	.	0.0024	<0.001	.	0.004	.	30-35 mm Ø x ~19 mm
BS SS1962	0.067	.	0.002	0.0018	(0.001)	.	.	0.004	.	38 mm Ø x ~7 or 19+ mm
13X 45500A	0.073	0.0048	(0.0050)	~38 mm Ø x ~15 mm
IARM 16C	0.072	.	(0.003)	0.0011	0.0014	.	.	(0.003)	.	31 mm Ø x 2 or 18 mm
SS 475	0.013	0.015	.	38 mm Ø x 19 mm
BS 9812	(0.002)	.	(0.005)	(0.0003)	0.0012	.	.	.	(0.007)	25(pre-17025)	.	0.004	.	50 mm Ø x ~7 or 19+ mm
BS 9811	(0.003)	.	(0.003)	(0.0003)	0.0014	.	.	.	(0.0060)	25(pre-17025)	.	0.004	.	38 mm Ø x ~7 or 19+ mm
IARM 318B	(0.004)	.	(0.004)	0.0003	0.009	.	.	0.004	(0.004)	31 mm Ø x 2 or 18 mm
13X PH2S143A	~40 mm Ø x ~15 mm
BS 179B	0.0070	.	0.0036	0.0015	(0.0004)	17025	[61.5]	(0.0004)	0.0037	(0.00002)	0.0005	0.0019	(0.0006)	38 mm Ø x 19+ mm
IARM 15C	(0.005)	.	0.0044	(0.0006)	(0.0004)	.	.	.	(0.003)	(0.003)	(0.003)	0.009	(0.004)	31 mm Ø x 2 or 18 mm
13X NSA 7B	0.0142	.	.	0.0018	0.0009	0.0020	.	.	~41 mm Ø x ~15 mm
BS 179C	0.0078	.	0.0034	0.0015	(0.0003)	17025	[61.6]	(0.0004)	0.0038	(0.00002)	0.0005	0.0018	(0.0006)	38 mm Ø x ~7 or 19+ mm
BS 450	(0.003)	.	0.0033	(0.0003)	<0.005	17025	75.5	.	0.0027	<0.005	0.0010	0.0046	.	44 mm Ø x ~7 or 19+ mm
CT 450	.	0.0013	0.001	.	0.008	.	30-35 mm Ø x ~15-19 mm
ECRM 295-1D	0.0203	.	0.0041	0.0018	.	.	48.36	(0.0003)	.	.	.	0.0007	0.0025	38 mm Ø x 25 or 30 mm
IARM 239B	0.008	.	0.0008	(0.004)	.	.	(0.003)	.	31 mm Ø x 2 mm
HRT FE2004-H	0.005	.	.	0.0021	32 mm Ø x 20 mm
13X PH 7F	0.012	~40 mm Ø x ~15 mm

SULFUR AND PHOSPHORUS IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	S	P	Ni	Cr	C	Mn	Si	Cu	Al	Co	Mo	N	Nb	Ti	V
2	CT 416	0.36	0.018	0.24	13.15	0.088	0.52	0.63	0.004	.	0.019	0.065	0.020	.	.	0.025
2	BS 150	0.33	0.020	0.19	18.61	0.048	1.71	0.43	0.042	0.002	0.024	1.97	0.029	0.003	.	0.054
1	SRM 1223	0.329	0.018	0.232	12.64	0.127	1.08	0.327	0.081	.	.	0.053	.	.	.	0.068
2	BS 90F	0.328	0.023	0.30	13.01	0.085	0.53	0.58	0.12	(0.006)	0.021	0.14	0.037	0.011	.	0.076
1	BS 303	0.326	0.028	8.17	17.23	0.044	1.80	0.415	0.627	0.0019	0.071	0.410	0.023	0.008	0.017	0.056
1	13X 30300A	0.312	0.0205	8.60	17.62	0.041	1.83	0.422	0.025	.	0.0255	0.334	0.034	.	.	0.091
2	CT 303	0.31	0.029	9.08	17.78	0.070	1.64	0.58	0.49	.	0.16	0.41	.	.	.	0.044
1	IARM 355A	0.31	0.0186	0.427	17.81	0.0274	0.47	0.435	0.083	0.0016	0.047	0.337	0.0439	0.0095	0.0020	0.038
2	BS 154	0.302	0.027	0.25	17.58	0.030	0.40	1.26	0.063	(0.002)	0.019	0.31	0.039	0.005	.	0.046
2	13X 12549K	0.29	0.092	1.26	11.70	0.16	0.34	0.43	0.10	.	0.52	1.49	.	0.23	.	.
2	BS 153	0.280	0.018	0.140	17.38	0.026	0.41	0.53	0.052	0.002	0.017	0.30	0.021	0.002	(0.004)	0.045
2	BS 152	0.275	0.022	0.14	13.41	0.320	0.36	0.44	0.050	(0.002)	0.015	0.061	0.020	0.006	.	0.051
3	CZ SP-1A	0.26	0.024	8.6	17.7	0.047	1.87	0.33	0.52	0.004	0.095	0.42	.	0.012	0.02	0.058
1	IARM 352A	0.21	0.0182	0.269	13.11	0.341	1.13	0.357	0.148	(0.0025)	(0.016)	0.38	0.029	(0.012)	0.0015	0.028
1	13X 43020A	0.189	0.0246	0.517	16.07	0.147	1.439	0.415	0.0687	0.0047	0.0191	0.226	0.0212	0.0102	.	0.0542
1	IMZ 154	0.16	0.040	9.86	17.71	0.076	2.18	0.89	0.33	(0.16)	0.105	2.58	.	.	1.00	0.073
1	NCS HS41751A	0.16	0.035	8.07	17.41	0.075	1.70	0.71	0.26	.	0.13	0.33	0.077	.	.	0.068
2	BS 155	0.145	0.014	0.13	16.64	1.00	0.35	0.40	0.035	(0.001)	0.019	0.46	0.032	0.002	.	0.10
1	13X 12536T	0.090	0.0449	12.12	16.09	0.146	0.374	0.546	0.0793	0.108	0.280	2.48	0.0084	0.060	0.444	0.0513
1	SRM C1154a	0.051	0.06	13.08	19.31	0.100	1.44	0.53	0.44	.	0.38	0.068	.	.	.	0.135
1	VS LG58	0.0280	0.0135	4.26	23.4	0.48	0.99	0.292	0.388	.	.	2.41	.	0.214	0.039	0.264
1	13X 19004C	0.0135	0.074	17.90	22.77	0.075	2.01	0.35	0.0112	0.030	0.0501	3.43	.	0.152	.	0.041

Number	Ag	As	B	O	Pb	Sn	Ta	W	Units
CT 416	0.0002	.	.	.	<0.001	0.005	.	.	30-35 mm Ø x ~16 mm
BS 150	.	.	.	0.012	.	(0.003)	.	0.01	35 mm Ø x ~7 or 19+ mm
SRM 1223	32 mm Ø x 19 mm
BS 90F	.	.	.	0.011	.	0.005	.	0.032	38 mm Ø x ~7 to 19 mm last
BS 303	.	.	0.0013	0.0058	.	0.0091	.	0.023	44 mm Ø x ~7 or 19+ mm 17025
13X 30300A	.	.	0.0035	~40 mm Ø x ~15 mm
CT 303	0.0003	.	.	.	0.001	0.007	.	.	30-35 mm Ø x ~16 mm
IARM 355A	.	(0.004)	(0.0011)	(0.010)	(0.0002)	(0.005)	.	(0.018)	31 mm Ø x 2 or 18 mm
BS 154	.	.	.	0.008	.	(0.005)	.	(0.01)	38 mm Ø x ~7 or 19+ mm
13X 12549K	40 mm Ø x 15 mm
BS 153	.	(0.004)	.	.	(0.001)	0.002	.	(0.002)	35 mm Ø x ~7 or 19+ mm
BS 152	0.003	.	<0.01	41 mm Ø x ~7 or 19+ mm
CZ SP-1A	.	0.006	0.0007	.	.	0.01	.	0.03	~39 mm Ø x 25 mm
IARM 352A	.	(0.005)	(0.0007)	(0.005)	.	0.0046	.	(0.005)	31 mm Ø x 2 or 18 mm
13X 43020A	.	.	(0.0032)	0.0108	~40 mm Ø x ~15 mm
IMZ 154	40 mm Ø x 40 mm
NCS HS41751A	38 mm Ø x 38 mm
BS 155	.	.	.	0.0048	.	(0.003)	.	.	36 mm Ø x ~7 or 19+ mm
13X 12536T	.	.	0.0214	.	.	0.0068	0.104	.	~40 mm Ø x ~15 mm
SRM C1154a	0.017	.	.	.	32 mm Ø x 19 mm
VS LG58	0.21	~47 mm Ø x ~30 mm
13X 19004C	.	.	(0.001)	.	.	(0.001)	0.011	.	~40 mm Ø x ~15 mm

SELENIUM IN STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

#	Number	Se	Ni	Cr	C	Mn	P	S	Si	Cu	Al	Co	Mo	N	Nb	Ti
2	BS 151	0.328	0.24	13.19	0.090	0.41	0.021	0.018	0.65	0.11	(0.002)	0.018	0.088	0.022	0.005	(<0.003)
2	BS 186A	0.229	35.86	0.16	0.040	0.72	0.008	0.0053	0.19	0.016	(0.001)	0.028	0.0032	0.0026	(<0.002)	(<0.003)
1	IARM 253A	0.21	9.17	17.90	0.041	1.50	0.140	0.0089	0.50	0.223	0.003	0.088	0.348	0.0373	0.016	0.002
1	IARM 24B	0.19	35.86	0.121	0.053	0.82	0.009	0.0010	0.28	0.052	0.002	0.036	0.011	0.0017	<0.01	0.002
1	IARM 353A	0.17	0.265	17.01	0.98	0.95	0.019	0.025	0.49	0.13	0.0018	0.032	0.50	0.027	(0.011)	0.0015
2	CT ISO124A	0.167	48.07	0.079	0.011	0.73	0.007	0.006	0.40	0.015	.	0.012	0.009	.	.	.
2	BS 156	0.142	0.35	16.87	1.06	1.15	0.022	0.007	0.47	0.09	(<0.002)	0.047	0.50	0.041	0.005	0.001
1	IARM 253B	0.13	9.11	17.64	0.051	1.61	0.13	0.011	0.46	0.44	(0.004)	0.145	0.59	0.031	0.021	0.0027

Number	B	Fe	O	Sn	Ta	V	W	Zr	Units
BS 151	.	.	0.009	0.005	.	0.046	0.010	.	50 mm Ø x ~7 or 19+ mm
BS 186A	.	.	.	(0.002)	.	0.0012	(0.01)	.	38 mm Ø x ~7, ~12 or 19 mm
IARM 253A	0.0003	.	0.009	0.01	.	0.106	0.10	.	31 mm Ø x 2 or 18 mm
IARM 24B	(0.001)	62.6	0.003	0.0018	<0.005	<0.005	<0.04	<0.005	31 mm Ø x 2 or 18 mm
IARM 353A	(0.0006)	.	(0.005)	0.0056	(0.004)	0.116	0.041	(0.002)	31 mm Ø x 2 mm
CT ISO124A	.	50.65	44-47 mm Ø x ~11 or ~19 mm
BS 156	.	.	0.0045	(0.004)	.	0.13	0.11	.	41 mm Ø x ~7 or 19+ mm
IARM 253B	0.0007	.	0.007	(0.012)	(0.003)	0.092	(0.05)	.	31 mm Ø x 2 or 18 mm

STAINLESS STEEL WITH C > 0.05 %

CONTINUED FROM THE PREVIOUS PAGE

Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units
VS LG76	0.034	-45 mm Ø x -28 mm
VS LG74	0.035	-45 mm Ø x -28 mm
KUT S21	30-35 mm Ø x 18 mm last
CZ CM-19A	0.0788	.	(0.091)	.	(0.0036)	0.0283	.	.	-37 mm Ø x -25 mm
VS LG79	0.059	-45 mm Ø x -28 mm
CZ SP-3C	0.095	(0.03)	1.67	(0.02)	.	.	-39 mm Ø x 25 mm
DSZU C016	0.007	.	.	.	0.0004	40 mm Ø x 25 mm
CZ SP-3B	0.08	.	0.88	0.01	.	.	-39 mm Ø x 25 mm
KUT S19	30-35 mm Ø x 18 mm
SRM C1153a	0.006	32 mm Ø x 19 mm
13X 18001B	0.0157	-40 mm Ø x -15 mm
KUT H6/1	30-35 mm Ø x 18 mm
CZ SP-3D	0.037	(0.03)	2.45	(0.04)	.	.	-39 mm Ø x 25 mm
13X NSB1D	40 mm Ø x 15 mm
IARM 339A	0.004	(0.001)	0.0006	.	0.0014	.	0.016	.	.	(0.002)	(0.005)	(0.003)	31 mm Ø x 2 or 18 mm
13X 18002D	0.0617	-40 mm Ø x -15 mm
CZ CM-18A	0.0344	-37 mm Ø x -25 mm
SS 468/1	38 mm Ø x 19 mm
SRM C1152a	0.0047	32 mm Ø x 19 mm
VS LG32/5	0.156	-38 mm Ø x -25 mm
13X NSA2J	-40 mm Ø x -15 mm
IARM 289A	0.01	.	0.0003	.	.	.	0.0104	.	.	(0.002)	<0.005	.	31 mm Ø x 2 mm
IARM 241D	0.022	(0.001)	0.0016	.	(0.0012)	.	(0.005)	(0.0003)	.	(0.0022)	(0.007)	(0.005)	31 mm Ø x 2 or 18 mm
DSZU C018	0.086	.	.	.	0.0003	40 mm Ø x 25 mm
13X NSB3G	42 mm Ø x 15 mm
KUT H5	30-35 mm Ø x 18 mm
13X 18003C	0.0292	-40 mm Ø x -15 mm
IRSID 1819	.	.	(0.0004)	47 mm x 47 mm x 30 mm
13X 17002E	(0.030)	.	0.0012	(0.012)	.	-40 mm Ø x -15 mm
NCS HS28743	0.0056	0.0042	0.0004	.	0.0025	.	.	38 mm Ø x 35 mm
IMZ 166A	0.036	(0.0026)	(0.0035)	.	.	40 mm Ø x 40 mm
13X 12855N	0.048	.	0.0098	0.093	.	0.122	.	-40 mm Ø x -15 mm
13X 14828A	0.008	0.0128	.	.	-40 mm Ø x -15 mm
VS LG81	0.409	-45 mm Ø x -28 mm
VS LG77	-45 mm Ø x -28 mm
IMZ 164	0.040	(0.005)	(0.002)	.	(0.003)	.	.	40 mm Ø x 40 mm
13X 17003A	40 mm Ø x 15 mm
VS LG73	-45 mm Ø x -28 mm
KUT S20	30-35 mm Ø x 18 mm
VS LG80	0.025	-45 mm Ø x -28 mm
BS 253	0.016	0.005	0.044	.	.	0.006	25(pre-17025)	.	38 mm Ø x -7 or 19+ mm
IARM 234C	0.035	(0.001)	0.0023	.	(0.0017)	.	(0.005)	(0.001)	.	0.0017	(0.003)	(0.006)	31 mm Ø x 2 or 18 mm
SS 462	.	0.007	0.0005	38 mm Ø x 19 mm last
DSZU C015	(0.008)	.	.	.	0.0017	40 mm Ø x 25 mm
SS 464/1	.	(0.003)	0.0004	38 mm Ø x 19 mm
13X 17004B	0.043	.	0.0066	0.057	.	-40 mm Ø x -15 mm
IMZ 165	0.038	(0.003)	(0.001)	.	0.003	.	.	40 mm Ø x 40 mm
SS 467/1	.	0.004	0.004	.	.	0.0017	.	38 mm Ø x 19 mm
13X 12854M	.	.	0.0101	0.0052	0.068	.	0.020	0.0146	-40 mm Ø x -15 mm
VS LG35/5	0.087	-38 mm Ø x -25 mm
Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units
13X 17001C	0.0312	.	0.0085	0.0124	.	-40 mm Ø x -15 mm
KUT S26	30-35 mm Ø x 18 mm
NCS HS41750	0.009	38 mm Ø x 35 mm
ECRM 270-1D	(0.0023)	(0.0034)	Ce: 0.0487	La: 0.0154	(0.0007)	(0.0035)	.	(0.002)	38 mm Ø x 25 mm
VS LG78	0.15	-45 mm Ø x -28 mm
BS 192	1.17	(0.005)	(0.0003)	.	0.0007	.	0.0014	25(pre-17025)	.	0.008	(0.001)	.	38 mm Ø x -7 or 19+ mm
BS 83G	(0.004)	.	(0.001)	.	.	.	0.0064	.	.	0.003	.	.	38 mm Ø x -7 or 19+ mm
NM 301	35 mm Ø x 20 mm
VS LG72	0.089	-45 mm Ø x -28 mm
NM 302	35 mm Ø x 20 mm
13X 12534X	0.0485	0.031	.	-40 mm Ø x -15 mm
IARM 316A	0.006	0.007	(0.0003)	.	0.0017	0.064	0.0052	(0.0001)	.	0.006	(0.003)	.	31 mm Ø x 2 or 18 mm
IARM 18D	(0.006)	.	(0.0011)	(0.007)	.	.	31 mm Ø x 18 mm
13X 12853L	0.18	.	0.0018	0.034	.	-40 mm Ø x -15 mm
VS LG63	0.45	-47 mm Ø x -30 mm
KUT S25	30-35 mm Ø x 18 mm
SRM 1171	31 mm Ø x 19 mm
BS 9841	(<0.006)	(0.003)	0.0026	25(pre-17025)	.	.	(0.011)	(0.001)	(0.006)	0.006	.	(0.002)	44 mm Ø x -7 or 19+ mm
SS 465/1	0.026	.	0.0006	(<0.001)	38 mm Ø x 19 mm
BS 192A	0.98	(0.0035)	(0.0003)	.	(0.0006)	.	(0.0006)	.	.	0.008	25(pre-17025)	.	38 mm Ø x -7 or 19+ mm
IMZ 152	40 mm Ø x 40 mm
IMZ 152A	(0.004)	(0.002)	0.0022	(0.001)	.	.	38 mm Ø x 20 mm
VS LG71	0.072	-45 mm Ø x -28 mm
CT 304	<0.001	.	0.017	.	.	30-35 mm Ø x -16 mm Ag: 7ppm
BS 82E	0.006	.	0.0024	.	0.0014	0.006	.	.	38 mm Ø x -7 to 19 mm
13X 31008A	-38 mm Ø x -15 mm
KUT H7/1	30-35 mm Ø x 18 mm
CT 316	0.001	.	0.006	.	.	30-35 mm Ø x -19 mm Ag: 5ppm
VS LG36/5	0.080	-38 mm Ø x -25 mm
BS 321D	0.103	0.0040	0.0012	.	(0.0003)	.	0.0009	(0.0003)	(0.001)	0.0091	17025	(0.001)	44 mm Ø x -7 or 19+ mm Fe,Mg
13X NSB2D	40 mm Ø x 15 mm
BS 9842	0.014	(0.002)	0.0025	.	0.0010	.	(0.0044)	.	.	0.005	25(pre-17025)	.	38 mm Ø x -7 or 19+ mm
BS 82D	(0.002)	.	0.0040	.	0.0007	.	0.007	.	.	0.004	.	last	38 mm Ø x -7 mm
SRM 1172	<0.001	.	32 mm Ø x 19 mm
VS LG82	0.076	-45 mm Ø x -28 mm
BS 87F	0.004	0.005	(0.0006)	.	0.0007	.	0.005	.	.	0.004	.	.	41 mm Ø x -7 or 19+ mm
BS 86F	(0.007)	(0.003)	0.0026	.	(0.001)	.	.	(0.001)	.	0.004	.	.	44 mm Ø x -7 or 19+ mm
DSZU C017	0.28	.	.	.	0.0031	40 mm Ø x 25 mm
IARM Fe304H-18	(0.005)	0.0076	(0.008)	.	.	(0.014)	.	.	31 mm Ø x 2 or 18 mm
BS 347B	0.002	(0.003)	0.0036	.	(0.0005)	.	0.005	.	.	0.006	(<0.004)	.	38 mm Ø x -7 or 19+ mm
BS 347A	(0.002)	(0.003)	(0.0004)	.	(0.0002)	.	0.0047	.	.	0.007	(<0.004)	.	38 mm Ø x 19+ mm
Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units

STAINLESS STEEL WITH C < 0.05 %

CONTINUED FROM THE PREVIOUS PAGE

analysis listed in mass %

Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units
ECRM 269-1D	.	0.0061	0.0099	.	35 mm Ø x 25 mm
IARM 8H	(0.005)	.	(0.0002)	(0.008)	(0.01)	31 mm Ø x 2 or 18 mm
IARM 61	0.084	(0.005)	0.0034	(0.0004)	0.0012	.	.	(0.0060)	.	31 mm Ø x 2 mm
ECRM 289-1D	0.199	.	0.0044	0.111	.	38 mm Ø x 30 mm
IMZ 150A	0.022	40 mm Ø x 40 mm
IARM 4F	0.015	(0.003)	(0.0012)	(0.002)	(0.004)	.	(0.001)	(0.005)	(0.007)	31 mm Ø x 2 or 18 mm
13X 14211R	0.089	0.0152	~40 mm Ø x ~15 mm
13X 32100A	0.0247	.	0.0025	0.0115	.	~38 mm Ø x ~15 mm
IARM Fe303-18	.	0.007	(0.0012)	.	(0.006)	.	.	(0.015)	.	31 mm Ø x 2 or 18 mm
BS 188B	0.168	0.0045	0.0047	(0.00003)	0.0006	(0.0001)	(0.0006)	0.0051	.	38 mm Ø x ~7 or 19+ mm Fe: 55.8 17025
IARM 4G	0.008	(0.005)	0.0032	(0.001)	(0.003)	(0.0005)	(0.001)	0.008	(0.008)	31 mm Ø x 2 mm
IARM 6J	0.0195	.	0.0024	.	(0.001)	.	.	(0.009)	(0.01)	31 mm Ø x 2 mm
BS 303	0.0019	.	0.0013	(0.0015)	0.0058	.	(0.002)	0.0091	.	44 mm Ø x ~7 or 19+ mm 17025 Fe:[70.7]
IARM 4E	0.004	(0.005)	0.0011	.	0.0021	.	.	0.0060	0.005	31 mm Ø x 2 mm
13X 18004C	0.011	(0.0025)	.	~40 mm Ø x ~15 mm
CZ SL-3A	0.007	.	0.002	0.006	.	~39 mm Ø x 25 mm
IARM 8i	(0.0030)	.	(0.0005)	.	(0.004)	.	.	(0.012)	.	31 mm Ø x 2 or 18 mm
13X 14216P	~40 mm Ø x ~15 mm
IARM 8G	0.0030	(0.007)	(0.0005)	(0.0005)	(0.003)	.	.	0.0107	(0.004)	31 mm Ø x 2 mm
VS LG70	0.029	~45 mm Ø x ~28 mm
NILAB 500HA D	38 mm Ø x 20 mm
13X 12538J	40 mm Ø x 15 mm
NCS HS28741	.	0.0035	.	.	.	0.0001	.	0.0051	.	38 mm Ø x 35 mm
13X 14207L	0.0226	0.082	~40 mm Ø x ~15 mm
IRSD 1821	47 mm x 47 mm x 30 mm
IMZ 153A	0.036	.	.	0.0024	38 mm Ø x 20 mm
ECRM 292-1D	(0.002)	(0.008)	.	(0.0006)	(0.001)	38 mm Ø x 25 or 30 mm
BS 184A	1.00	.	(0.0004)	(0.0003)	(0.0003)	.	.	(0.002)	(0.002)	38 mm Ø x ~7 or 19+ mm
SS 462/1	38 mm Ø x 19 mm
SRM C1151a	0.0039	.	.	.	32 mm Ø x 19 mm
13X 31400A	0.022	.	.	0.0024	~40 mm Ø x ~15 mm
BS 9812	(0.002)	(0.005)	(0.0003)	0.0012	(0.007)	.	.	0.004	.	50 mm Ø x ~7 or 19+ mm 25(pre-17025)
13X NSA9B	.	.	0.0018	~40 mm Ø x ~15 mm
13X 30403B	0.0056	.	.	0.0027	.	.	.	0.0139	.	~40 mm Ø x ~15 mm
HRT FE2014-H	35mm Ø x 20 mm
VS LG75	0.113	~45 mm Ø x ~28 mm
BS 9811	(0.003)	(0.003)	(0.0003)	0.0014	(0.0060)	.	.	0.004	.	38 mm Ø x ~7 or 19+ mm 25(pre-17025)
SRM 1155a	<0.01	(0.007)	(0.002)	.	(0.003)	<0.005	.	(0.0069)	.	32 mm Ø x 19 mm
13X 32900A	0.007	.	0.0028	0.0033	~40 mm Ø x ~15 mm
BS 317L	0.0044	(0.003)	0.0012	0.0017	(0.006)	(0.0002)	(0.002)	0.0049	(0.002)	37 mm Ø x ~7 or 19+ mm 17025

Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units
IARM 162D	(0.0026)	0.0072	0.0027	(0.003)	0.005	.	(0.0019)	0.0102	(0.005)	31 mm Ø x 2 mm
IARM Fe304L-18	(0.003)	0.007	(0.0012)	.	(0.006)	.	.	(0.013)	.	31 mm Ø x 2 mm
NCS HS28764	.	Bi:0.013	40 mm Ø x 30 mm
IARM 153C	(0.003)	0.0061	0.0009	(0.0026)	0.006	(0.001)	(0.002)	0.010	(0.006)	31 mm Ø x 2 mm
ECRM 297-1D	0.0195	0.0040	1.146	(0.0002)	40 mm Ø x 30 mm
NCS HS28746	0.086	0.0032	.	.	.	0.0002	.	0.0065	.	38 mm Ø x 35 mm
BS 9942	0.004	(0.004)	0.0014	0.0014	(0.0023)	.	.	0.006	.	44 mm Ø x ~7 or 19+ mm 25(pre-17025)
BS 9941	0.004	(0.010)	0.0025	(0.0003)	(0.0058)	.	.	0.007	.	38 mm Ø x ~7 or 19+ mm 25(pre-17025)
IARM Fe316L-18	(0.006)	.	.	.	(0.005)	.	.	(0.013)	.	31 mm Ø x 2 mm
IRSD 1820	.	.	(0.0013)	47 mm x 47 mm x 30 mm
BS 2205A	(0.004)	0.0072	0.0022	0.0007	0.0046	.	.	0.0058	.	38 mm Ø x ~7 or 19+ mm 17025 Fe: 66.2
NCS HS28742	.	0.0025	.	.	.	0.0001	.	(0.0001)	.	38 mm Ø x 35 mm
13X NSA8B	.	.	0.0017	0.0011	~38 mm Ø x ~15 mm
13X NSA13A	(0.007)	.	0.0030	.	.	(0.0008)	.	0.0046	.	~40 mm Ø x ~15 mm
SS 463/1	.	.	0.0022	38 mm Ø x 19 mm
13X NSA12A	0.0169	.	0.0020	~40 mm Ø x ~15 mm
IARM 212D	(0.005)	(0.01)	0.001	(0.001)	0.0034	(0.001)	.	(0.003)	(0.003)	31 mm Ø x 2 mm last of stock
13X FV520BA	~40 mm Ø x ~15 mm
HRT FE2000-H	.	.	0.0013	40 mm Ø x 20 mm
IARM Fe2205-18	(0.007)	.	.	.	(0.004)	.	.	(0.006)	.	31 mm Ø x 2 or 18 mm
NCS HS28745	.	0.0055	.	.	.	0.0001	.	0.0073	.	38 mm Ø x 35 mm
SS 476	.	0.0053	.	0.0028	.	.	.	0.0059	.	38 mm Ø x 19 mm
BS 304B	0.0036	0.0051	(0.0004)	0.0009	0.0038	(0.0008)	.	0.0057	.	38 mm Ø x ~7 to 19+ mm 17025 last
IARM 239C	0.007	(0.004)	0.0014	.	.	* Provisional Analysis	.	(0.003)	(0.004)	31 mm Ø x 2 or 18 mm
IARM FeZ100-18	(0.017)	.	0.002	.	(0.003)	.	.	(0.006)	.	31 mm Ø x 2 or 18 mm
BS 179C	0.0078	0.0034	0.0015	(0.0003)	0.0038	(0.00002)	0.0005	0.0018	(0.0006)	38 mm Ø x ~7 or 19+ mm 17025 Fe:[61.6]
BS 179B	0.0070	0.0036	0.0015	(0.0004)	0.0037	(0.00002)	0.0005	0.0019	(0.0006)	38 mm Ø x 19+ mm 17025 Fe:[61.5]
ECRM 287-1D	.	.	0.924	38 mm Ø x 25 or 30 mm
13X 34700A	0.023	.	0.0008	~38 mm Ø x ~15 mm
13X NSA11A	(0.021)	~38 mm Ø x ~15 mm
CZ SL-2A	0.005	0.008	0.002	0.01	.	~39 mm Ø x 25 mm
BS 316F	(0.002)	0.0067	0.0019	0.0018	0.0055	(0.0002)	.	0.0092	Fe:68.1	38 mm Ø x ~7 or 19+ mm 17025
IARM 319A	(0.010)	(0.004)	0.0020	.	0.0025	.	.	0.0055	(0.002)	31 mm Ø x 2 mm
SS 466/2	0.0018	0.0020	0.0039	38 mm Ø x 19 mm
IARM 163E *	0.0039	(0.008)	0.0019	(0.002)	0.007	.	(0.002)	0.012	.	31 mm Ø x 2 mm * Provisional Analysis, last
HRT FE2016-H	30 mm Ø x 20 mm
SS 461/1	0.069	38 mm Ø x 19 mm
13X 30600A	0.020	.	.	.	Mg:0.0016	~32 mm Ø x ~20 mm
BS SS1961	0.067	0.004	0.0022	.	(0.002)	.	.	0.004	.	38 mm Ø x 12 mm last
JK 27B	.	.	0.00072	0.0022	.	.	.	0.0068	.	~37 mm Ø x 25 mm
BS SS1962	0.062	0.002	0.0018	.	(0.001)	.	.	0.004	.	38 mm Ø x ~7 or 19+ mm
IARM 354A	(0.05)	(0.002)	0.0023	(0.0003)	(0.0012)	(0.004)	(0.0002)	(0.002)	.	31 mm Ø x 2 or 18 mm
CT IS0123A	0.027	.	0.0021	44-47 mm Ø x ~16 mm Fe: 74.72
13X 46500A	0.069	.	0.0016	0.0030	.	~32 mm Ø x ~20 mm
ECRM 284-3D	.	0.00131	0.00020	0.00074	.	39 mm Ø x 28 mm

Number Al As B Ca O Pb Sb Sn Ta Units

HIGH ALLOY STEEL XRF SET

Part Number:	BS HAS-12	RM except CRM as noted, available as set or individually										* Provisional Analysis					~7 mm Ø discs		
Number Grade	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	B	Co	N	Nb	Sn	Ti	V	W	O
BS 189A AL6XN CRM	0.0147	0.639	0.019	(0.001)	0.30	0.184	23.8	20.4	6.04	0.0129	(0.0002)	0.100	0.198	(0.13)	0.0035	0.0065	0.054	0.037	0.0024
		17025																	
BS 179A Alloy 255	0.017	1.04	0.021	0.001	0.44	1.94	5.84	25.45	3.24	(0.009)	(0.001)	0.58	0.184	0.030	0.005	0.006	0.070	(0.2)	.
BS 183B Greek Ascology CRM	0.181	0.344	0.018	0.0042	0.41	0.074	1.96	12.45	0.33	0.0009	(0.0007)	0.032	0.044	(0.0075)	0.0046	(0.0016)	0.165	3.5	(0.0054)
		17025																	
BS 186A Invar 36	0.040	0.72	0.008	0.0053	0.19	0.016	35.86	0.16	0.0032	(0.001)	.	0.028	0.0026	(<0.002)	(0.002)	(<0.003)	0.0012	(0.01)	.
BS 187A Carp. 20Cb3	0.022	0.52	0.017	0.0025	0.26	3.10	33.06	19.75	2.06	(0.009)	0.0022	0.32	0.0157	0.57	0.003	(0.002)	0.10	(0.02)	.
BS 188B A-286 CRM	0.046	0.247	0.016	(0.0007)	0.266	0.120	24.81	14.32	1.30	0.168	0.0047	0.274	0.0021	0.099	0.0051	2.20	0.264	0.043	0.0006
		17025																	
BS 190 Nitronic® 40	0.022	9.72	0.015	0.001	0.46	0.072	6.74	19.57	0.15	(0.004)	0.0005	0.044	0.255	(0.004)	0.003	0.002	0.11	0.015	0.0045
BS 180A Nitronic® 50	0.018	5.05	0.012	0.001	0.32	0.067	13.19	21.09	2.04	0.012	(0.0024)	0.039	0.334	0.20	(0.002)	(0.002)	0.20	0.02	0.003
BS 181A Nitronic® 60	0.071	8.16	0.019	0.001	4.03	0.18	8.15	16.52	0.21	0.022	0.0009	0.072	0.148	0.017	0.005	0.007	0.094	0.04	0.0010
BS 193 18Cr-12Mn	0.104	12.11	0.018	0.002	0.66	0.088	1.82	18.48	0.21	(0.003)	0.0007	0.028	0.37	0.014	0.004	0.003	0.107	(0.007)	.
BS 182 17Cr-15Mn	0.037	15.09	0.022	(0.003)	0.46	0.56	1.11	16.67	0.99	.	.	0.032	(0.40)	(0.005)	(0.003)	(0.003)	0.059	(0.01)	.
BS 191 16Cr-6Mn-4Si	0.098	5.71	0.024	0.023	3.66	0.33	5.34	16.33	0.36	(0.002)	(0.0006)	0.11	0.117	0.024	(0.006)	0.012	0.083	0.033	.

CRM CAST IRON SETS AVAILABLE IN SETS ONLY, as grouped

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Sn	Ti	V	Ce	La	Mg	N
30 mm Ø x 28 mm																	
NCS HS11712a-6	4.02	1.41	0.021	0.026	0.163	1.83	1.89	0.112	0.019	0.726	0.057	0.238	0.509	<0.0001	<0.0001	0.104	0.013
NCS HS11712a-7	3.94	1.38	0.085	0.0048	0.918	1.10	1.37	1.05	0.214	0.168	0.134	0.114	0.390	<0.0001	<0.0001	0.056	0.0063
NCS HS11712a-5	3.52	0.311	0.420	0.019	1.17	0.389	1.03	0.766	.	0.629	0.013	0.161	0.324	<0.0001	<0.0001	0.021	0.0047
NCS HS11712a-4	3.16	0.462	0.396	0.017	1.96	0.921	0.778	1.40	0.0073	0.428	0.024	0.065	0.166	<0.0001	<0.0001	0.025	0.0073
NCS HS11712a-2	2.22	0.301	0.043	0.058	2.44	0.458	0.341	2.13	0.060	0.087	0.044	0.065	0.055	0.0010	0.010	0.0085	0.024
NCS HS11712a-3	2.55	0.878	0.071	0.045	1.50	0.641	0.519	0.417	0.034	0.354	0.021	0.027	0.085	0.027	0.0061	0.024	0.024
NCS HS11712a-1	1.75	0.080	0.580	0.119	3.40	0.025	0.030	2.48	0.248	0.031	0.0031	0.038	0.021	<0.0001	<0.0001	0.0006	0.015
30 mm Ø x 30 mm																	
NCS HS19701-7	4.13	2.06	0.306	0.111	1.85	.	0.026	0.157	.	.	0.043	0.399	0.821
NCS HS19701-6	3.93	1.46	0.168	0.124	0.99	.	0.094	0.387	.	(0.112)	0.0018	0.105	0.506
NCS HS19701-5	3.67	0.596	0.072	0.117	0.183	.	0.502	0.171	.	(0.68)	0.0022	0.066	0.335
NCS HS19701-4	3.70	0.857	0.087	0.076	0.451	.	0.032	0.117	.	(0.031)	0.0017	0.030	0.158
NCS HS19701-3	3.29	1.22	0.045	0.056	0.689	.	0.046	0.030	.	.	0.009	0.043	0.071
NCS HS19701-2	2.99	0.329	0.033	0.038	0.937	.	0.194	0.080	.	.	0.024	0.216	0.044
NCS HS19701-1	2.46	0.072	0.011	0.019	0.099	.	0.183	0.511	.	.	0.005	0.0059	0.0090

RM GRAY IRON as cast (not chill cast) CONTAINS FREE GRAPHITE OBS regularly requires extension of preburn time to analyze correctly

Table with 19 columns: Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, As, Co, Mo, Sb, Sn, Ti, V, mm Ø x mm H. Rows include BS 20G, BS 20W, BS 20R, BS 20E, BS 20P.

DUCTILE / NODULAR IRON

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

Table with 19 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Ce, Co, Mg, Mo, Ti, V. Rows include various grades like SCRM 666/12, BS 286CH, BS 286CF, BS 286CE, BS 286CD, BS 286CC, BS 286CB, BS 286CA, BS SIMO 2/2, SCRM 668/14, SRM C2424, BAS SIMO 1/6.

Table with 16 columns: Number, As, B, Ca, Fe, La, Nb, Pb, Sb, Sn, W, Zr, Units. Rows include grades like SCRM 666/12, BS 286BH, BS 286CI, BS 286BG, BS 286CH, BS 286CF, BS 286CE, BS 286CD, BS 286CC, BS 286CB, BS 286CA, BAS SIMO 2/2, SCRM 668/14, SRM C2424, BAS SIMO 1/6.

RM Si-Mo CAST IRON

BAS SIMO: 48 mm x 42 mm x 12 mm block

CTIF: each unit = one pair 43 mm Ø x 5 mm discs

Table with 17 columns: Number, C, Mn, P, S, Si, Cu, Ni, Cr, Mo, Al, Ti, V, Co, As, Sn, Ce, Mg. Rows include CTIF SiMo-3, CTIF SiMo-1, CTIF SiMo-5, CTIF SiMo-2, BAS SIMO 1/3, CTIF SiMo-4, BAS SIMO 2/3.

CAST IRON WITH MAGNESIUM - continued on the next page

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
1	CZ 20034 17b	4.38	0.501	0.089	0.0040	0.178	0.111	2.34	0.200	0.009	.	(0.002)	(0.003)	0.043	0.030	0.016	0.086
1	CZ 20034 17a	4.30	0.494	0.115	0.0034	0.170	0.082	2.38	0.200	0.007	.	(0.002)	(0.003)	0.043	0.030	0.016	0.086
1	CZ 20034 17c	4.08	0.503	0.104	0.0033	0.150	0.037	2.32	0.178	0.007	.	(0.002)	(0.003)	0.043	0.030	0.015	0.076
1	Y 2863-11	4.03	0.61	0.613	0.026	0.79	0.96	0.46	1.65	0.0075	0.94	0.29	0.079
2	CZ SPL17 43A	3.98	1.322	0.190	0.008	1.63	0.385	0.411	0.032	(0.04)	.	0.024	0.017	0.045	0.152	0.065	0.152
2	CZ SPL17 42A	3.94	0.764	0.294	0.0040	1.94	0.199	0.492	0.145	(0.06)	.	0.087	0.039	0.010	0.021	0.126	0.093
1	Y 451045	3.90	0.12	0.023	0.0027	2.29	0.022	0.45	0.028	0.033	0.0030	0.016	0.0014
1	SCRМ 668/14	3.77	0.702	0.045	0.0220	1.72	0.65	0.096	0.99	0.009	.	.	0.023	.	0.0179	0.086	0.195
1	Y 2863-12	3.77	0.158	0.053	0.057	0.150	0.55	0.192	2.31	0.0024	0.44	0.030	0.229
1	CZ 02033 2f	3.77	0.091	0.159	0.009	1.23	0.89	0.658	0.022	0.053	.	0.024	0.018	(0.003)	(0.002)	0.021	0.010
1	VS ChG 25/1	3.75	0.67	0.013	0.0048	1.46	0.81	0.406	0.214	0.0096	0.271	0.0087	0.0070
1	CZ 02033 3c	3.68	0.333	0.026	0.007	2.15	0.421	0.040	0.100	0.006	(0.005)	0.024	0.013	0.026	0.490	0.021	0.016
1	SCRМ 666/12	3.599	0.106	.	.	1.763	0.0581	1.709	0.102	0.0838	0.0979	0.1069	0.0486
1	VS ChG 27/1	3.59	1.20	0.039	0.019	1.97	0.351	0.030	0.139	.	.	0.011	.	.	0.131	0.060	0.070
2	Y 4510058B-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.042	.	.	0.022	.	0.180	0.044	0.174
2	Y 4510058C-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.039	.	.	0.022	.	0.180	0.044	0.174
2	Y 4510058D-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.036	.	.	0.022	.	0.180	0.044	0.174
2	Y 4510058E-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.032	.	.	0.022	.	0.180	0.044	0.174
2	CZ SPL17 31A	3.54	0.041	0.025	0.006	2.10	0.005	0.538	0.019	0.070	.	0.005	(0.004)	0.022	0.004	0.007	0.008
2	CZ SPL17 34A	3.48	0.980	0.105	0.008	2.29	0.230	0.493	0.102	0.026	.	0.010	0.008	0.025	0.072	0.044	0.073
1	CZ 20034 15c	3.47	0.060	0.054	0.0028	1.68	1.123	0.728	0.078	0.040	.	0.010	0.030	0.026	(0.002)	0.036	0.019
2	CZ SPL17 32A	3.39	0.288	0.037	0.007	2.74	0.306	0.015	0.060	0.024	.	0.029	(0.004)	(0.002)	0.116	0.044	0.005
1	CZ 02033 3b	3.38	0.260	0.012	0.012	1.74	0.400	0.049	0.235	0.012	.	0.026	0.006	0.012	0.456	0.023	0.009
2	CZ SPL17 40A	3.38	0.042	0.021	0.0035	1.98	0.010	0.045	0.031	0.007	.	0.096	0.012	0.027	0.005	0.015	0.014
1	VS ChG 28	3.29	0.414	0.025	0.015	2.22	1.29	0.166	0.127	0.010	.	0.015	.	.	0.0024	0.0041	0.0020

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
1	VS ChG 28/1	3.28	0.420	0.039	0.008	2.14	1.30	0.177	0.177	0.014	.	0.0097	.	.	.	0.019	0.013
1	CZ 02033 3d	3.24	0.317	0.008	0.006	2.12	0.396	0.025	0.236	0.016	.	0.055	0.006	0.014	0.453	0.016	0.072
1	CZ 02033 1f	3.23	0.693	0.043	0.005	2.68	0.018	0.373	0.035	0.070	(0.007)	0.073	0.036	0.024	0.182	0.041	0.014
1	CZ 20034 13c	3.15	0.704	0.0261	0.0044	2.23	0.089	1.299	0.124	0.064	.	0.022	0.011	0.024	0.360	0.015	0.043
1	CZ 20034 14c	3.14	0.275	0.0162	0.0081	2.49	0.585	0.030	0.045	0.017	.	0.007	0.019	0.009	0.646	0.018	0.013
1	CZ 20034 13a	3.13	0.691	0.0244	0.0046	2.19	0.021	1.266	0.122	0.053	.	0.017	0.011	0.024	0.364	0.014	0.048
1	CZ 20034 13b	3.12	0.692	0.0243	0.0041	2.12	0.021	1.313	0.125	0.054	.	0.019	0.011	0.024	0.364	0.012	0.048
1	BS CC-11A	3.07	1.23	0.020	0.011	1.90	0.007	0.046	0.048	0.014	0.026	0.0055	0.018	(0.007)	0.0063	0.0091	0.0066
1	VS ChM5/I	3.04	0.311	0.056	0.016	1.37	.	.	.	0.045	.	0.013
1	SCRМ 667/13	3.04	0.222	.	.	2.866	0.497	1.303	0.294	0.070	.	.	0.110	.	.	.	0.103
1	VS ChG 24/1	3.04	0.280	0.237	0.007	2.40	0.104	0.85	0.030	0.021	.	0.027	0.021	.	0.028	0.089	0.026
1	VS ChM6/1	3.03	0.54	0.055	0.0074	2.75	.	.	.	0.072	.	0.022
1	VS ChM8/1	3.02	0.83	0.055	0.0034	3.39	.	.	.	0.105	.	0.041
2	CZ SPL17 36A	3.02	0.057	0.026	0.010	2.13	0.007	0.011	0.014	0.012	.	(0.003)	0.0007	(0.004)	0.004	0.021	0.021
1	BS CC-11B	2.97	1.17	0.020	0.008	1.94	0.0210	0.173	0.189	0.025	0.019	0.028	0.045	(0.022)	0.018	0.031	0.0179
1	VS ChM13	2.96	1.05	0.043	0.009	2.98	0.062	1.65	0.273	0.09	.	0.065	.	.	.	0.018	0.0096
1	VS ChG 26/1	2.96	0.132	0.104	0.0058	2.89	0.022	1.41	0.050	0.052	.	0.041	0.017	.	0.070	0.016	0.159
1	SCRМ 669/14	2.955	0.526	.	.	2.201	0.194	0.473	0.214	0.0224	.	.	0.0415	.	0.0550	0.0499	0.532
1	VS ChG 26	(2.9)	0.126	0.123	0.0041	2.98	0.014	1.52	0.050	0.044	.	0.038	.	.	0.075	0.0026	0.040
1	VS ChM10	2.89	0.43	0.067	0.017	1.13	0.082	0.85	0.067	0.024	.	0.005	.	.	.	0.028	0.079
1	SRМ C1137a	2.86	0.52	0.087	0.017	1.15	0.192	2.17	0.643	0.032	.	(0.007)	0.016	.	0.86	(0.04)	0.019
2	CZ SPL17 33A	2.75	0.710	0.060	0.007	3.10	0.730	0.389	0.239	0.021	.	0.054	0.026	0.015	0.220	0.130	0.356
1	SRМ C2424	2.68	0.268	0.041	0.024	3.37	0.125	0.061	0.13	0.006	.	(<0.01)	0.0046	(0.05)	0.019	0.050	0.083
1	VS ChM9	2.61	1.28	0.075	0.021	1.59	0.095	0.38	0.083	0.011	.	0.016	.	.	.	0.027	0.068
1	VS ChM11	2.26	0.77	0.032	0.011	2.32	0.067	1.75	0.122	0.066	.	0.035	.	.	.	0.014	0.0044
1	Y 2863-7	1.98	3.42	0.067	0.0061	3.10	0.089	4.47	0.150	0.050	.	.	0.019	.	0.052	0.060	0.87

BS: 28-34 mm Ø x 17-35 mm

CKD 24x: 37 mm x 37 mm x ~15-20 mm
CZ: 40 mm Ø x 18 mmSCRМ: 48 mm x 42 mm x 12 mm
SRМ: 32 mm Ø x 19 mmVS: ~40 mm Ø x ~40 mm
Y: 30 mm Ø x 30 mm

CAST IRON WITH MAGNESIUM - continued from the previous page

sizes shown below

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
CZ 20034 17b	0.008	(0.0002)	(0.001)	(0.002)	.	.	(0.002)	0.004	.	.
CZ 20034 17a	0.007	(0.0002)	(0.001)	(0.002)	.	.	(0.002)	0.004	.	.
CZ 20034 17c	0.0005	(0.0006)	(0.002)	(0.002)	.	.	(0.002)	0.004	.	.
Y 2863-11	(0.022)	0.053	0.33	(0.0057)	(0.174)	.	(0.108)	0.010	.	.
CZ SPL17 43A	.	0.0014	(0.002)	.	.	.	0.008	0.014	(0.004)	.	0.067	0.038	Zn:0.013	.
CZ SPL17 42A	.	0.0036	(0.002)	.	.	.	0.045	0.020	0.015	.	0.027	0.020	Zn:0.013	.
Y 451045	last
SCRM 668/14
Y 2863-12	(0.0097)	0.0078	0.21	(0.056)	(0.471)	.	(0.307)	0.13	.	.
CZ 02033 2f	.	0.0020	(0.002)	0.005	0.028	.	0.014	(0.003)	(0.005)	Zn: 0.018
VS ChG 25/1	0.067	.	.	0.011	.	.
CZ 02033 3c	(0.007)	0.0044	(0.002)	0.005	.	.	0.009	(0.003)	.	.
SCRM 666/12
VS ChG 27/1	0.036	.	.	0.125	.	.
Y 4510058B-18	0.0021	0.024
Y 4510058C-18	0.0021	0.024
Y 4510058D-18	0.0021	0.024
Y 4510058E-18	0.0021	0.024	last
CZ SPL17 31A	.	(0.0004)	(0.003)	(0.005)	.	.
CZ SPL17 34A	.	0.0076	(0.005)	.	.	.	0.014	(0.006)	0.007	.	0.051	0.016	Zn:0.007	.
CZ 20034 15c	(0.003)	0.0057	0.008	0.056	.	0.006	0.004	.	.
CZ SPL17 32A	.	(0.0005)	(0.007)	0.022	0.023	.	(0.012)	(0.008)	Zn:0.011	.
CZ 02033 3b	.	0.0042	0.001	0.009	.	.	0.019	.	.	.
CZ SPL17 40A	.	0.0008	(0.004)	.	Zn:(0.002)	.
VS ChG 28	0.015	.	0.0017	.	.	.

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
VS ChG 28/1	0.0017	.	.	.
CZ 02033 3d	(0.018)	0.0071	(0.002)	0.005	0.007	.	0.009	.	.	.
CZ 02033 1f	.	0.0043	(0.001)	0.009	.	.	0.030	0.022	(0.008)	.
CZ 20034 13c	(0.002)	(0.002)	.	0.014	(0.003)	(0.02)	.
CZ 20034 14c	0.035	0.0123	0.020	.	0.025	(0.003)	0.013	Zn: 0.010
CZ 20034 13a	(0.002)	(0.002)	.	0.014	(0.003)	0.029	.
CZ 20034 13b	(0.002)	(0.002)	.	0.014	(0.003)	0.023	.
BS CC-11A	0.0018	0.0008	(0.005)	(0.0009)	93.6	(0.004)	(0.007)	(0.002)	(0.01)	Zn:0.0032	(0.004)	(0.017)	(0.0025)	17025
VS ChM5/1
SCRM 667/13
VS ChG 24/1	0.011	.	0.081	.	.	.
VS ChM6/1
VS ChM8/1
CZ SPL17 36A	.	0.022	(0.007)	0.016	.	.	(0.002)	.	Zn:(0.002)	.
BS CC-11B	0.0074	0.0033	(0.016)	(0.002)	93.2	(0.008)	0.043	0.014	0.026	Zn:0.008	0.021	0.028	0.0165	17025
VS ChM13
VS ChG 26/1	0.0055	.	0.034	.	.	.
SCRM 669/14
VS ChG 26	0.031	.	.	.
VS ChM10
SRM C1137a
CZ SPL17 33A	.	0.0064	(0.002)	.	.	.	0.032	0.010	0.019	.	0.039	0.079	Zn:0.009	.
SRM C2424	.	(0.002)	.	.	.	0.0011
VS ChM9
VS ChM11
Y 2863-7	(0.021)	0.100	0.041	(0.0025)	(0.010)	.	(0.0073)	.	.	.

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
--------	----	---	----	----	----	----	----	----	----	----	----	---	----	-------

BS: 28-35 mm Ø x 17-35 mm

CZ: 40 mm Ø x 18 mm
SCRM: 48 mm x 42 mm x 12 mmSRM: 32 mm Ø x 19 mm
Y: 30-35 mm Ø x 18-30 mmVS ChM: ~39 mm Ø x ~39 mm
VS ChG: ~34 mm x ~35 mm X ~22 mm

RM CAST IRON WITH YOUR CHOICE OF MAGNESIUM LEVELS each unit: 2 pcs mushroom 43 mm Ø x 5 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Al	Ce	Co	Sn	Ti	V	Zn	Other
CTIF 6134	3.70	0.25	0.030	<0.01	1.60	0.020	2.00	0.040	*	.	<0.03
CTIF 8532	3.7	0.288	0.05	.	2.6	0.0443	0.888	0.04	*	.	<0.025	.	0.0303	0.02	0.07	.	.
CTIF 6135	3.6	0.38	0.0130	(0.003)	0.9	0.0219	1.98	0.04	*	(0.006)	.	0.037	.	0.007	0.0155	.	.
CTIF 4500	3.38	0.60	0.059	(0.002)	1.97	.	1.45	0.014	*	0.033	0.023	0.065
CTIF 5781	3.35	0.26	0.030	(0.0025)	2.50	0.0061	0.83	0.040	*	.	.	(0.004)	.	0.0208	0.0150	.	.
CTIF 4497	3.12	0.605	0.043	(-0.002)	2.66	0.048	1.90	0.040	*	.	.	.	0.094	0.031	0.44	.	.
CTIF 7160	3.1	0.57	0.05	(0.001)	2.4	0.08	1.0	(0.1)	*	(0.02)	0.02	0.09	.	0.013	0.018	.	As: 0.009
CTIF 5037	3.04	0.76	0.043	(0.0025)	3.40	.	0.64	0.014	*	0.029	.	.	.
CTIF 3601B	3.0	0.35	0.037	(0.005)	2.1	0.019	1.08	0.029	*	.	<0.01	.	.	0.016	(0.005)	<0.05	Pb:(<0.002)
CTIF 8018	3.0	0.7	0.07	(0.0015)	3.0	0.08	0.127	0.09	*	0.02	(<0.02)	.	0.07	0.06	0.39	.	Sb:(0.01)
CTIF 6736	2.8	0.65	0.012	(0.002)	1.6	0.0258	1.7	0.03	*	0.008	(0.03)	.	.
CTIF 5783	2.55	0.2	0.0266	(0.003)	2.3	0.110	1.23	0.05	*	.	.	0.0074	.	0.015	0.0127	.	As: 0.0016

Magnesium level available in the below samples. X = available

For Mg Range	Order Suffix	3601B	4497	4500	5037	5781	5783	6134	6135	6736	7160	8018	8532
<0.005	<0.005	X	.	.	.	X	X	X	X
0.005 - 0.009	0.005	X	.	.	X	X	X	.	.	X	.	X	X
0.010 - 0.014	0.01	.	.	.	X	X	X	.	.	X	X	X	X
0.015 - 0.024	0.02	X	.	.	X	X	X	.	X	X	X	X	X
0.025 - 0.034	0.03	.	.	.	X	.	X	.	X	X	X	X	X
0.035 - 0.044	0.04	.	.	.	X	.	X	.	X	X	X	X	X
0.045 - 0.054	0.05	.	.	.	X	.	X	.	X	X	X	X	X
0.055 - 0.064	0.06	.	X	.	.	.	X	.	X	X	X	X	X
0.065 - 0.074	0.07	.	X	X	.	.	X	.	X	X	X	X	X
0.075 - 0.084	0.08	.	X	X	.	.	X	X	X	X	X	X	X
0.085 - 0.094	0.09	.	X	X	.	.	X	X	X	X	X	X	X
0.095 - 0.104	0.10	X	X	X	X	X	X	X
0.105 - 0.114	0.11	X	X	X	X	X	X	X
0.115 - 0.124	0.12	X	X	X	X	X	X	X
0.125 - 0.134	0.13	X	X	X	X	X	X	X
0.135 - 0.144	0.14	X	X	X	X	X	X	X
0.145 - 0.154	0.15	X	.	.
0.155 - 0.164	0.16	X	.	.
0.165 - 0.174	0.17	X	.	.
0.175 - 0.184	0.18	X	.	.

The above cast iron samples can be ordered with your choice of Magnesium. Examples:
 to order CTIF 6736 with Mg 0.035 - 0.044 then order as part number CTIF 6736 0.04
 to order CTIF 8018 with 0.08 % Mg, order as part number CTIF 8018 0.08

CRM WHITE IRON analysis listed in mass %

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	Nb	Ti	V
BS WI-2	3.61	0.80	0.22	0.056	0.52	0.0124	0.254	0.229	0.0118	0.219	0.128	0.089	0.215
SRM CII45	2.92	0.187	0.215	0.191	0.271	0.46	0.62	0.63	0.058	0.48	.	0.012	0.112
VS ChG 8/6	(2.7)	1.51	0.040	0.013	3.93	.	.	(0.2)	(0.3)
VS ChG 10/6	(2.7)	0.86	0.103	0.0072	2.86	.	.	(0.2)	(0.3)
VS ChG 11/6	(2.7)	0.312	0.23	0.039	1.79	.	.	(0.2)	(0.3)
VS ChG 9/6	(2.7)	0.155	0.38	0.071	0.80	.	.	(0.2)	(0.3)
BS WI-1	1.75	0.24	0.051	0.114	1.90	0.027	0.053	0.048	0.0074	0.0103	0.027	0.020	0.008

17025

17025

Number	Al	As	B	Bi	Ca	Fe	Mg	Pb	Sb	Sn	W	Zr	Units
BS WI-2	0.0192	0.0016	0.0008	.	(0.00013)	[93.6]	(0.0002)	0.013	0.023	0.0042	0.023	0.0045	~35 mm Ø x ~30 mm
SRM CII45	(0.04)	(0.03)	(0.02)	(<0.01)	.	.	.	0.0012	(0.04)	(0.10)	.	(0.002)	32 mm Ø x 19 mm
VS ChG 8/6	.	(0.003-0.006)	~38 mm Ø x ~40 mm
VS ChG 10/6	.	(0.003-0.006)	~38 mm Ø x ~40 mm
VS ChG 11/6	.	(0.003-0.006)	~38 mm Ø x ~40 mm
VS ChG 9/6	.	(0.003-0.006)	~38 mm Ø x ~40 mm
BS WI-1	0.075	0.0067	0.0032	.	0.0005	[95.5]	0.0009	0.115	.	0.0081	0.185	0.0034	~35 mm Ø x ~30 mm

CAST IRON WITH C > 2.75%

CONTINUED ON THE NEXT PAGE

= Class, 1 = CRM and 2 = RM

Table with 19 columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Co, Mo, Nb, Sn, Ti, V, Zn. The table lists various iron solid grades and their chemical compositions.

CAST IRON WITH C > 2.75%

CONTINUED FROM THE PREVIOUS PAGE

analysis in mass % except * = mg/kg

Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
CZ SPL17 35A	.	(0.0002)	(0.002)	.	.	.	(0.005)	.	40 mm Ø x 18 mm last
MBH FEPIGH	-40 mm Ø -15 mm
CZ 02033 4e	.	.	(0.002)	(0.002)	40 mm Ø x 18 mm
CZ 02033 4d	(0.012)	(0.0001)	(0.002)	0.007	40 mm Ø x 18 mm
SCRM 659/9	48 mm x 42 mm x 12 mm
Y 2582-7	0.043	30 mm Ø x 18-30 mm
DSZU CH04	.	(0.0007)	.	(7)	.	.	(0.0001)	.	(0.007)	.	.	.	(<0.0002)	.	-30 mm x -35 mm x -19mm
DSZU CH05	.	(0.03)	.	(20)	.	.	(0.001)	-30 mm x -35 mm x -19mm
CZ 02033 4b	0.004	(0.001)	40 mm Ø x 18 mm
VS ChG 2/9	(0.003)	-38 mm Ø x -40 mm
DSZU CH06	.	(0.02)	.	(10)	0.1	.	-35 mm x -35 mm x -19mm
CZ 20034 16c	(0.003)	0.020	0.015	0.010	.	.	0.015	(0.002)	40 mm Ø x 18 mm
CZ 20034 16a	.	0.005	0.018	0.006	0.011	.	.	0.019	(0.002)	40 mm Ø x 18 mm
11X CSW	0.0544	0.0043	0.007	Cd:(0.0003)	Ag:0.0042	.	.	0.0070	0.007	0.058	0.006	0.013	0.0242	.	-40 mm Ø x -15 mm
CZ 20034 16b	0.005	0.018	0.007	0.011	.	.	0.019	(0.002)	40 mm Ø x 18 mm
VS ChG 32	.	.	0.361	-37 mm x -37 mm x -24 mm
SCRM 674/1	40 mm x 37 mm x 10 mm
Y 2582-4	0.0017	30 mm Ø x 18-30 mm
CZ SPL17 39A	.	0.0195	0.008	0.017	0.037	40 mm Ø x 18 mm
Y 2582-5	0.0022	30 mm Ø x 18-30 mm
VS ChG 1/9	(0.003)	-38 mm Ø x -40 mm
CZ 02033 7b	0.045	.	40 mm Ø x 18 mm
CZ 02033 7c	.	0.0008	(0.002)	0.037	.	40 mm Ø x 18 mm
DSZU CH03	(0.004)	(0.001)	.	(20)	.	.	(0.0001)	.	(0.01)	.	.	(0.006)	.	(0.006)	-30 mm x -35 mm x -16mm
VS ChG 3/9	(0.003)	-38 mm Ø x -40 mm
VS ChG 27	0.029	-35 mm x -35 mm x -22 mm
VS ChG 5/9	(0.003)	-38 mm Ø x -40 mm
11X HPC4Q	-40 mm Ø x -15 mm
Y 2863-5	.	0.060	0.158	.	30 mm Ø x 18-30 mm
11X C3AD	0.086	0.0253	0.0124	0.0075	0.0170	0.243	0.028	.	0.040	.	-40 mm Ø x -15 mm
CZ SPL17 41A	.	(0.0004)	(0.007)	0.010	0.016	.	.	0.012	.	40 mm Ø x 18 mm
VS ChL1/1	-38 mm Ø x -38 mm
CZ SPL17 38A	.	0.0027	(0.002)	(0.003)	0.018	.	.	(0.005)	.	40 mm Ø x 18 mm
11X C10D	0.019	0.0030	.	Cd:(0.0004)	.	.	.	0.0057	0.006	0.040	.	.	0.308	.	-40 mm Ø x -15 mm
VS ChG 35	-34 mm Ø x -37 mm
KUT 120	30 x 30 x 13 mm
Y 2863-3	.	0.056	30 mm Ø x 18-30 mm
KUT 121	30 x 30 x 13 mm
KUT 205	30 x 30 x 13 mm
KUT 206	30 x 30 x 13 mm
KUT 122	30 x 30 x 13 mm
KUT 123	30 x 30 x 13 mm
NCS HS11784	0.0041	.	0.0083	0.0002	0.0007	31 mm Ø x 28 mm
Y 2582-3	0.009	30 mm Ø x 18-30 mm
VS ChG 4/9	(0.003)	-38 mm Ø x -40 mm
11X HPC3K	-40 mm Ø x -15 mm
BAS NCRM3	40 mm x 37 mm x 10 mm
NCS HS11782	0.0065	31 mm Ø x 28 mm
KUT 125	30 x 30 x 13 mm
MBH FEPIGM	-40 mm Ø -15 mm

Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
VS ChG 31	.	.	0.068	-37 mm x -37 mm x -24 mm
NCS HS11785	0.0049	.	0.013	0.0002	0.0005	31 mm Ø x 28 mm
DSZU CH02	.	(0.016)	.	(10)	.	.	(0.002)	-35 mm Ø x -18 mm
11X C2V	0.0541	0.0098	0.0084	0.0096	0.0133	0.115	0.0157	.	0.0228	.	-40 mm Ø x -15 mm
VS ChM 12	(0.08)	-38 mm Ø x -38 mm
SCRM 671/1	40 mm x 37 mm x 12 mm
KUT 126	30 x 30 x 13 mm
KUT 202	30 x 30 x 13 mm
SCRM 657/9	48 mm x 42 mm x 12 mm
KUT 204	30 x 30 x 13 mm
KUT 127	30 x 30 x 13 mm
CZ 02033 6c	.	0.0024	(0.003)	0.044	.	0.007	.	40 mm Ø x 18 mm
CZ SPL17 37A	.	0.0124	(0.002)	(0.002)	.	.	.	0.026	.	40 mm Ø x 18 mm
VS ChG 30	.	.	0.082	-37 mm x -37 mm x -24 mm
BAS NCRM1	40 mm x 37 mm x 10 mm
VS ChL3/1	-38 mm Ø x -38 mm
11X C9E	0.53	0.0047	(0.0023)	0.145	.	0.0097	0.31	(0.0017)	-40 mm Ø x -15 mm
DSZU CH08	.	(0.08)	.	(10)	-35 mm x -35 mm x -19mm
VS ChG 39	-34 mm Ø x -37 mm
BAS LARM2	0.044	.	.	.	0.008	.	.	.	0.007	40 mm x 37 mm x 10 mm
BAS LARM4	0.008	.	.	.	0.018	40 mm x 37 mm x 10 mm
BAS LARM1	.	0.006	0.011	.	0.005	40 mm x 37 mm x 10 mm
BAS LARM5	0.018	0.0012	0.0010	0.0005	40 mm x 37 mm x 10 mm
BAS LARM3	0.092	0.003	0.022	40 mm x 37 mm x 10 mm
Y 2863-4	.	0.041	30 mm Ø x 18-30 mm
BAS LARM5/1	.	0.0016	0.0012	<0.001	40 mm x 37 mm x 10 mm
BAS NCRM2	40 mm x 37 mm x 10 mm
KUT 124	30 x 30 x 13 mm
CZ 02033 6b	0.049	40 mm Ø x 18 mm
SCRM 662/4	48 mm x 42 mm x 12 mm
VS ChG 36	-34 mm Ø x -37 mm
CZ 20034 12b	0.024	0.047	0.006	0.009	0.046	.	.	0.007	(0.002)	40 mm Ø x 18 mm
SRM C1145a	(0.03)	(0.02)	0.0012	(0.04)	.	.	.	(0.002)	32 mm Ø x 19 mm
VS ChG 34	.	.	0.223	-37 mm x -37 mm x -24 mm
CZ 20034 12a	0.022	0.036	0.005	0.007	0.046	.	.	0.011	(0.002)	40 mm Ø x 18 mm
NCS HS11786	0.0075	.	0.015	0.0003	0.0008	31 mm Ø x 28 mm
11X CSY	0.0203	0.0058	0.005	0.0094	0.0108	0.030	0.0072	(0.0022)	0.0072	(0.0024)	-40 mm Ø x -15 mm
KUT 201	30 x 30 x 13 mm

Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
--------	----	---	----	-----	----	----	----	---	----	----	----	----	---	----	-------

CAST IRON WITH C < 2.75%

= Class, 1 = CRM and 2 = RM

analysis in mass % except * = mg/kg

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
1	VS ChL4/1	2.69	1.37	0.054	0.027	1.99	0.161	0.725	0.92	.	0.017	0.116	.	.	0.11	0.258	.
1	SRM C1291	2.67	1.14	0.028	0.032	1.34	0.26	4.34	2.78	.	.	0.32	.	.	.	0.031	.
1	VS ChG 6/9	2.65	0.83	0.54	0.027	0.53	0.34	.	0.241	0.028	0.130	.
1	DSZU CH01	2.61	0.258	0.012	0.0045	1.95	0.097	0.072	0.88	0.079	(0.06)	0.070	(0.010)	(0.05)	0.132	0.134	.
1	VS ChG 40	2.59	1.56	0.059	0.019	1.60	0.98	1.61	1.47	.	.	0.229	.	.	0.18	0.325	.
1	11X C8V	2.60	0.394	1.00	0.204	1.643	0.310	0.275	0.148	0.086	0.126	0.148	0.0217	0.1063	0.235	0.064	0.0068
1	SCRM 661/4	2.56	0.30	0.84	0.068	2.96	.	.	(1)
1	SCRM 656/9	2.537	0.820	0.060	0.108	2.504
1	Y 2863-2	2.50	1.83	0.069	0.026	3.14	0.020	3.73	0.136	.	.	0.096	.	.	0.066	0.61	.
1	VS ChG 37	2.49	0.92	0.038	0.046	2.03	0.512	0.90	0.82	.	.	0.55	.	.	0.092	0.227	.
1	SCRM 673/1	2.455	0.123	0.317	0.0112	1.702	.	0.103	0.0423	0.0287	0.053	0.0092	.	0.0206	0.0718	0.052	.
1	CZ 20034 11b	2.44	0.382	0.271	0.140	3.67	0.130	0.082	1.178	0.067	0.005	1.144	.	0.074	0.041	0.182	.
1	VS ChG 38	2.43	0.302	0.386	0.084	2.30	1.20	0.162	1.98	.	.	0.046	.	.	0.105	0.119	.
1	CZ 02033 5b	2.42	0.812	0.033	0.073	1.32	0.031	0.188	0.061	0.062	.	0.089	.	.	0.007	0.005	.
1	VS ChL2/1	2.38	1.03	0.054	0.023	0.55	0.97	0.114	0.077	.	0.013	0.012	.	.	0.009	0.050	.
1	CZ 20034 11a	2.37	0.343	0.271	0.163	3.31	0.086	0.084	1.219	0.046	0.005	1.130	.	0.070	0.028	0.184	.
1	SCRM 652/4	2.34	1.19	0.071	0.129	0.878	.	.	(1)
1	DSZU CH07	2.33	1.36	0.090	0.064	3.01	0.35	0.403	0.34	0.036	.	0.66	(0.08)	(0.07)	0.150	0.52	.
1	CZ 02033 5c	2.30	0.704	0.027	0.091	1.40	0.013	0.188	0.085	0.103	0.013	0.104	.	(0.002)	0.008	0.054	.
1	11X C4S	1.954	0.565	0.1014	0.096	2.98	0.095	3.21	1.382	0.006	0.0210	0.177	0.0233	0.0140	0.080	0.0165	0.0037
1	SCRM 675	1.92	1.81	0.045	0.072	1.29	0.012	0.210	0.080	0.007	0.023	0.034	.	0.0062	0.007	0.178	0.0006
1	SCRM 655/4	1.90	0.44	0.180	0.076	2.110	.	.	(1)
1	Y 2863-1	1.78	2.41	0.021	0.009	3.62	0.022	4.77	0.031	.	.	0.038	0.0052	.	0.068	1.13	.

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
	Number	As	B	Bi	Ca*	Ce	Mg	N	Pb	Sb	Se	Te	W	Zr	Units		
	VS ChL4/1	~38 mm Ø x ~38 mm
	SRM C1291	32 mm Ø x 19 mm
	VS ChG 6/9	(0.003)	~38 mm Ø x ~40 mm
	DSZU CH01	.	(0.03)	.	(10)	.	(0.0005)	(0.02)	.	.	.	~30 mm x ~35 mm
	VS ChG 40	~34 mm Ø x ~37 mm
	11X C8V	0.0812	0.0366	0.014	.	.	.	0.0065	0.0052	0.069	0.0210	0.0049	0.0258	0.0064	.	.	~40 mm Ø x ~15 mm
	SCRM 661/4	48 mm x 42 mm x 12 mm
	SCRM 656/9	48 mm x 42 mm x 12 mm
	Y 2863-2	.	0.0025	30 mm Ø x 18-30 mm
	VS ChG 37	~34 mm Ø x ~37 mm
	SCRM 673/1	40 mm x 37 mm x 10 mm
	CZ 20034 11b	0.005	0.0032	0.007	0.007	0.011	.	.	(0.005)	0.007	.	.	40 mm Ø x 18 mm
	VS ChG 38	~34 mm Ø x ~37 mm
	CZ 02033 5b	.	0.014	0.020	40 mm Ø x 18 mm
	VS ChL2/1	~38 mm Ø x ~38 mm
	CZ 20034 11a	0.005	0.0018	0.011	0.017	0.013	.	.	(0.005)	0.007	.	.	40 mm Ø x 18 mm
	SCRM 652/4	48 mm x 42 mm x 12 mm
	DSZU CH07	.	(0.13)	.	(10)	.	(0.01)	~35 mm x ~35 mm x ~19mm
	CZ 02033 5c	.	0.0078	0.007	(0.002)	(0.010)	.	(0.009)	.	.	40 mm Ø x 18 mm
	11X C4S	0.0235	0.0351	0.0070	.	.	.	0.0126	0.034	0.0055	0.009	.	0.099	.	.	.	~40 mm Ø x ~15 mm
	SCRM 675	0.035	40 mm x 37 mm x 10 mm
	SCRM 655/4	48 mm x 42 mm x 12 mm
	Y 2863-1	.	0.0024	30 mm Ø x 18-30 mm

ALLOYED CAST IRON, CHART 1 of 2

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
2	DSZU CH021	3.93	3.66	0.064	0.009	0.52	0.369	5.86	9.07	0.168	4.42	.	.	0.093	0.61	.	.
1	VS ChG 41/1	3.88	1.23	0.037	0.090	1.77	0.56	5.84	8.7	.	0.50	.	.	0.21	0.25	.	.
2	BAS NCRM5	3.70	0.27	0.025	0.015	1.15	0.204	6.74	10.44	.	0.10	.	.	.	0.06	.	.
1	SRM C1292	3.47	0.55	0.049	0.016	0.59	0.36	5.04	11.4	.	0.25	.	.	.	0.041	.	.
2	BAS CRRM5/2	3.43	0.30	0.029	0.018	0.20	0.22	0.36	30.35	0.15	0.63	.	.	0.009	0.11	.	.
1	Y 451052-1	3.31	1.54	0.369	0.0047	0.098	0.449	2.57	1.17	.	1.47	0.952	.
1	BS PM15	3.54	0.416	0.0198	0.0127	0.912	0.142	0.203	5.33	0.0025	1.22	(0.00001)	0.0034	0.0029	14.79	(0.0002)	0.111
1	VS ChG 48	3.44	0.100	0.0070	0.0039	0.923	0.90	0.280	22.79	0.049	0.591	.	0.0018	0.0022	0.0016	0.072	.
1	VS ChG 44/1	3.25	1.91	0.018	0.029	1.28	2.46	0.210	25.4	.	0.028	.	.	0.43	0.106	.	.
1	11X 15309T	3.18	1.53	0.034	0.021	1.22	0.056	0.152	24.9	0.097	0.066	.	0.0047	0.013	0.098	.	.
1	Y 451052-7	3.13	0.201	0.024	0.116	2.48	0.154	0.129	31.26	.	0.086	.	.	0.033	0.087	.	.
2	58A SC01141	3.08	0.62	0.045	0.036	0.56	0.77	1.21	15.32	.	2.70	.	.	0.020	0.28	.	.
1	SRM C1290	3.04	0.66	0.030	0.013	0.971	0.065	0.917	30.5	.	(0.041)	.	.	.	0.442	.	.
1	Y TSK205	3.03	0.16	0.041	0.088	1.65	0.35	0.37	30.35	.	0.22	.	.	.	0.077	.	0.108
1	Y 451054-2	3.00	1.42	0.133	0.016	0.56	0.324	1.43	7.23	.	2.48	.	.	0.015	0.88	.	.
1	NCS HS11788	2.97	1.62	0.191	0.010	3.29	0.51	17.77	2.56	(0.0023)	0.0013	.	0.0003	0.043	0.017	.	.
1	Y 451052-2	2.96	1.24	0.211	0.0077	0.491	1.57	1.99	9.75	.	2.17	.	.	0.300	0.669	.	.
2	BAS NIRM5/1	2.95	1.01	0.103	0.005	1.50	0.21	21.7	0.51	0.055	.
2	58A ZS01036	2.95	0.719	0.077	0.024	0.970	0.448	0.806	13.89	.	0.683	.	0.048	0.035	0.135	.	.
2	BAS NIRM2/2	2.94	2.01	0.096	0.007	1.43	5.93	13.69	1.48	0.044	.
2	BAS CRRM4/2	2.93	0.58	0.049	0.042	0.45	0.53	0.58	21.93	<0.005	1.15	.	.	0.008	0.11	.	.
2	11X 20003K	2.91	1.53	0.174	0.007	3.03	0.52	17.8	2.53
1	11X S/1 Cr3J	2.91	0.861	0.072	0.023	1.07	9.01	14.53	1.61
2	DSZU CH022	2.90	1.76	0.033	0.018	0.43	2.53	2.19	14.85	0.053	2.65	.	.	0.078	0.45	.	.
2	11X 20001J	2.90	0.58	0.005	0.143	1.01	0.01	21.4	1.50
1	11X 15294W	2.76	0.451	0.082	0.029	0.36	0.103	0.309	29.3	(0.147)	0.091	0.012	0.036	.	0.132	.	.
1	Y 451054-3	2.73	1.09	0.105	0.036	0.99	0.451	1.20	12.97	.	2.08	.	.	0.045	0.66	.	.
1	VS ChG 45	(2.7)	1.01	0.096	0.047	2.96	0.040	0.60	32.65	.	0.198	.	.	0.011	0.111	.	.
1	VS ChG 42/1	2.69	2.78	0.068	0.034	0.411	1.37	0.26	14.8	.	1.87	.	.	0.131	0.48	.	.
2	BAS NCRM4	2.66	0.40	0.203	0.012	2.13	0.68	5.34	7.94	.	0.57	.	.	.	0.11	.	.
1	NCS HS11787	2.65	1.08	0.067	0.037	2.07	0.306	19.84	1.98	(0.085)	0.0014	.	0.0054	0.022	0.0096	.	.
1	11X 15310B	2.63	0.97	0.070	0.029	0.99	2.37	4.59	20.7	0.018	0.92	.	.	0.034	0.096	.	.
1	11X 0331-2M	2.62	1.85	0.050	(0.09)	3.14	6.68	15.1	1.54	0.137	0.067	0.019	0.0271	0.198	0.051	.	.
1	11X 15295S	2.58	1.02	0.059	0.048	0.783	0.213	0.326	28.5	0.122	0.363	0.008	0.026	0.008	0.270	.	.
1	Y TSK201	2.56	1.07	0.253	0.023	0.66	1.53	2.44	10.14	.	2.56	.	.	.	0.42	.	0.029
2	BAS NIRM6/1	2.53	4.07	0.225	0.049	2.68	0.11	26.9	1.02	.	0.51
2	BAS NIRM3	2.51	0.51	0.208	0.096	2.21	1.00	17.8	2.43
1	VS ChG 47	2.43	0.949	0.099	0.083	2.73	0.0104	0.149	14.45	0.0056	0.0019	.	0.093	0.041	0.129	.	.
1	VS ChG 45/1	1.96	0.59	0.021	0.0091	3.08	0.056	0.95	33.8	.	0.209	.	.	.	0.21	.	.
1	VS ChG 43/1	0.87	1.02	0.063	0.076	4.44	0.171	0.439	23.7	.	0.107	.	.	0.033	0.040	.	.

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
	Number	B	Ce	Co	Nb	W	Zr		Units								Other
	DSZU CH021	35 mm x 35 mm x 16 mm								
	VS CHG41/1	-37 mm ϕ x -22 mm								
	BAS NCRM5	40 mm x 37 mm x 10 mm								
	SRM C1292	32 mm ϕ x 19 mm								
	BAS CRRM5/2	48 mm x 42 mm x 12 mm								
	Y 451052-1	0.177	.	.	0.018	0.015	.	.	30 mm ϕ x 18-30 mm								
	BS PM15	.	.	0.0330	0.014	0.109	(0.0005)	0.109	38 mm ϕ x 19+ mm 17025	Fe:[73.0]	As:0.0040	N:0.111	O:0.0129				
	VS ChG 48	As:0.0021	.	0.044	.	.	Sb:0.0017	.	-35 mm ϕ x -17 mm								
	VS CHG44/1	-37 mm ϕ x -22 mm								
	11X 15309T	.	.	0.76	0.056	0.022	.	.	-40 mm ϕ x -15 mm								
	Y 451052-7	0.015	.	.	0.010	0.175	.	.	30 mm ϕ x 18-30 mm								
	58A SC01141	-35 mm ϕ x -30 mm								
	SRM C1290	32 mm ϕ x 19 mm								
	Y TSK205	35 mm ϕ x 18-30 mm								
	Y 451054-2	30 mm ϕ x 18-30 mm								
	NCS HS11788	0.0008	.	(0.0063)	.	(0.0002)	.	.	31 mm ϕ x 28 mm	As: 0.014							
	Y 451052-2	0.142	.	.	0.182	1.99	.	.	30 mm ϕ x 18-30 mm								
	BAS NIRM5/1	.	0.016	.	0.15	.	.	.	48 mm x 42 mm x 12 mm								
	58A ZS01036	.	.	0.024	0.025	0.172	.	.	-32 mm ϕ x -30 mm	As: (0.003)							
	BAS NIRM2/2	.	0.018	48 mm x 42 mm x 12 mm								
	BAS CRRM4/2	48 mm x 42 mm x 12 mm								
	11X 20003K	40 mm ϕ x 15 mm								
	11X S/1 Cr3J	-40 mm ϕ x -15 mm								
	DSZU CH022	35 mm x 35 mm x 16 mm								
	11X 20001J	40 mm ϕ x 15 mm								
	11X 15294W	.	.	0.128	.	0.265	.	.	-40 mm ϕ x -15 mm								
	Y 451054-3	30 mm ϕ x 18-30 mm								
	VS ChG45	-36 mm x -36 mm ϕ x -18 mm	last							
	VS CHG42/1	-37 mm ϕ x -22 mm								
	BAS NCRM4	40 mm x 37 mm x 10 mm								
	NCS HS11787	0.0007	.	(0.0054)	.	(0.0002)	.	.	31 mm ϕ x 28 mm	As: 0.0075							
	11X 15310B	.	.	0.157	.	0.188	.	.	-40 mm ϕ x -15 mm								
	11X 0331-2M	.	.	0.179	0.134	0.004	0.0022	.	-40 mm ϕ x -15 mm								
	11X 15295S	.	.	1.55	0.091	0.202	(0.0012)	.	-40 mm ϕ x -15 mm								
	Y TSK201	35 mm ϕ x 18-30 mm								
	BAS NIRM6/1	.	0.006	48 mm x 42 mm x 12 mm								
	BAS NIRM3	.	0.007	.	0.09	.	.	.	40 mm x 37 mm x 10 mm								
	VS ChG 47	As:0.014	.	0.0042	.	.	Sb:0.040	.	-35 mm								

ALLOYED CAST IRON, CHART 2 of 2

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
1	Y 451052-3	2.40	1.06	0.115	0.015	0.821	0.953	1.55	13.30	.	0.869	.	.	0.171	0.482	.	.
2	BAS CRRM3/2	2.37	0.92	0.073	0.087	1.21	1.09	1.35	18.78	0.102	1.58	.	.	0.015	0.042	.	.
2	DSZU CH023	2.33	0.43	0.023	0.073	0.98	0.054	0.715	23.45	0.255	1.46	.	.	0.38	0.288	.	.
1	Y 451054-4	2.31	0.725	0.071	0.046	1.40	0.739	0.914	17.60	.	1.44	.	.	0.084	0.46	.	.
1	Y TSK200	2.11	0.82	0.319	0.022	0.17	1.86	3.22	4.97	.	3.50	.	.	.	0.60	.	0.021
2	DSZU CH024	2.01	1.22	0.102	0.037	2.18	0.88	0.222	27.84	0.096	3.86	.	.	0.099	0.164	.	.
1	Y 451052-4	2.00	0.803	0.090	0.025	1.16	0.738	1.07	18.28	.	0.598	.	.	0.087	0.380	.	.
2	BAS NIRM4	1.97	2.37	0.051	0.008	3.03	0.52	20.2	3.56	0.014	.
1	NCS HS11789	1.97	1.08	0.048	0.076	2.58	6.39	17.80	2.51	0.061	0.062	0.015	0.014	0.011	0.0093	.	.
2	BAS CRRM2/1	1.92	1.11	0.097	0.079	1.18	1.59	1.61	14.13	0.054	2.44	.	.	0.070	0.063	.	.
1	VS ChG 46	1.87	0.067	0.0106	0.108	3.24	0.0109	5.44	8.58	.	0.63	.	.	.	0.109	.	.
2	BAS NIRM1/1	1.83	6.74	0.058	0.015	3.26	0.20	11.8	0.300	0.021	.
2	BAS CRRM1/1	1.83	1.45	0.132	0.099	1.53	2.01	2.03	11.18	0.117	3.05	.	.	0.096	0.040	.	.
1	Y 451054-5	1.83	0.466	0.043	0.091	1.80	0.904	0.517	23.40	.	0.739	.	.	0.068	0.26	.	.
1	Y TSK202	1.81	1.16	0.201	0.057	2.00	1.10	1.91	15.42	.	2.20	.	.	.	0.33	.	0.075
2	DSZU CH025	1.80	0.387	0.030	0.026	2.70	1.23	1.77	35.14	0.351	0.302	.	.	0.117	0.044	.	.
2	BAS CRRM1/2	1.70	1.43	0.16	0.099	1.84	1.97	2.03	11.28	0.140	3.06	.	.	0.054	0.063	.	.
2	DSZU CH026	1.62	0.305	0.050	0.032	1.14	0.288	3.63	35.87	0.059	0.96	.	.	0.013	0.067	.	.
1	Y 451052-5	1.48	0.579	0.041	0.058	1.37	0.583	0.708	22.55	.	0.359	.	.	0.056	0.314	.	.
2	BAS NIRM8/2	1.45	1.58	0.105	0.014	5.61	0.23	35.3	2.47	.	0.77	0.033	.
1	Y 451054-6	1.45	0.254	0.024	0.123	2.38	1.15	0.216	28.96	.	0.213	.	.	0.084	0.13	.	.
1	Y TSK203	1.23	0.68	0.117	0.044	0.46	0.75	1.55	19.93	.	1.58	.	.	.	0.22	.	0.094
1	Y 451052-6	1.16	0.302	0.033	0.086	1.44	0.845	0.289	25.76	.	0.150	.	.	0.019	0.146	.	.
1	Y TSK204	0.91	0.34	0.078	0.063	1.00	0.53	0.97	25.37	.	0.95	.	.	.	0.14	.	0.114

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
	Number	B	Ce	Co	Nb	W	Units		Other								
	Y 451052-3	0.102	.	.	0.149	1.57	30 mm Ø x 18-30 mm										
	BAS CRRM3/2	40 mm x 37 mm x 10 mm										
	DSZU CH023	35 mm x 35 mm x 16 mm										
	Y 451054-4	30 mm Ø x 18-30 mm										
	Y TSK200	35 mm Ø x 18-30 mm										
	DSZU CH024	35 mm x 35 mm x 16 mm										
	Y 451052-4	0.086	.	.	0.071	1.05	30 mm Ø x 18-30 mm										
	BAS NIRM4	.	0.011	.	0.37	.	40 mm x 37 mm x 10 mm										
	NCS HS11789	0.0008	.	(0.0075)	.	(0.0002)	31 mm Ø x 28 mm		As: 0.0076		Bi: 0.067						
	BAS CRRM2/1	40 mm x 37 mm x 10 mm										
	VS ChG 46	Sb:0.140	~35 mm Ø x ~17 mm										
	BAS NIRM1/1	.	0.022	.	.	.	40 mm x 37 mm x 10 mm										
	BAS CRRM1/1	40 mm x 37 mm x 10 mm		last								
	Y 451054-5	30 mm Ø x 18-30 mm										
	Y TSK202	35 mm Ø x 18-30 mm										
	DSZU CH025	35 mm x 35 mm x 16 mm										
	BAS CRRM1/2	40 mm x 37 mm x 10 mm										
	DSZU CH026	35 mm x 35 mm x 16 mm										
	Y 451052-5	0.076	.	.	0.022	0.694	30 mm Ø x 18-30 mm										
	BAS NIRM8/2	.	0.013	.	.	.	48 mm x 42 mm x 12 mm										
	Y 451054-6	30 mm Ø x 18-30 mm										
	Y TSK203	35 mm Ø x 18-30 mm										
	Y 451052-6	0.055	.	.	0.014	0.370	30 mm Ø x 18-30 mm										
	Y TSK204	35 mm Ø x 18-30 mm										
	Number	B	Ce	Co	Nb	W	Units		Other								

RM CAST IRON MUSHROOMS

CONTINUED ON THE NEXT PAGE

typical analysis

each unit is one pair of 43 mm Ø x 5 mm mushroom discs

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF F019	4.04	1.05	1.05	0.032	0.057
CTIF F012	3.71	1.86	0.44	0.038	0.004	0.77	.	.	0.008	.	.	0.011	.	.	.
CTIF F08	3.6	1.04	0.37	0.107	0.021	0.215	0.30	0.30	.	.	0.005	0.05	0.055	0.014	.
CTIF FCR7	3.59	1.07	0.365	0.099	0.0427	0.704	0.947	33.65	.	.	2.62
CTIF F06	3.49	0.55	0.715	0.87	0.106	0.120	0.128	0.45	.	.	0.202	0.039	0.080	0.110	.
CTIF F010	3.5	0.67	1.05	0.20	0.101	0.114	0.118	0.38	.	.	0.20	.	0.1	0.08	.
CTIF NH3	3.47	0.85	0.175	0.36	0.024	0.031	2.53	1.76	.	.	0.73
CTIF F011	3.45	1.57	0.685	0.052	0.103	0.211	0.235	0.34	.	(0.013)	0.225	0.066	0.078	0.113	.
CTIF F018	3.43	1.24	0.590	1.34	0.136	0.049	0.140	0.170	.	.	0.179	0.046	0.057	0.102	.
CTIF NH7-1	3.43	0.95	0.63	0.035	0.022	0.105	5.53	9.02
CTIF FCR5	3.43	0.35	0.62	0.052	0.0175	1.02	2.69	28.5	.	.	3.27
CTIF FT2-1	3.39	1.415	0.78	0.045	0.095	0.01	0.070	0.030	0.100	0.405	.
CTIF NiMo1	3.22	2.585	0.200	0.0590	(0.0030)	0.376	2.165	0.0353	.	0.0205	0.457	0.0020	0.0190	0.0169	.
CTIF FL7	3.22	2.550	0.100	1.34	0.048	0.351	0.232	0.043	.	.	0.335	0.0291	0.0525	0.0796	.
CTIF FT3	3.2	1.55	0.345	0.063	0.051	0.015	0.092	0.685	0.2	0.016	.
CTIF NH7-2	3.2	1.20	0.91	0.034	0.0120	0.108	5.53	8.87
CTIF F05	3.2	0.7	0.2	1.30	0.027	0.12	0.172	0.3	.	.	0.41	0.109	0.04	0.14	.
CTIF NH9	3.13	1.24	0.65	0.087	0.029	0.203	4.11	11.70	.	.	0.059
CTIF NR Cu1	3.12	1.465	0.172	0.090	0.99	4.95	18.02	0.994	(0.095)
CTIF FL6	3.1	1.4	0.6	0.012	0.18	0.079	1.03	0.167	.	0.028	0.50	0.005	0.15	0.033	.
CTIF FL10	3.1	1.3	0.85	0.323	0.066	0.104	0.10	(0.07)	(0.03)	.	0.0335	0.028	0.045	0.048	(0.02)
CTIF FFA 1	3.090	0.0300	0.100	0.0022	0.0009	0.0622	0.0450	0.0710	.	0.0097	0.0109	.	0.0010	0.0010	.
CTIF NR 8S	3.05	1.41	4.39	0.124	.	0.071	14.20	0.191
CTIF F017	3.01	2.48	0.475	0.470	0.168	(0.006)	0.021	(0.016)	.	0.032	.	0.024	0.032	0.018	.
CTIF FAL 1	3.0	1.0	0.2	0.04	<0.001	0.2	0.06	0.04	2.1	.	0.015	.	0.01	.	.
CTIF NR 3L	2.99	3.05	0.72	0.088	0.052	0.26	21.58	2.97
CTIF NH1	2.98	1.35	0.90	0.060	0.105	1.99	1.38	0.83	.	.	1.45
CTIF NH8	2.98	0.80	0.57	0.052	0.076	0.065	8.16	5.03	.	.	0.125
CTIF NR 3S	2.92	2.91	0.77	0.024	.	0.33	24.63	3.05
CTIF FT1	2.9	2.12	0.71	0.12	0.025	0.012	0.11	0.057	.	.	.	0.067	0.19	0.525	.

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF NR 8L	2.89	1.70	5.19	0.054	0.030	0.075	13.33	0.165
CTIF NH4	2.84	0.49	0.28	0.12	0.022	0.09	3.60	2.46	.	.	0.30
CTIF F04	2.81	1.51	0.64	0.58	0.009	0.31	0.32	0.17	.	.	0.095	0.013	0.075	0.049	.
CTIF FCR2	2.86	1.07	0.740	0.137	0.055	0.135	1.87	11.8	.	.	3.88
CTIF FL5	2.8	2.3	0.4	0.02	(0.005)	0.5	0.05	0.35	.	0.010	0.01	0.07	0.01	0.01	.
CTIF FCR Ni3	2.74	0.69	0.47	0.036	0.011	.	11.05	31.65
CTIF NH6	2.70	2.28	0.355	0.066	0.036	0.115	7.06	6.60	.	.	0.11
CTIF F09	2.7	1.5	0.7	0.02	0.015	0.31	0.355	0.18	.	.	0.13	0.144	0.017	0.022	.
CTIF FL4	2.6	2.91	0.5	0.288	0.137	0.0168	0.061	0.45	.	.	0.090	0.011	0.0296	0.116	.
CTIF NR 1S	2.58	3.02	1.54	0.19	0.0015	0.11	20.60	2.00
CTIF NR 1L	2.50	3.00	1.34	0.125	0.10	0.49	25.87	1.74
CTIF NH2	2.50	1.81	1.04	0.047	0.058	1.02	1.78	1.26	.	.	1.01
CTIF NR Cu2	2.48	2.07	1.078	0.113	0.049	6.50	15.85	2.05
CTIF NR 4S	2.47	4.87	1.71	0.145	.	0.63	18.30	1.50
CTIF FCR4	2.47	1.40	2.05	0.097	0.066	1.32	0.571	24.2	.	.	2.16
CTIF FCR1	2.46	0.48	0.63	0.019	0.007	0.031	1.30	18.71	.	.	1.41
CTIF F07	2.45	0.675	0.70	0.84	0.085	0.125	0.15	0.455	.	.	0.26	.	0.065	0.13	.
CTIF NR 4L	2.41	5.89	1.495	0.155	0.010	0.758	15.90	1.403
CTIF NR 2S	2.32	1.43	0.530	0.062	.	0.210	36.3	0.51
CTIF NH5	2.31	0.31	0.24	0.115	0.04	0.035	4.90	2.85	.	.	0.017
CTIF FL3	2.3	2.1	0.27	0.729	(0.013)	0.102	0.553	0.107	.	.	0.106	0.111	0.05	0.049	.
CTIF NR 4G	2.24	5.60	1.72	0.11	(0.002)	0.64	21.30	1.40
CTIF NR 2G	2.25	1.47	0.380	0.0476	(0.003)	0.232	36.34	0.395
CTIF FL2	2.18	3.61	0.0400	0.049	0.082	0.0497	0.0238	0.440	(0.006)	0.0263	(0.004)	0.140	0.0750	0.201	.
CTIF FL1	2.1	3.2	0.80	0.118	0.0765	0.0195	0.245	0.06	.	(0.022)	0.038	0.305	0.020	0.015	.
CTIF FCR Ni2	2.02	1.50	0.61	0.185	0.024	.	13.05	29.00
CTIF NR Cu3	1.94	3.12	0.60	0.046	0.016	8.05	13.3	3.50
CTIF NR 6S	1.82	2.44	0.99	0.019	.	0.03	30.75	1.06
CTIF NR 5L	1.77	2.99	1.207	0.037	0.083	0.48	33.89	0.27
CTIF NR 6L	1.76	2.07	0.70	0.031	0.063	0.020	30.37	3.49
CTIF NR 5S	1.67	1.97	1.23	0.035	.	0.50	27.05	0.24
CTIF FCR6	1.44	0.76	1.47	0.201	0.086	0.480	0.188	30.84	.	.	0.455
CTIF FCR Ni1	1.27	1.63	0.71	0.41	0.06	0.02	16.50	26.20

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
--------	---	----	----	---	---	----	----	----	----	----	----	----	----	---	---

CAST IRON MUSHROOMS

CONTINUED FROM THE PREVIOUS PAGE

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF F019	0.0005	.
CTIF F012
CTIF F08
CTIF FCR7
CTIF F06
CTIF F010
CTIF NH3
CTIF F011
CTIF F018	0.0040
CTIF NH7-1
CTIF FCR5
CTIF FT2-1
CTIF NiMo1
CTIF FL7	(0.0266)	(0.010)	.	(0.010)	.	0.0035
CTIF FT3
CTIF NH7-2
CTIF F05
CTIF NH9
CTIF NR Cu1
CTIF FL6	.	0.008
CTIF FL10	(0.022)	.	(0.012)	(0.004)	.	.	(0.018)	(0.002)	(0.032)	(0.001)	(0.029)
CTIF FFA 1	0.0109	0.0125
CTIF NR 8S
CTIF F017
CTIF FAL 1
CTIF NR 3L
CTIF NH1
CTIF NH8
CTIF NR 3S
CTIF FT1
Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF NR 8L
CTIF NH4
CTIF F04
CTIF FCR2
CTIF FL5	.	(0.002)	.	(0.0005)
CTIF FCR Ni3
CTIF NH6
CTIF F09
CTIF FL4	(0.05)	.	.	(0.003)	.	0.007
CTIF NR 1S
CTIF NR 1L
CTIF NH2
CTIF NR Cu2	(0.0079)
CTIF NR 4S
CTIF FCR4
CTIF FCR1
CTIF F07
CTIF NR 4L
CTIF NR 2S - producer low stock, only undersized pieces remaining
CTIF NH5
CTIF FL3	0.008
CTIF NR 4G
CTIF NR 2G	0.27
CTIF FL2	.	.	.	(0.0135)
CTIF FL1
CTIF FCR Ni2
CTIF NR Cu3
CTIF NR 6S
CTIF NR 5L
CTIF NR 6L
CTIF NR 5S
CTIF FCR6
CTIF FCR Nil
Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn

CARBON STEEL

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

Table with columns: Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Co, Mo, N, V, W. Rows include materials like VS UG128, BS 54J, IARM Fe1050-18, BS 1040, BS 1030A, BS 1026A, BS 54J, NM 309, IMZ 71A, DSZU C041a, etc.

Table with columns: Number, As, B, Fe, Nb, O, Sb, Sn, Ti, Alloy, Units, Others. Rows include VS UG128, BS 54J, IARM Fe1050-18, BS 1040, BS 1030A, BS 1026A, BS 54J, NM 309, IMZ 71A, DSZU C041a, etc.

RESULFURIZED STEEL

= Class, where 1 = CRM and 2 = RM

Table with columns: Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Co, Mo, N, V, W. Rows include IARM 307B, CZ CM-22A. Second table below with columns: Number, As, Nb, Sn, Ti, Alloy, Units. Rows include IARM 307B, CZ CM-22A.

CRM LOW ALLOY STEEL WITH EXTENSIVE ANALYSIS

Table with columns: Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Co, Mo, N, Ti, V, W. Rows include VS UG143, VS UG146, VS UG144, VS UG145, VS UG141, VS UG142. Second table below with columns: Number, As, B, Bi, Ca, Ce, Nb, O, Pb, Sb, Sn, Ta, Zn, Zr, Units. Rows include VS UG143, VS UG146, VS UG144, VS UG145, VS UG141, VS UG142.

LOW ALLOY AND TOOL STEEL, CHART 2 of 2

= Class, where 1 = CRM and 2 = RM

* Provisional Analysis

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
2 HRT FE2019-H	1.54	0.39	0.025	(0.003)	0.51	0.08	0.14	11.89	0.015	.	0.86	.	0.80	.
2 CZ LA-4D	1.143	1.266	0.028	0.0091	0.181	0.066	0.367	1.83	0.067	0.037	0.136	0.0064	0.103	0.025
1 ECRM 268-1D	1.134	0.293	0.0209	0.0154	0.373	0.123	0.143	4.57	.	0.0290	3.20	2.03	8.47	3.70
1 VS UG127	0.962	0.93	0.020	0.029	0.427	0.145	0.151	0.188	0.0051	.	.	0.0155	0.141	.
1 VS UG126	0.856	0.78	0.0128	0.0077	0.348	0.030	0.029	0.591	0.0015	.	.	0.0123	0.075	.
1 VS UG130	0.80	0.228	0.0078	0.0071	0.226	0.252	0.104	0.258
2 CZ CM-1D	0.735	1.80	0.0218	0.026	0.341	0.186	0.547	0.456	0.024	0.029	0.100	0.0124	0.089	0.063
1 12X LA5D	0.681	0.855	0.040	0.016	0.53	0.107	0.409	0.291	0.177	0.151	0.206	0.086	0.603	(0.004)
1 12X LA4C	0.657	0.374	0.050	0.0258	0.482	0.265	0.485	0.526	0.183	0.099	0.405	0.0116	0.372	0.091
1 NCS HS13752	0.51	0.99	0.027	0.011	0.21	.	.	0.67	.	.	0.27	.	0.09	.
1 DSZU C051	0.443	0.795	0.0162	0.029	0.293	0.140	0.041	0.048	(0.010)	(0.003)	.	.	(0.002)	.
1 IMZ 54/1	0.43	0.14	(0.009)	0.010	0.17	(0.034)	4.01	0.12	.	.	(0.007)	.	0.19	.
2 CZ LA-5C	0.439	1.87	0.017	0.0088	0.394	0.138	2.59	3.815	0.081	0.088	0.86	0.024	0.536	0.631
2 CZ CM-16B	0.421	0.762	0.0508	0.0376	0.574	0.296	0.733	0.635	0.128	0.058	0.424	0.0154	0.272	0.141
1 12X 15260X	0.404	1.67	0.034	0.086	0.390	0.119	0.499	2.48	0.57	0.085	0.093	.	0.417	.
1 SS 214/2	0.39	1.61	0.032	0.043	0.18	0.21	0.15	0.09	.	.	0.26	.	.	.
1 DSZU C045a	0.374	0.382	0.012	0.0032	0.267	0.191	0.147	1.45	0.86	0.010	0.184	0.0063	0.004	(0.005)
2 HRT FE2021-N	0.33	0.31	0.0178	0.0014	0.28	0.070	0.193	2.81	0.014	0.011	2.7	0.007	0.52	0.027
2 HRT FE2022-N	0.319	0.447	0.0058	(0.0011)	0.256	0.029	0.170	2.97	0.0134	0.0084	0.93	0.0060	0.279	(0.0050)
1 BS 1763 *	0.27	1.50	0.017	0.025	0.68	0.18	0.53	0.56	0.052	0.12	0.55	<0.05	0.29	0.023
1 BS 9325B	0.254	0.504	0.032	0.0067	0.38	0.166	3.13	1.22	0.027	0.0073	0.203	0.0112	0.0080	0.0036
2 CZ CM-8B	0.185	1.95	0.015	0.014	0.112	0.081	0.032	1.22	0.0028	0.007	0.011	0.0075	0.0078	(0.009)
1 IRSID 1658	0.180	0.618	0.014	0.032	0.160	0.345	0.241	0.147	0.029	.	0.046	.	(0.002)	.
2 HRT FE2019-N	0.17	1.27	0.015	(0.001)	0.30	0.03	0.33	0.75	0.068	(0.003)	0.40	0.0040	(0.003)	.
1 VS RG31	0.169	0.291	0.0048	0.006	0.39	0.46	2.08	1.31	.	0.28	0.306	.	0.207	0.39
1 DSZU C042a	0.132	0.488	0.0091	0.0062	0.286	0.137	0.195	0.995	0.018	0.009	0.31	(0.01)	0.189	(0.006)
1 12X 12746V	0.048	1.19	0.034	0.064	0.156	0.646	0.226	0.374	0.459	0.142	0.658	0.0208	0.105	.
1 VS UG102	0.045	1.78	0.0082	.	0.222	0.172	0.277	0.0143	0.036	.	0.209	.	.	.

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
--------	---	----	---	---	----	----	----	----	----	----	----	---	---	---

Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Units	Others
HRT FE2019-H	.	.	.	0.071	.	.	.	0.012	40 mm Ø x 20 mm	.
CZ LA-4D	0.010	.	.	0.0046	.	.	0.014	0.0154	~39 mm Ø x ~25 mm	Pb:0.040
ECRM 268-1D	0.0062	0.0009	.	.	.	0.0017	0.0078	.	38 mm Ø x 25 mm	.
VS UG127	0.0094	~38 mm Ø x ~20 mm	Bi:0.011 Pb:0.0049
VS UG126	~38 mm Ø x ~20 mm	Bi:0.0055 Pb:0.009
VS UG130	0.0093	~39 mm Ø x ~25 mm	.
CZ CM-1D	.	0.0017	.	0.050	.	0.0112	0.0144	0.054	~39 mm Ø x ~25 mm	.
12X LA5D	0.0101	.	.	0.0039	.	.	0.0142	0.080	~40 mm Ø x ~15 mm	Zr:0.0013
12X LA4C	0.018	~40 mm Ø x ~15 mm	Zn:0.006
NCS HS13752	0.006	38 mm Ø x 38 mm	.
DSZU C051	(0.002)	.	.	(0.001)	.	.	(0.004)	(0.001)	40 mm Ø x 25 mm	.
IMZ 54/1	40 mm Ø x 40 mm	.
CZ LA-5C	0.026	.	.	0.057	Pb:0.015	0.018	0.031	0.048	~37 mm Ø x 25 mm	.
CZ CM-16B	0.065	0.0128	Ca:0.00033	0.094	Pb:0.0294	0.0282	0.0289	0.121	37 mm Ø x 25 mm	Zn:0.0156 Zr:0.102
12X 15260X	0.044	.	.	0.183	.	Pb:0.0012	0.0021	0.0064	~40 mm Ø x ~15 mm	Zr:0.0054
SS 214/2	42 mm Ø x 19 mm	.
DSZU C045a	0.010	(0.0004)	.	0.003	.	.	0.012	0.004	40 mm Ø x 25 mm	Ca:(0.002)
HRT FE2021-N	0.004	0.0006	Ce:0.0011	0.007	.	0.001	0.004	0.001	36 mm Ø x 20 mm	Zn:0.002 Zr:0.0012
HRT FE2022-N	(0.0025)	(0.0004)	.	(0.0034)	.	(0.0012)	0.0029	(0.0015)	31 mm Ø x 20 mm	.
BS 1763 *	0.072	0.003	[94.6]	0.14	<0.05	<0.05	0.015	0.31	37 mm Ø x 19 or 20 mm	Zr:0.027
BS 9325B	0.0033	(0.0003)	94.0	(0.002)	0.011	<0.05	(0.002)	0.0010	38 mm Ø x 30 mm	17025 Pb:0.0019 Ta:0.0020
CZ CM-8B	0.0035	0.0023	.	(0.002)	.	(0.004)	0.0126	0.0008	~39 mm Ø x 25 mm	.
IRSID 1658	0.034	0.022	(0.002)	40 mm Ø x 30 mm	.
HRT FE2019-N	.	0.0016	.	0.029	.	.	.	0.004	40 mm x 40 mm x 20 mm	Ca:0.0014
VS RG31	0.21	~45 mm Ø x ~28 mm	.
DSZU C042a	0.0069	(0.0005)	.	0.0025	.	.	0.0079	0.0029	40 mm Ø x 25 mm	.
12X 12746V	0.051	0.264	0.088	~40 mm Ø x ~15mm	.
VS UG102	.	.	.	0.071	~45 mm Ø x ~25 mm	Ca:0.0018

Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Units	Others
--------	----	---	----	----	---	----	----	----	-------	--------

SILICON STEEL

= Class, where 1 = CRM and 2 = RM

Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	N	V	W
2 CZ CM-12C	3.7	0.038	0.275	0.0103	0.0110	0.175	0.046	0.081	0.145	0.0044	0.012	0.0056	0.027	(0.004)
1 ECRM 191-3C	3.226	0.0027	0.153	0.0097	0.0005	0.0097	0.0124	0.0242	0.81	.	0.00127	0.00105	0.00043	.
1 DSZU C047A	1.94	0.789	0.411	0.022	0.0107	0.150	0.311	4.76	0.054	0.105	0.76	0.022	1.21	2.37
2 CZ CM-20A	1.74	0.63	0.594	0.0383	0.020	0.237	1.007	0.97	0.076	0.124	0.365	0.0086	0.225	0.104
1 SS 405/1	1.71	0.032	1.28	0.018	0.069	0.013	0.22	0.15	.	.	(0.002)	.	0.28	.
1 SS 409/1	1.46	0.082	0.44	0.025	0.021	0.048	3.06	0.94	.	0.014	0.65	.	0.09	.
1 IMZ 52/1	1.38	0.41	0.25	0.012	(0.009)	0.094	2.35	0.12	.	.	(0.041)	.	.	.
2 CZ LA-3G	1.29	0.626	0.68	0.047	0.035	0.236	1.01	1.377	0.047	0.127	0.326	0.011	0.232	0.105

Number	As	B	Nb	Pb	Sb	Sn	Ti	Zr	Units	Others
CZ CM-12C	0.0030	0.0033	0.0066	.	.	(0.005)	0.0128	.	~39 mm Ø x ~25 mm	Ca:0.0010
ECRM 191-3C	0.0014	0.00024	.	.	.	0.0013	0.0020	.	~30 mm Ø x ~39 mm	Mg:0.0036
DSZU C047A	(0.0095)	0.0006	0.020	.	.	0.0104	0.0096	.	40 mm Ø x 25 mm	Ca:0.0022
CZ CM-20A	0.073	0.0071	0.074	0.015	0.025	0.033	0.175	0.083	~37 mm Ø x ~25 mm	Zn:0.007
SS 405/1	38 mm Ø x 19 mm	.
SS 409/1	38 mm Ø x 19 mm	.
IMZ 52/1	40 mm Ø x 40 mm	.
CZ LA-3G	0.051	0.0039	0.071	0.0098	0.024	0.031	0.143	0.068	~39 mm Ø x ~25 mm	Ca:0.0016

LOW NICKEL STAINLESS STEEL

= Class, where 1 = CRM and 2 = RM

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
2 BS 93E	1.02	0.52	0.022	0.0010	0.90	0.12	0.35	17.33	0.009	0.048	0.50	0.0359	0.24	0.11
2 BS 98	0.309	0.48	0.019	0.0014	0.72	0.098	0.21	13.35	0.003	0.020	0.034	0.0181	0.075	0.009
2 DSZU C116	0.296	0.464	0.0214	0.0118	0.295	0.082	0.209	12.71	(0.006)	0.021	0.029	0.022	0.029	(0.01)
2 BS 97	0.216	0.71	0.021	0.0004	0.39	0.066	0.76	11.82	0.018	0.041	1.05	0.030	0.21	0.95
1 BS 183B	0.181	0.344	0.018	0.0042	0.41	0.074	1.96	12.45	0.0009	0.032	0.33	0.044	0.165	3.5
1 13X 12548N	0.175	0.510	0.023	0.189	0.193	0.264	1.10	12.70	(0.02)	0.388	1.42	0.102	0.025	0.038
1 BS 183C	0.173	0.368	0.015	0.0040	0.427	0.060	1.87	12.72	0.0020	0.027	0.189	0.039	0.109	2.83
1 BS 431A	0.159	0.53	0.019	0.0036	0.31	0.111	2.21	15.78	(0.0012)	0.041	0.172	0.058	0.079	0.021
2 DSZU C115	0.145	0.341	0.0278	0.0026	0.389	0.122	1.66	11.73	0.011	0.028	0.368	0.039	0.250	1.98
2 DSZU C119	0.128	0.229	0.027	0.0068	0.51	0.069	0.244	25.38	0.017	(0.01)	0.084	0.010	0.052	0.046
2 DSZU C117	0.071	0.200	0.0240	0.0122	0.393	0.091	0.52	16.89	0.012	0.019	0.044	0.008	0.027	(0.04)
2 BS 91E	0.066	0.42	0.017	0.002	0.52	0.05	0.17	16.58	(0.002)	0.02	0.035	0.032	0.09	0.01
1 IARM Fe174PH-18	0.041	0.47	0.024	(<0.0040)	0.52	3.33	4.73	15.10	0.007	0.047	0.315	0.0436	0.051	0.015
1 13X 41500A	0.038	0.596	0.021	0.0101	0.402	0.129	3.52	13.00		0.099	0.504	0.0504	0.091	.
1 13X 41008B	0.034	0.684	0.013	0.0070	0.761	0.267	0.338	12.36	0.028	0.053	0.042	0.0088	0.061	.
1 13X 40800A	0.032	0.804	0.034	0.0030	0.80	0.299	0.58	12.32	0.042	0.033	0.268	0.0054	0.034	0.005
2 DSZU C118	0.018	1.23	0.0057	0.0098	0.142	0.344	3.45	19.69	(0.004)	0.093	0.337	0.028	0.109	0.32
1 IARM Fe155PH-18	0.015	0.616	0.021	(0.0004)	0.430	3.35	4.79	15.13	0.014	0.024	0.129	0.0494	0.055	0.019
1 IARM Fe409-20	0.010	0.387	0.021	(0.0007)	0.52	0.0655	0.110	11.28	0.017	0.019	0.011	0.010	0.075	0.0036

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units				
BS 93E	.	.	.	0.005	0.0040	.	0.003	0.007	440C	41 mm Ø x	~7 mm	last of stock		
BS 98	(0.003)	(0.0002)	.	0.003	0.0038	.	0.006	0.002	420	38 mm Ø x	~7 mm	last of stock		
DSZU C116	.	.	.	(0.01)	.	.	(0.005)	(0.002)		40 mm Ø x	20 mm			
BS 97	.	.	.	0.007	.	.	(0.003)	(0.002)	422	35 mm Ø x	~7 or 19+ mm			
BS 183B	(0.005)	(0.0007)	80.4	(0.0075)	(0.0054)	0.0009	0.0046	(0.0016)	Greek Ascoloy	38 mm Ø x	~7 or 19+ mm	17025		
13X 12548N	(0.003)	.	.	0.49	.	0.019	0.0064	0.0027	Resulfurized	~40 mm Ø x	~15 mm			
BS 183C	0.0041	(0.0008)	81.1	0.0054	(0.005)	0.0007	0.0039	(0.002)	Greek Ascoloy	38 mm Ø x	~7 or 19+ mm	17025	Ca: 0.0006	
BS 431A	0.0033	0.0002	80.5	0.0062	0.0067	0.0012	0.0047	0.0010	431	38 mm Ø x	~7 or 19+ mm	17025	Zr: 0.0012	
DSZU C115	.	.	.	0.015	.	.	0.006	(0.0020)		40 mm Ø x	20 mm			
DSZU C119	.	.	.	(0.02)	.	.	(0.006)	1.02		40 mm Ø x	20 mm			
DSZU C117	.	.	.	(0.02)	.	.	(0.005)	0.59		40 mm Ø x	20 mm			
BS 91E	.	.	.	(0.004)	.	.	0.004	(0.002)	430	41 mm Ø x	~7 or 19+ mm			
IARM Fe174PH-18	.	.	.	(0.0015)	0.0035	.	0.0069	.	17-4 PH	31 mm Ø x	2 or 18 mm			
13X 41500A	.	.	.	0.040	.	.	.	0.0012	415	~40 mm Ø x	~15 mm			
13X 41008B	.	.	.	0.019	.	.	0.0081	.	410	~40 mm Ø x	~15 mm	Zr:0.047		
13X 40800A	0.004	.	.	0.020	.	(0.002)	0.0028	0.84	408	~40 mm Ø x	~15 mm			
DSZU C118	.	.	.	0.116	.	.	0.026	0.117		40 mm Ø x	20 mm			
IARM Fe155PH-18	(0.0026)	(0.0005)	75.03	0.273	0.0028	.	0.0021	.	15-5PH	31 mm Ø x	2 or 18 mm			
IARM Fe409-20	0.0026	.	.	0.0041	.	0.0011	0.0053	0.141	409	38 mm Ø x	2 or 19 mm			

Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units				
--------	----	---	----	----	---	----	----	----	-------	-------	--	--	--	--

STAINLESS AND HIGH ALLOY STEEL

= Class, where 1 = CRM and 2 = RM

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
1 IARM Fe422-22	0.239	0.687	0.021	0.0095	0.4	0.126	0.616	12.22	0.0024	0.022	0.97	0.050	0.210	1.03
1 IARM FeA100-18	0.222	(0.013)	(0.004)	<0.0010	(0.039)	(0.010)	11.2	2.98	(0.007)	13.4	1.19	(0.0010)	(0.007)	(0.006)
1 IMZ 303	0.105	1.23	0.038	0.011	0.74	0.018	8.26	19.56	0.100	0.017	.	0.0113	0.037	.
2 DSZU Cl20	0.078	0.158	0.0138	0.0030	0.35	0.122	8.46	30.8	(0.02)	(0.03)	(0.03)	0.042	0.041	(0.01)
1 IARM Fe309-18	0.066	1.61	0.029	(0.002)	0.30	0.430	12.2	22.42	.	0.248	0.357	.	0.073	0.063
1 BS 309	0.062	1.61	0.028	0.0011	0.24	0.349	12.16	22.40	(0.0025)	0.200	0.193	0.073	0.075	(0.031)
1 BS 347C	0.051	1.67	0.022	0.022	0.677	0.110	10.08	17.27	(0.003)	0.072	0.27	0.039	0.097	0.013
2 CZ SP-1B	0.050	1.67	0.039	0.30	0.505	0.47	8.32	17.42	(0.003)	0.161	0.40	0.063	0.060	0.032
1 IARM FeINVR36-22	0.0497	0.78	0.0041	0.0019	0.07	0.058	36.0	0.094	0.0023	0.010	0.012	0.0021	0.0013	(0.0328)
2 PV 112/1	0.047	1.577	0.018	0.023	0.515	0.102	11.14	17.56	.	.	2.03	.	.	.
2 HRT FE2021-H	0.041	1.19	0.021	0.002	0.34	0.17	12.7	15.6	0.007	0.044	1.11	0.088	0.59	(0.025)
1 13X 33425A	0.039	0.997	0.028	0.0052	0.85	0.204	20.90	22.3	0.017	0.092	2.52	0.0106	(0.014)	(0.006)
2 BS 95A	0.035	0.58	0.026	0.004	0.46	1.50	6.42	14.72	0.002	0.081	0.73	0.0255	0.52	0.02
1 13X 32180A	0.031	2.11	0.007	0.0093	0.485	0.49	10.16	18.92	0.043	0.040	0.245	0.0067	0.026	0.039
1 BS 2507	0.026	0.79	0.023	(0.0005)	0.32	0.222	6.94	25.3	(0.004)	0.040	3.75	0.273	0.064	0.074
2 TL 2001D	0.0244	0.679	0.022	0.0006	0.27	0.612	7.5	25.58	.	0.046	3.49	0.279	0.079	0.57
1 IARM FeKovar-18	0.024	0.26	(0.004)	(0.0055)	(0.09)	0.077	29.0	0.068	.	17.3	0.062	.	.	(0.020)
2 PV 111/1	0.0226	1.538	0.019	0.026	0.485	0.105	8.57	18.49	.	.	0.173	.	.	.
1 BS 186B	0.022	0.288	(0.0027)	0.0016	0.254	0.057	36.1	0.11	0.0080	0.041	0.025	0.0033	(0.002)	(0.007)
1 BS 160B	0.022	0.27	0.0033	0.0032	0.112	0.059	29.13	0.06	(0.005)	17.24	0.047	0.0006	0.0039	(0.011)
2 TL 2003D	0.0193	1.068	0.0274	0.0169	0.5020	0.2773	9.231	18.25	.	0.1270	0.2871	0.0556	0.0711	0.0150
1 IARM FeN40-18	0.019	9.13	0.025	0.0012	0.31	0.421	6.42	19.45	.	0.122	0.343	0.348	0.086	0.030
1 BS 254	0.019	0.95	0.026	0.0009	0.312	0.612	18.47	20.2	<0.01	0.08	6.07	0.210	0.062	(0.02)
1 IARM FE2507-21	0.019	0.85	0.024	0.0005	0.36	0.125	7.12	25.2	(0.0051)	0.039	3.76	0.27	0.067	0.026
1 IARM Fe415-21	0.018	0.640	0.028	0.013	0.42	0.198	3.55	11.64	0.0018	0.065	0.537	0.073	0.086	0.042
1 BS 179A	0.017	1.04	0.021	0.001	0.44	1.94	5.84	25.45	(0.009)	0.58	3.24	0.184	0.070	(0.2)
1 IARM Fe254SMO-21	0.017	0.892	0.022	0.0010	0.301	0.77	18.1	19.7	0.022	0.118	6.09	0.200	0.052	0.041
2 TL 2002D	0.0149	1.30	0.022	0.0206	0.53	0.438	11.0	16.7	0.087	0.087	2.05	0.0341	0.068	.
1 ECRM 298-2D	0.0140	0.788	0.0210	0.0006	0.331	0.105	6.87	24.91	0.0148	0.0482	3.78	0.277	0.070	0.0094
1 IARM Fe904L-22	0.0133	1.14	0.020	0.0007	0.654	1.30	24.0	19.3	0.036	0.126	4.03	0.045	0.064	0.024
1 IARM Fe304L-22	0.013	1.46	0.031	0.0324	0.287	0.443	8.65	18.21	0.0020	0.331	0.362	0.083	0.081	0.066
1 SS 477	0.0102	1.623	0.0209	0.00039	0.473	1.340	25.07	20.38	0.0303	0.0875	4.23	0.0562	0.0527	.
2 BS 96A	0.009	0.04	0.007	0.004	0.06	2.07	8.38	11.62	0.08	0.03	0.021	.	0.07	.
1 IARM 99D	(0.006)	(0.013)	(0.004)	0.0011	(0.03)	(0.045)	18.4	(0.12)	0.117	9.24	4.8	0.0014	(0.037)	(0.010)
1 BS 161B	0.0031	0.010	(0.004)	0.0007	0.0107	0.010	18.56	0.034	0.073	9.28	4.87	0.0011	0.0011	0.010
1 IARM FeC250-21	0.0028	0.022	0.0033	0.0006	0.0091	(0.0041)	18.6	(0.0093)	0.101	7.92	4.93	0.0004	(0.0074)	(0.0069)
1 BS M250 *	0.002	0.025	0.003	<0.005	<0.05	0.004	18.7	0.005	0.093	7.93	4.92	<0.005	<0.005	0.008

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
--------	---	----	---	---	----	----	----	----	----	----	----	---	---	---

Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units	
IARM Fe422-22	0.0039	0.0006	.	0.013	0.0073	0.0009	0.0035	0.0017	422	31 mm Ø x 2 or 18 mm	Ca: 0.0029
IARM FeA100-18	.	.	.	0.070	(0.0009)	.	(0.004)	(0.008)	Aermet 100	31 mm Ø x 2 or 18 mm	
IMZ 303	0.60		40 mm Ø x 37 mm	
DSZU Cl20	.	.	.	0.015	.	.	0.004	0.005		40 mm Ø x 20 mm	
IARM Fe309-18	0.0065	.	.	0.021	.	0.0018	0.012	.	309	-38 mm Ø x -3 or -19 mm	
BS 309	0.0048	(0.0004)	62.6	0.0090	0.0027	(0.0017)	0.0089	0.0020	309, 309H	38 mm Ø x -7 or 19+ mm	17025 Ca: 0.0010
BS 347C	(0.003)	0.0018	69.1	0.58	0.0053	(0.002)	0.0034	(0.004)	347	44 mm Ø x -7 or 19+ mm	17025
CZ SP-1B	(0.003)	0.0007	.	(0.012)	.	.	0.013	(0.002)		-37 mm Ø x -25 mm	
IARM FeINVR36-22	0.0029	0.0019	.	(0.0016)	(0.0042)	(0.0006)	0.0042	(0.0020)	INVAR-36	31 mm Ø x 2 or 18 mm	Se: 0.21
PV 112/1	0.394	316 Ti	40 mm Ø x 25 mm	
HRT FE2021-H	0.004	0.0021	.	0.57	.	0.003	0.005	0.004	X8CrNiMoVNb16-13	50 mm Ø x 20 mm	
13X 33425A	(0.0021)	.	.	0.047	.	(0.002)	0.0106	0.178		31 mm Ø x 2 or 18 mm	
BS 95A	.	0.0010	.	0.55	.	.	0.008	(0.003)	450	38 mm Ø x -7 or 19+ mm	
13X 32180A	(0.003)	(0.0011)	.	(0.0021)	.	(0.0011)	0.0116	0.81	ER321	-40 mm Ø x -15 mm	
BS 2507	0.0046	0.0021	62.3	(0.011)	0.0038	0.0008	0.0050	0.0028	2507	38 mm Ø x -7 or 19+ mm	17025
TL 2001D	.	.	.	0.024	Super Duplex	40 mm Ø x 20 mm	
IARM FeKovar-18	.	.	53.3	.	.	.	0.0021	.	Kovar	31 mm Ø x 2 or 18 mm	
PV 111/1	304 L	40 mm Ø x 25 mm	
BS 186B	0.0022	(0.0006)	63.0	(0.002)	0.0011	(0.0007)	0.0025	0.0028	Invar 36	43 mm Ø x -7 or 19+ mm	17025 Zr: 0.0020
BS 160B	<0.005	0.0003	53.0	0.0015	0.0010	(0.0009)	0.0020	(0.003)	Kovar	38 mm Ø x -7 or 19+ mm	17025 Ca: 0.0004
TL 2003D	.	.	.	0.0150	304 L	40 mm Ø x 20 mm	
IARM FeN40-18	.	.	.	0.032	.	.	0.0081	.	Nitronic 40	-38 mm Ø x -3 or -19 mm	
BS 254	(0.006)	0.0018	52.9	(0.03)	0.0038	0.0014	0.0063	0.0019	254 SMO	38 mm Ø x -7 or 19+ mm	17025 Zr: 0.0026
IARM FE2507-21	0.004	0.0024	.	0.022	(0.0048)	0.0015	0.0034	0.0019	2507	31 mm Ø x 2 or 18 mm	Zr: 0.0013
IARM Fe415-21	0.0036	0.0008	.	0.0049	0.0075	0.0019	0.0104	0.0013	415	31 mm Ø x 2 or 18 mm	
BS 179A	(0.003)	(0.001)	.	0.030	.	.	0.005	0.006	Ferralium 255	31 mm Ø x -7 mm last of stock	
IARM Fe254SMO-21	0.0044	0.0009	53.7	(0.0083)	0.0025	0.0017	0.0041	0.004	254 SMO	31 mm Ø x 2 or 18 mm	Ca: 0.0024
TL 2002D	0.0098	0.0098	316 MOD	40 mm Ø x 20 mm	
ECRM 298-2D	0.0028	0.0024	.	0.0011	.	0.0006	0.0029	0.0023	1.4410	38 mm Ø x 25 mm	
IARM Fe904L-22	0.0044	(0.0005)	49.0	0.017	0.0018	0.0018	0.0051	0.0020	904 L	40 mm Ø x 3 or 19 mm	Ca: 0.0041 Mg: 0.0009
IARM Fe304L-22	0.0054	0.0010	Ca:0.0005	0.015	(0.005)	0.0025	0.0101	0.0021	304 L	38 mm Ø x 3 or 19 mm	
SS 477	0.00399	0.00198	.	Mg:0.00053	.	0.00078	0.00453	.		38 mm Ø x 19 mm	
BS 96A	.	(0.0017)	.	0.26	.	.	.	1.18	455	38 mm Ø x -7 or 19+ mm	
IARM 99D	.	0.0026	.	(0.011)	.	.	.	0.67	Maraging 300	31 mm Ø x 2 or 18 mm	
BS 161B	.	0.0027	66.6	(0.0034)	0.0005	.	(0.0011)	0.67	Maraging 300	41 mm Ø x -7 or 19+ mm	17025
IARM FeC250-21	(0.0011)	0.0029	.	0.0019	0.0006	(0.0044)	(0.0015)	0.418	Maraging 250	31 mm Ø x 2 or 18 mm	
BS M250 *	.	0.003	[67.9]	.	<0.005	.	.	0.42	Maraging 250	38 mm Ø x -7 or 19+ mm	

Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units	
--------	----	---	----	----	---	----	----	----	-------	-------	--

CAST IRON

= Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Ce	La	Mg	Se	Te
1	MBH-FEPIGH-21	4.42	0.127	0.050	0.141	1.60	0.0113	0.040	0.088	0.20	0.018
1	NCS AH11112	3.95	0.511	0.055	0.014	2.30	0.487	0.141	0.251	0.014	.	.	.	0.032	.	.
1	NCS HS11799	3.95	0.511	0.055	0.014	2.30	0.487	0.141	0.251	0.014	.	0.012	0.0064	0.032	.	.
2	CZ SPL22 47A	3.82	0.084	0.137	0.011	1.07	0.82	0.606	0.016	0.024	(0.002)	0.010	.	0.035	.	.
1	VS ChG 56	(3.8)	(0.2)	(0.8)	(0.01)	(0.5)	(0.4)	(0.1)	(0.1)	(0.01)	(0.005)
1	VS ChG 57	(3.8)	(0.2)	1.17	(0.03)	(0.6)	(0.3)	(0.3)	(0.4)	(0.06)	(0.01)
1	NCS HS11798	3.78	0.606	0.053	0.020	2.73	0.526	0.856	0.700	0.042	.	0.0097	0.0042	(0.034)	.	.
1	SCRM 660/11	3.62	0.444	0.137	0.115	1.74
2	CZ SPL22 46A	3.66	0.098	0.109	0.010	1.42	0.86	0.628	0.014	0.026	.	0.005	.	0.047	.	.
2	CZ SPL22 48A	3.63	0.338	0.025	0.006	2.15	0.407	0.043	0.128	0.021	0.025	0.009	.	0.019	.	.
1	NCS HS92744c	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	.	.	0.022	.	0.042	.	.
1	NCS HS92746a	3.59	0.226	0.046	0.012	2.25	0.263	0.501	0.097	0.014	.	.	.	0.029	.	.
2	CZ SPL22 53A	3.56	0.052	0.053	0.0097	1.60	1.357	0.687	0.071	0.047	0.032	0.023	.	0.032	.	.
2	CZ SPL22 51A	3.46	0.405	0.147	0.004	1.63	0.152	0.111	0.075	0.006	0.035
2	CZ SPL22 50A	3.39	0.529	0.179	0.055	2.14	0.151	0.113	0.137	0.004	0.029
2	CZ SPL22 45A	3.33	0.778	0.031	0.010	2.83	0.008	0.405	0.058	0.078	0.031	0.032	.	0.066	.	.
1	SCRM 658/12	3.33	0.55	0.243	0.076	2.03
1	MBH-FEPIGM-21	3.22	0.077	0.051	0.053	0.71	0.0117	0.028	0.057	0.060	0.015
2	CZ SPL22 44A	3.20	0.711	0.033	0.005	2.51	0.018	0.521	0.063	0.046	0.024	0.005	.	0.015	.	.
1	NCS AH11353	3.15	0.47	0.020	0.0006	2.30	0.029	0.59	0.025	0.023	0.015	.	.	0.029	.	.
2	CZ SPL22 49A	3.12	0.328	0.038	0.009	2.06	0.384	0.132	0.300	0.064	0.094	(0.005)	.	0.007	.	.
1	Y 2863-9A	3.04	1.43	0.049	0.015	1.53	0.269	1.59	0.72	.	0.042
2	CZ SPL22 52A	3.03	0.301	0.021	0.0094	2.38	0.607	0.021	0.025	0.011	0.010	0.012	.	0.008	.	.
1	BS CC-23	2.96	0.73	0.53	0.082	0.43	0.307	0.56	0.467	0.060	0.090	(0.0006)	(0.0008)	(0.0006)	.	(0.03)
1	CKD 242A	1.84	0.060	0.039	0.036	3.06	0.055	0.039	0.029	0.036	0.002	(0.00)	(0.00)	0.000	(0.000)	(0.08)

Number	As	B	Bi	Fe	Mo	Nb	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units in mm
MBH-FEPIGH-21	0.0015	.	.	.	0.027	0.019	.	.	0.0075	0.42	0.108	(0.004)	.	0.0039	-40 Ø x ~15
NCS AH11112	0.474	.	.	.	0.055	0.117	0.312	.	.	.	31 Ø x 30
NCS HS11799	0.474	.	.	.	0.055	0.117	0.312	.	.	.	31 Ø x 30
CZ SPL22 47A	.	(0.0005)	.	.	(0.002)	.	0.012	0.026	0.016	0.027	0.007	0.004	0.027	(0.010)	40 Ø x 18
VS ChG 56	0.18	(0.001)	.	.	(0.01)	(0.002)	.	0.014	.	(0.06)	(0.02)	(0.004)	.	.	-37 Ø x ~17
VS ChG 57	0.095	(0.002)	.	.	(0.01)	(0.004)	.	(0.001)	(0.01)	(0.08)	(0.04)	(0.01)	.	.	-37 Ø x ~17
NCS HS11798	0.359	.	.	0.025	0.032	0.117	0.018	.	.	.	31 Ø x 30
SCRM 660/11	48 x 42 x 12
CZ SPL22 46A	(0.003)	0.0021	0.005	.	0.011	(0.012)	0.021	0.024	0.014	0.046	0.008	0.008	0.018	(0.004)	40 Ø x 18
CZ SPL22 48A	(0.021)	0.0045	.	.	0.482	.	0.015	.	0.010	0.030	0.016	.	.	.	40 Ø x 18
NCS HS92744c	0.0021	0.024	.	.	0.180	0.044	0.174	.	.	.	35 Ø x 30
NCS HS92746a	(0.003)	0.0086	.	.	0.214	0.040	0.033	.	.	.	35 Ø x 30
CZ SPL22 53A	(0.004)	0.0046	(0.007)	.	0.002	.	.	0.066	0.007	0.035	0.013	0.010	(0.004)	.	40 Ø x 18
CZ SPL22 51A	(0.007)	.	(0.008)	.	0.037	.	0.006	0.012	0.072	0.033	0.017	(0.005)	(0.002)	.	40 Ø x 18
CZ SPL22 50A	.	(0.0008)	0.011	.	0.045	.	0.004	0.011	0.068	0.030	0.015	(0.006)	.	.	40 Ø x 18
CZ SPL22 45A	.	0.022	.	.	0.182	.	0.005	.	0.034	0.079	0.022	0.015	.	(0.015)	40 Ø x 18
SCRM 658/12	48 x 42 x 12
MBH-FEPIGM-21	(0.0018)	.	.	.	0.0157	0.014	.	.	0.0061	0.258	0.071	(0.003)	.	0.0022	-40 Ø x ~15
CZ SPL22 44A	.	0.0037	0.009	.	0.174	(0.014)	0.017	0.018	0.026	0.084	0.014	0.018	0.009	(0.007)	40 Ø x 18
NCS AH11353	0.008	0.004	.	.	0.002	N:0.003	.	0.0005	0.003	0.027	0.032	0.003	.	.	30 Ø x 25
CZ SPL22 49A	0.020	0.0075	.	.	0.475	(0.005)	0.008	(0.007)	0.011	0.024	0.081	0.013	(0.003)	.	40 Ø x 18
Y 2863-9A	(0.041)	0.153	.	.	1.38	0.11	(0.093)	(0.116)	(0.124)	0.212	0.41	.	.	.	30 Ø x 18-30
CZ SPL22 52A	0.041	0.0082	0.011	.	0.621	(0.003)	(0.003)	0.014	0.032	0.029	0.023	(0.004)	0.004	0.015	40 Ø x 18
BS CC-23	0.016	0.067	.	(92.8)	0.267	(0.002)	0.008	0.17	0.052	0.091	0.195	(0.002)	17025	0.057	-32 Ø x ~17 17025
CKD 242A	0.015	0.008	(0.015)	(92.9)	1.13	0.013	(0.012)	0.007	0.010	0.19	0.37	(0.007)	(0.00)	(0.000)	37x37x ~18-20 last

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
1.0812		ECRM 191-2D	15-5PH		BS 9622	3115		BS XCCT
1.2344		ECRM 271-1D	15-5PH		IARM Fe155PH-18	314		IMZ 165
1.4410		ECRM 298-2D	15-5PH		ECRM 273-1D	314		IMZ 166A
1.4435, 1.4436		JK 27B	16MnCr5		PV 102/1	316 H		13X NSA2
1.5415		HRT FE2012-N	17-4PH		13X PH2	316 H		CT 316
1.6587		HRT FE2013-N	17-4PH		BS 17-4PHA	316 H		IARM 339A
1.7149 20MnCrS5		ECRM 187-2D	17-4PH	17025	BS 17-4PHB	316 H		NILAB 500HAD
1.7160		ECRM 194-1D	17-4PH	17025	BS 17-4PHC	316 L	17025	BS 316F
1.8550		ECRM 129-3D	17-4PH		IARM Fe174PH-18	316 L		CZ SL-2A
1.8519		HRT FE2010-N	17-4PH		SRM C2400	316 L		IARM Fe316L-18
1.8928		ECRM 194-2D	17-7PH		13X PH17700	316 L		IARM 163E
1005	17025	BS 1005	17-7PH 25(preceeded 17025)		BS 192	316 L		SRM 1155A
1005		DSZU C040a	17-7PH 25(preceeded 17025)		BS 192A	316 L		SS 466/2
1005		ECRM 064-2D	17-7PH		IARM 152C	316 MOD		TL 2002
1005		RM Fe 1/5	17-7PH		IARM Fe177PH-18	316 Ti		IRSID 1821
1005		SRM 1765	182FM		BS 150	316 Ti		PV 112/1
1005		SRM 1766	18Cr2Ni12Mn		CT ISO035A	316 Ti		VS LG72
1005		SS 111/1	201		BS 191	317 L	17025	BS 317L
1006		IRSID 1670	201		SRM 1297	317 L	25(pre-17025)	BS 9941
1006		NM 305	20Cb3		BS 187A	317 L	25(pre-17025)	BS 9942
1008	17025	BS XCAS	20Cb3		CT 20 Cb-3	317 L		IARM 153C
1008		ECRM 057-2D	20MoCr4		ECRM 197-1D	318	17025	BS 2205
1009	17025	BS 1009	2101		IARM 292A	318		BS 2205A
1009 + Al	17025	BS XCCS-2	21Cr6Ni9Mn		CT ISO129A	321		13X 32100
100C6		IRSID 1747	2205		13x NSA9	321	17025	BS 85D
1010		IMZ 111	2205	17025	BS 2205	321	17025	BS 321D
1011		IMZ 73	2205	17025	BS 2205A	321		IARM 6i
1012, 1013		IMZ 71A	2205		IARM 212D	321		IARM 6J
1016	17025	BS 1016	2205		HRT FE2000-H	321		SRM 1171
1017		IMZ 112B	2205		IARM Fe2205-18	321		SS 465/1
1017		IRSID 1664	2304		IARM 317A	321 - Ti		IMZ 152
1018		12X 10180B	2507	17025	BS 2507	32750		13X NSA13
1018		12X 10180C	2507		IARM 301B	3310		BS 3310
1018	17025	BS 1018	2507		IARM Fe2507-21	347		13X 34700
1018		ECRM 087-1D	253 MA	25(pre-17025)	BS 253	347		BS 347A
1018		IARM 28K	253 MA		IARM 316A	347		BS 347B
1020	17025	BS 1020	254 SMO	17025	BS 254	347		BS 347C
1020		BS 57F	254 SMO		IARM Fe254SMO-21	347		IARM 8G
1020		IARM Fe1020-18	254 SMO		NILAB 501HAD	347		IARM 8H
1023		IMZ 112A	255, Duplex		IARM 239B	347		IARM 8i
1026	17025	BS 1026	255, Duplex		IARM 239C	347 H		BS 87F
1026	17025	BS 1026A	300M		12X 44220	348		SRM 1172
1026		IARM 359A	300M	17025	BS 300A	355	17025	BS 355
1030	17025	BS 1030	300M		IARM 340A	355		IARM 335A
1030	17025	BS 1030A	301		IARM 289A	35MV7		IRSID 1750
1030		IARM 209D	301		IARM 289B	405		SRM 1295
1033		IRSID 1663	301		IRSID 1819	408		13X 40800A
1035	17025	BS 1035	302		IARM 241D	409		13X 40900
1035		IARM 360A	302 HQ		IARM 234C	409		13X 40930
1039		IRSID 1637	303		13X 30300	409		IARM Fe409-20
1040	17025	BS 1040	303	17025	BS 303	409 + Cr		NCS HS20743
1040		IARM 210D	303		CT 303	410		13X 41008
1040		IRSID 1657	303		CZ SP-1A	410	25(pre-17025)	BS 0021
1042		IRSID 1656	303		IARM Fe303-18	410, F6NM	25(pre-17025)	BS 0022
1042		NM EN-8	303 Se		IARM 253A	410	17025	BS 410C
1043		IRSID 1652	303 Se		IARM 253B	410		CT 410
1045	17025	BS 1045	304 H		13X NSB1	410		IARM Fe410-18
1045		BS 56E	304 H + Ca	17025	BS CA304-4	410 + Mo		ECRM 296-1D
1045		IARM 200D	304 H		CT 304	410 + Mo		IMZ 161
1045		IPT 503	304 H		IARM Fe304H-18	410 H		13X 41001
1050		IARM Fe1050-18	304 H		SS 468/1	4130	17025	BS 4130
1060		IARM 373A	304 L		13X 30403	4130		IARM 143F
1060 + P		NM 309	304 L	17025	BS 304B	4130		SRM 1225
1069		ECRM 059-2D	304 L		IARM 162D	4130 H		IPT 501
1070	17025	BS 54H	304 L		IARM Fe304L-18	4140		12X 41400
1078		ECRM 056-2D	304 L		IARM Fe304L-22	4140	25(pre-17025)	BS 1962
1078		SRM 1224	304 L		ECRM 287-1D	4140	17025	BS 4140C
1080		BS 54T	304 L		ECRM 292-1D	4140		IARM 30H
1090		SS 602/2	304 L		IARM 162D	4140		IARM 30J
1095		BS 64C	304 L		PV 111/1	4140		IARM Fe4140-19
1095		SRM 1227	304 L		TL 2003D	4140 Bi		BS 4140A
1117 25(preceeded 17025)		BS 3993	304 L		SS 463/1	4140 Bi		BS 4140B
1117		BS 65C	305		ECRM 297-1D	41L40MOD	17025	BS 70B
1117		IARM 29E	306		13X 30600A	41L40MOD	17025	BS 70C
1118		IARM 307A	308		DSZU C017	4150 Bi & S		BS 4150MOD
1118		IARM 307B	309		BS 82E	4150 S	17025	BS 4150MOD-A
1141		BS 66B	309	17025	BS 309	4150 S	17025	BS 42
1141		IARM 348A	309		IARM Fe309-18	415		13X 41500A
1144	17025	BS 1144	310		13X 31008	415		IARM Fe415-21
1144	17025	BS 1144A	310		BS 83G	416		BS 90F
1144		IARM 199C	310	25(pre-17025)	BS 9841	416	17025	BS 416
11L17	17025	BS 75F	310	25(pre-17025)	BS 9842	416		CT 416
11L17	17025	BS 75G	310		CZ SL-3A	416		SRM 1223
1215		BS 66K	310		IARM 4E	416 H		13X 41600
1215	17025	BS 66L	310		IARM 4F	416 Se		BS 151
1215		IARM Fe1215-18	310		IARM 4G	418		IARM Fe418-18
12L14		BS 74B	310		SS 464/1	41CAD7		IRSID 1749
12L14	17025	BS 74C				41L40	17025	BS 70B
12L14	17025	BS 74D				41L50	17025	BS 72B
12Mn18Cr		BS 193				42		CT ISO138A
1345		BS XCCV				42		CT ISO139A
13-8PH		13X PH13800				42CrMo4		PV 101/1
13-8PH		BS 184A				420		BS 98
13-8PH		CT X92834				420		BS SS4951
13-8PH		IARM 21D				420		BS SS4952
1429		ECRM 058-2D				420		ECRM 272-1D
1513		IMZ 76				420		IARM 154C
1526 MOD		SRM 1269				420		SS 469
1541		IARM 349A				420 F		BS 152
1541		IPT 504				420 F S		IARM 352A
1541		IRSID 1648				422		13X 42200
1544		IRSID 1644				422		BS 97
15-5PH		BS 185A				422	17025	BS 422
15-5PH		BS 9621				422		IARM 205D
						422		IARM Fe422-22

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within this catalog.

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
430		BS 91E	A-36		BS LF2B	Invar		14X 93603
430	17025	BS 430	A-36		IARM 213C	Invar-36	17025	BS 186B
430		IARM 11D	A-36		IARM 213D	Invar-36 + Se		BS 186A
430		NCS HS20742	A-485-1		BS A485-1	Invar-36 + Se		IARM 24B
430 F		BS 153	A-6		BS 40B	Invar 36 + Se		IARM FeINVR36-22
430 F		BS 154	A-6		IARM 40B	Invar 42		14X 94100
430 F S		IARM 355A	A-6		IARM 40C	ISO 898-1		SS 457/2
431	17025	BS 431	A615-75		IARM 378A	Kovar	17025	BS 160A
431		BS 92B	A706-60		IARM 380A	Kovar	17025	BS 160B
431		IARM 12C	A706-60		IARM 380B	Kovar		IARM 98B
431		HRT FE2010-H	A706-80		IARM 381A	Kovar		IARM FeKovar-18
431		SRM 1219	Aermet 100		CT ISO045A	L-2	17025	BS 43A
4320		BS 3961	Aermet 100		IARM 242A	L-6	17025	BS 39B
4330 MOD		BS 4330MOD	Aermet 100		IARM FeA100-18	L-6		IARM FeL6-18
4330 MOD		IARM 330B	AL6XN	17025	BS 189A	LDX2101		13X 32101
4340	17025	BS 4340	AL6XN		IARM 157D	LF-2		BS 2971
4340	17025	BS 4340A	C-.5Mo	17025	BS 3952	LF-2	17025	BS LF2B
4340		IARM 31G	C-.5Mo		IARM 229B	LF-2		SS 601/2
440 C		13X 44004	C-250		IARM 308A	LF-3		BS LF3
440 C		BS 93E	C-350		IARM 309A	M-1		BS TM1
440 C	17025	BS 93F	CA6NM		HRT FE2009-H	M-1		CT M1
440 C		IARM 13D	CA6NM		IARM 327A	M-1		IARM 304A
440 F		BS 155	CD3MN		ECRM 298-2D	M-1		IARM FeM1-18
440 F Se		BS 156	CD4MCU	17025	BS CD4MCU	M-10		CT M10
440 F Se		IARM 353A	CD4MCU	17025	BS CD4MCU-A	M-10		IARM 324A
446		BS 94C	CD6MN		VS LG58	M-152		13X 64152
450		BS 95A	CF-3		IRSID 1820	M-152		IARM 291A
450	17025	BS 450	CF3M		ECRM 284-3D	M-2		BS 32D
450	25(pre-17025)	BS 9811	CLA6		IARM 169B	M-2		CT M2
450	25(pre-17025)	BS 9812	CLA7		IARM 170B	M-2		IARM 44C
450		IARM 15C	CLA11		IARM 180A	M-2		IARM FeM2-18
450		CT 450	CLA5		IARM 168A	M-2		SRM 1157
455		13X 45500	CLA9		IARM 172A	M-35		IARM 320A
455		BS 96A	CPM15V	17025	BS PM15	M-4		IARM 251A
455		BS SS1962	CPM15V		IARM Fe15V-18	M-4		IARM FeM4-18
455		CT 455	D-2		BS 37E	M-42		SS 487/1
455		IARM 16C	D-2		BS 37G	M-47	17025	BS M-47
446		IARM 14C	D-2		CT D2	M-50	17025	BS M-50
4615	17025	BS 3962	D-2		IARM 41D	M-50		IARM 306B
4620		BS 4620	D-6	17025	BS D-6	M-65		IARM FeM62-18
4620	17025	BS 51F	D-6	17025	BS D-6A	M-7		CT M7
4620		IARM 33D	D6-AC		IARM 299A	Maraging 250		CT 250
465		13X 46500	DP1080		IARM FeDP1080-18	Maraging 250		ECRM 285-2
465		IARM 354A	Duplex		13X NSA9	Maraging 250		IARM FeC250-21
465		CT ISO123A	Duplex	17025	BS 2205	Maraging 300	25(pre17025)	BS 161A
4820	17025	BS 4820A	Duplex		IMZ 163A	Maraging 300	17025	BS 161B
4820		BS 4820B	Duplex		IMZ 164	Maraging 300		CT 300
4820		IARM 155F	Duplex		TL 2001	Maraging 300		IARM 99D
5140H		IARM Fe4820-18	E52100		BS 53G	Mold Steel	17025	BS PP20
5140H		IARM Fe5140H-18	E52100	17025	BS E52100	NIT 135M		IARM 305B
5160		IMZ 116	E52100		IARM 49E	Nitriding 135G		BS 68B
6150	17025	BS 43A	E52100 Bi		BS 53MOD	Nitriding 135G	17025	BS 68E
6150		BS 4941	Elect./ Magnetic		SRM 1159	Nitronic 40		13X NSC6
6150		IARM 34C	Electrolytic		SRM 1265a	Nitronic 40		BS 190
630		CT 630	ER321		13X 32180A	Nitronic 40		IARM FeN40-18
6418	17025	BS 6418	F-1		RM Fe 2	Nitronic 50		BS 180A
6418		BS 69B	F-11		BS 45A	Nitronic 50	17025	BS 180B
6526		BS 9-4-30	F-11	17025	BS 45B	Nitronic 50		IARM 17D
709		CT X67975	F-11		IARM 35L	Nitronic 50		IARM FeN50-18
8620		12X 86200-21	F-11		IARM FeF11-21	Nitronic 60		13X 21800
8620		BS 1931	F-2		CT X27081	Nitronic 60		BS 181A
8620 + Bi		BS 8620A	F-22	17025	BS 46B	Nitronic 60	17025	BS 181B
8620		BS 8620G	F-22	25(preceded 17025)	BS 1982	Nitronic 60		IARM 18D
8620		IARM Fe8620-18	F-22		IARM 36C	NMS 100		IARM 214A
8620		IPT 502	F-22		SRM 1270	NMS 140		IARM 295A
86L20	25(preceded 17025)	BS 73B	F-22 + Cr		HRT FE2009-N	NMS J38		IARM 294A
86L20		BS 73C	F-5		BS 47A	O-1	17025	BS 35D
8630	17025	BS 8630	F-5		BS 47B	O-1		CT O1
8740		BS 67B	F-5		IARM 37C	O-2		CZ LA-4C
8740	17025	BS 8740	F-51	17025	BS 2205	O-6	17025	BS 41
8740		IARM 252C	F-51		BS 2205A	O-6	25(preceded 17025)	BS 41A
8740		IARM 252D	F-9	17025	BS 48B	O-6		IARM 45A
8740		IARM 252E	F-9		IARM FeF9-18	O-6		IARM 45B
8740		IARM 252F	F-91		13X 90901	P-20	17025	BS 55G
8822		BS 8822	F-91	17025	BS 9905A	P-20 MOD		BS 55H
8822	17025	BS 8822A	F-91		HRT FE2003-H	P-20 + Al		BS 68C
904L		13X NSA12	F-91		IARM Fe91-18	PP-20	17025	BS PP20
904L		ECRM 295-1D	Ferrallium 255		BS 179A	RA330		BS 86F
904L		IARM Fe904L-22	Ferallium 255	17025	BS 179B	Railroad Steel	17025	BS 54H
9310		BS 58C	Ferallium 255	17025	BS 179C	S-1		BS 33D
9310		BS 58D	F6NM 25(preceded 17025)		BS 0022	S-1		BS 33E
9310		BS 58E	Greek Ascoloy		BS 183A	S-1		IARM 46B
9310		IARM FeE9310-18	Greek Ascoloy	17025	BS 183B	S-1 MOD	17025	BS 33F
9325	17025	BS 9325A	Greek Ascoloy	17025	BS 183C	S-5		BS 38C
9325		BS 9325B	Greek Ascoloy		IARM 20C	S-5		IARM 47B
9-4-30		IARM 341A	H-10		BS 49	S-7		BS TS7
A-10		BS A-10	H-11		BS TH11	S-7	17025	BS TS-7A
A-11		BS 10V	H-11		ECRM 276-2D	S-7		IARM 259A
A-11	17025	BS A-11	H-11		IARM 255A	S-7		IARM FeS7-18
A-106 Gr B		SRM 1228	H-11		IARM 255B	S-7		SRM 1772
A-193 B16		BS 4942	H-11		IMZ 173	S42027		13X 42027A
A-193 B16	17025	BS 4942A	H-12		BS TH12	SA213-T22		IMZ 159
A-2		BS 36C	H-13		BS 34D	SA213-T22		IMZ 160
A-2		BS 36D	H-13	17025	BS H-13A	SA213-T22		IMZ 169
A-2		CT A2	H-13		CT H13	SAE G2500		BS 20E
A-2		IARM 39B	H-13		IARM 42C	STA 361		IARM 268B
A-2		IARM 39C	H-13		IMZ 174	T-1	17025	BS 30D
A-242		IPT 500	H-19	17025	BS H-19	T-1		IARM FeT1-18
A-242 Mod		SRM C1285	HC 250+v		SRM C1290	T-4		IARM 281A
A-286	17025	BS 188B	High Perm		CT ISO124A	T-15	17025	BS TS15
A-286		IARM 26D	High Perm		CT ISO136A	T23		IARM FeT23-18
A-286		SRM 1230	High Perm 49		CT ISO141A	VM12		IMZ 196
A-36		BS 1016	HSLA 100		SRM 1271	W-5		14X 72305
A-36		BS 1016	HY 130		SRM 1226	Z30C13		IRSID 1825
A-36		BS 1018	HY 80		SRM 1286	Zeron 100, Duplex		13X NSA8
A-36		BS 1020	Hy-Tuff		IARM 342A	Zeron 100, Duplex		IARM 319A
						Zeron 100, Duplex		IARM FeZ100-18

CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S
1005	<0.06	<0.35	<0.03	<0.05
1006	<0.08	0.25-0.40	<0.03	<0.05
1008	<0.10	0.30-0.50	<0.03	<0.05
1009	<0.15	<0.60	<0.03	<0.05
1010	0.08-0.13	0.30-0.60	<0.03	<0.05
1011	0.09-0.14	0.60-0.90	<0.03	<0.05
1012	0.10-0.15	0.30-0.60	<0.03	<0.05
1013	0.11-0.16	0.50-0.80	<0.03	<0.05
1015	0.13-0.18	0.30-0.60	<0.03	<0.05
1016	0.13-0.18	0.60-0.90	<0.03	<0.05
1017	0.15-0.20	0.30-0.60	<0.03	<0.05
1018	0.15-0.20	0.60-0.90	<0.03	<0.05
1019	0.15-0.20	0.70-1.00	<0.03	<0.05
1020	0.18-0.23	0.30-0.60	<0.03	<0.05
1021	0.18-0.23	0.60-0.90	<0.03	<0.05
1022	0.18-0.23	0.70-1.00	<0.03	<0.05
1023	0.20-0.25	0.30-0.60	<0.03	<0.05
1025	0.22-0.28	0.30-0.60	<0.03	<0.05
1026	0.22-0.28	0.60-0.90	<0.03	<0.05
1029	0.25-0.31	0.60-0.90	<0.03	<0.05
1030	0.28-0.34	0.60-0.90	<0.03	<0.05
1033	0.29-0.36	0.70-1.00	<0.03	<0.05
1034	0.32-0.38	0.50-0.80	<0.03	<0.05
1035	0.32-0.38	0.60-0.90	<0.03	<0.05
1037	0.32-0.38	0.70-1.00	<0.03	<0.05
1038	0.35-0.42	0.60-0.90	<0.03	<0.05
1039	0.37-0.44	0.70-1.00	<0.03	<0.05
1040	0.37-0.44	0.60-0.90	<0.03	<0.05
1042	0.40-0.47	0.60-0.90	<0.03	<0.05
1043	0.40-0.47	0.70-1.00	<0.03	<0.05
1044	0.43-0.50	0.30-0.60	<0.03	<0.05
1045	0.43-0.50	0.60-0.90	<0.03	<0.05
1046	0.43-0.50	0.70-1.00	<0.03	<0.05
1049	0.46-0.53	0.60-0.90	<0.03	<0.05
1050	0.48-0.55	0.60-0.90	<0.03	<0.05
1053	0.48-0.55	0.70-1.00	<0.03	<0.05
1055	0.50-0.60	0.60-0.90	<0.03	<0.05
1059	0.55-0.65	0.50-0.80	<0.03	<0.05
1060	0.55-0.65	0.60-0.90	<0.03	<0.05
1064	0.60-0.70	0.50-0.80	<0.03	<0.05
1065	0.60-0.70	0.60-0.90	<0.03	<0.05
1069	0.65-0.75	0.40-0.70	<0.03	<0.05
1070	0.65-0.75	0.60-0.90	<0.03	<0.05
1074	0.70-0.80	0.50-0.80	<0.03	<0.05
1078	0.72-0.85	0.30-0.60	<0.03	<0.05
1080	0.75-0.88	0.60-0.90	<0.03	<0.05
1084	0.83-0.93	0.60-0.90	<0.03	<0.05
1085	0.80-0.94	0.70-1.00	<0.03	<0.05
1086	0.80-0.93	0.30-0.50	<0.03	<0.05
1090	0.85-0.98	0.60-0.90	<0.03	<0.05
1095	0.90-1.03	0.30-0.50	<0.03	<0.05
Number	C	Mn	P	S

CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si
1513	0.10-0.16	1.10-1.40	<0.03	<0.05	.
1522	0.18-0.24	1.10-1.40	<0.04	<0.05	.
1524	0.19-0.25	1.35-1.65	<0.04	<0.05	.
1526	0.22-0.29	1.10-1.40	<0.04	<0.05	.
1527	0.22-0.29	1.20-1.50	<0.04	<0.05	.
1533	0.30-0.37	1.10-1.40	<0.04	<0.05	.
1534	0.30-0.37	1.20-1.50	<0.04	<0.05	.
1541	0.36-0.44	1.35-1.65	<0.04	<0.05	.
1544	0.40-0.47	0.80-1.10	<0.04	<0.05	.
1545	0.43-0.50	0.80-1.10	<0.04	<0.05	.
1546	0.44-0.52	1.00-1.30	<0.04	<0.05	.
1548	0.44-0.52	1.10-1.40	<0.04	<0.05	.
1552	0.47-0.55	1.20-1.50	<0.04	<0.05	.
1553	0.48-0.55	0.80-1.10	<0.04	<0.05	.
1566	0.60-0.70	0.85-1.15	<0.04	<0.05	.
1570	0.65-0.75	0.80-1.10	<0.04	<0.05	.
1580	0.75-0.88	0.80-1.10	<0.04	<0.05	.
1590	0.85-0.98	0.80-1.10	<0.04	<0.05	.
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30
Number	C	Mn	P	S	Si

RESULFURIZED STEEL SPECIFICATIONS

Number	C	Mn	P	S
1108	0.08-0.13	0.50-0.80	<0.04	0.08-0.13
1109	0.08-0.13	0.60-0.90	<0.04	0.08-0.13
1110	0.08-0.13	0.30-0.60	<0.04	0.08-0.13
1116	0.14-0.20	1.10-1.40	<0.04	0.16-0.23
1117	0.14-0.20	1.00-1.30	<0.04	0.08-0.13
1118	0.14-0.20	1.30-1.60	<0.04	0.08-0.13
1119	0.14-0.20	1.00-1.30	<0.04	0.24-0.33
1123	0.20-0.27	1.20-1.50	<0.04	0.06-0.09
1132	0.27-0.34	1.35-1.65	<0.04	0.09-0.13
1137	0.32-0.39	1.35-1.65	<0.03	0.08-0.13
1139	0.35-0.43	1.35-1.65	<0.04	0.13-0.20
1140	0.37-0.44	0.70-1.00	<0.03	0.08-0.13
1141	0.37-0.45	1.35-1.65	<0.03	0.08-0.13
1144	0.40-0.48	1.35-1.65	<0.03	0.24-0.33
1145	0.41-0.49	0.70-1.00	<0.04	0.08-0.13
1146	0.42-0.49	0.70-1.00	<0.04	0.08-0.13
1151	0.48-0.55	0.70-1.00	<0.04	0.08-0.13
1152	0.48-0.55	0.70-1.00	<0.04	0.06-0.09
1211	<0.13	0.60-0.90	0.07-0.12	0.10-0.15
1212	<0.13	0.70-1.00	0.07-0.12	0.16-0.23
1213	<0.13	0.70-1.00	0.07-0.12	0.24-0.33
1215	<0.09	0.75-1.05	0.04-0.09	0.26-0.35
Number	C	Mn	P	S

These are specifications,
not samples for sale.

LOW ALLOY STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other
1330	0.28-0.33	1.60-1.90	<0.035	<0.04	0.15-0.35
1335	0.33-0.38	1.60-1.90	<0.035	<0.04	0.15-0.35
1340	0.38-0.43	1.60-1.90	<0.035	<0.04	0.15-0.35
1345	0.43-0.48	1.60-1.90	<0.035	<0.04	0.15-0.35
3140	0.38-0.43	0.70-0.90	<0.04	<0.04	0.15-0.35	1.10-1.40	0.55-0.75	.	.	.
4023	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4027	0.25-0.30	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4028	0.25-0.30	0.70-0.90	<0.035	0.035-0.050	0.15-0.35	.	.	0.20-0.30	.	.
4037	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4047	0.45-0.50	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4118	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.08-0.15	.	.
4120	0.18-0.23	0.80-1.20	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.15-0.25	.	.
4121	0.18-0.23	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.45-0.65	0.15-0.25	.	.
4130	0.28-0.33	0.40-0.60	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4135	0.33-0.38	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4137	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4140	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
41L40	0.38-0.43	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	.
4142	0.40-0.45	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4145	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4147	0.45-0.50	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4150	0.48-0.53	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
41L50	0.48-0.53	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	.
4320	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	0.40-0.60	0.20-0.30	.	.
4340	0.38-0.43	0.60-0.80	<0.035	<0.04	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	.
4615	0.13-0.18	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4617	0.15-0.20	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4620	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4715	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.70-1.00	0.45-0.65	0.45-0.65	.	.
4720	0.17-0.22	0.50-0.70	<0.035	<0.04	0.15-0.35	0.90-1.20	0.35-0.55	0.15-0.25	.	.
4815	0.13-0.18	0.40-0.60	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	.
4820	0.18-0.23	0.50-0.70	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	.
50B46	0.44-0.49	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.20-0.35	.	.	B: 0.0005-0.003
5120	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
51L20	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	0.15-0.35	.
5130	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	.
5132	0.30-0.35	0.60-0.80	<0.035	<0.04	0.15-0.35	.	0.75-1.00	.	.	.
5140	0.38-0.43	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
5150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
5160	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
51B60	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	B: >0.0005
6150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	V: >0.15
8615	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8617	0.15-0.20	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8620	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
86L20	0.18-0.21	0.70-0.90	<0.035	0.02-0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	0.15-0.35	.
8622	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8630	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8637	0.35-0.40	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8640	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8645	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8720	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	.
8740	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	.
8822	0.20-0.25	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.30-0.40	.	.
9259	0.56-0.64	0.75-1.00	<0.035	<0.04	0.70-1.10	.	0.45-0.65	.	.	.
9260	0.56-0.64	0.75-1.00	<0.035	<0.04	1.80-2.20
E4340	0.38-0.43	0.65-0.85	<0.025	<0.025	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	.
E51100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	0.90-1.15	.	.	.
E52100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	1.30-1.60	.	.	.
E9310	0.08-0.13	0.45-0.65	<0.025	<0.025	0.15-0.35	3.00-3.50	1.00-1.40	0.08-0.15	.	.
F-11	0.10-0.20	0.30-0.60	<0.04	<0.04	0.50-1.00	.	1.00-1.50	0.44-0.65	.	.
F-22	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	2.00-2.50	0.90-1.10	.	.
F-5	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	4.00-6.00	0.45-0.65	.	.
F-9	<0.15	0.30-0.60	<0.03	<0.03	0.50-1.0	.	8.00-10.00	0.90-1.10	.	.
F-91	0.08-0.12	0.30-0.60	<0.02	<0.01	0.20-0.50	<0.40	8.00-9.50	0.85-1.05	.	Al: <0.04 N: 0.03-0.07
F-91	continued									Nb: 0.06-0.10 V: 0.18-0.25
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30
LF3	<0.20	<0.90	<0.035	<0.04	0.20-0.35	3.25-3.75

Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other
--------	---	----	---	---	----	----	----	----	----	-------

These are specifications,
not samples for sale.

TOOL STEEL SPECIFICATIONS

* notes optional chemistry

Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other
A-2	0.95-1.05	<1.00	<0.03	<0.03	<0.50	.	4.75-5.50	.	0.90-1.40	0.15-0.50	.	.
A-4	0.95-1.05	1.80-2.20	<0.03	<0.03	<0.50	.	0.90-2.20	.	0.90-1.40	.	.	.
A-6	0.65-0.75	1.80-2.50	<0.03	<0.03	<0.50	.	0.90-1.20	.	0.90-1.40	.	.	.
A-7	2.00-2.85	<0.80	<0.03	<0.03	<0.50	.	5.00-5.75	.	0.90-1.40	3.90-5.15	0.50-1.50	.
A-8	0.50-0.60	<0.50	<0.03	<0.03	0.75-1.10	.	4.75-5.50	.	1.15-1.65	.	1.00-1.50	.
A-9	0.45-0.55	<0.50	<0.03	<0.03	0.95-1.15	1.25-1.75	4.75-5.50	.	1.30-1.80	0.80-1.40	.	.
A-10	1.25-1.50	1.60-2.10	<0.03	<0.03	1.00-1.50	1.55-2.05	.	.	1.25-1.75	.	.	.
A-11	2.45	0.50	.	.	0.90	.	5.25	.	1.30	9.75	.	.
D-2	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	<1.00	0.70-1.20	<1.10	.	.
D-3	2.00-2.35	<0.60	<0.03	<0.03	<0.60	.	11.00-13.50	.	.	<1.00	<1.00	.
D-4	2.05-2.40	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	.	0.70-1.20	<1.00	.	.
D-5	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	2.50-3.50	0.70-1.20	<1.00	.	.
D-7	2.15-2.50	<0.60	<0.03	<0.03	<0.60	.	11.50-13.50	.	0.70-1.20	3.80-4.40	.	.
H-10	0.35-0.45	0.25-0.70	<0.03	<0.03	0.80-1.20	.	3.00-3.75	.	2.00-3.00	0.25-0.75	.	.
H-11	0.33-0.43	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.60	0.30-0.60	.	.
H-12	0.30-0.40	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.25-1.75	<0.50	1.00-1.70	.
H-13	0.32-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.75	0.80-1.20	.	.
H-14	0.35-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	.	.	4.00-5.25	.
H-19	0.32-0.45	0.20-0.50	<0.03	<0.03	0.20-0.50	.	4.00-4.75	4.00-4.50	0.30-0.55	1.75-2.20	3.75-4.50	.
H-21	0.26-0.36	0.15-0.40	<0.03	<0.03	0.15-0.50	.	3.00-3.75	.	.	0.30-0.60	8.50-10.00	.
H-22	0.30-0.40	0.15-0.40	<0.03	<0.03	0.15-0.40	.	1.75-3.75	.	.	0.25-0.50	10.00-11.75	.
H-23	0.25-0.35	0.15-0.40	<0.03	<0.03	0.15-0.60	.	11.00-12.75	.	.	0.75-1.25	11.00-12.75	.
H-24	0.42-0.53	0.15-0.40	<0.03	<0.03	0.15-0.40	.	2.50-3.50	.	.	0.40-0.60	14.00-16.00	.
H-26	0.45-0.55	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-4.50	.	.	0.75-1.25	17.25-19.00	.
H-42	0.55-0.70	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	.
L-2	0.45-1.00	0.10-0.90	<0.03	<0.03	<0.50	.	0.70-1.20	.	<0.25	0.10-0.30	.	.
L-6	0.65-0.75	0.25-0.80	<0.03	<0.03	<0.50	1.25-2.00	0.60-1.20	.	<0.50	.	.	.
M-1	0.78-0.88	0.15-0.40	<0.03	<0.03	0.20-0.50	.	3.50-4.00	.	8.20-9.20	1.00-1.35	1.40-2.10	.
M-2	0.78-1.05	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	.
M-3.1	1.00-1.10	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.25-2.75	5.00-6.75	.
M-3.2	1.15-1.25	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.75-3.25	5.00-6.75	.
M-4	1.25-1.40	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.75	.	4.25-5.50	3.75-4.50	5.25-6.50	.
M-6	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	11.00-13.00	4.50-5.50	1.30-1.70	3.75-4.75	.
M-7	0.97-1.05	0.15-0.40	<0.03	<0.03	0.20-0.55	.	3.50-4.00	.	8.20-9.20	1.75-2.25	1.40-2.10	.
M-10	0.84-1.05	0.10-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	7.75-8.50	1.80-2.20	.	.
M-30	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.25	4.50-5.50	7.75-9.00	1.00-1.40	1.30-2.30	.
M-33	0.85-0.92	0.15-0.40	<0.03	<0.03	0.25-0.55	.	3.50-4.00	7.75-8.75	9.00-10.00	1.00-1.35	1.30-2.10	.
M-34	0.85-0.92	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.00	7.75-8.75	7.75-9.20	1.90-2.30	1.40-2.10	.
M-36	0.80-0.90	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	7.75-8.75	4.50-5.50	1.75-2.25	5.50-6.50	.
M-41	1.05-1.15	0.20-0.60	<0.03	<0.03	0.15-0.50	.	3.75-4.50	4.75-5.75	3.25-4.25	1.75-2.25	6.25-7.00	.
M-42	1.05-1.15	0.15-0.40	<0.03	<0.03	0.15-0.65	.	3.50-4.25	7.75-8.75	9.00-10.00	0.95-1.35	1.15-1.85	.
M-46	1.22-1.30	0.20-0.40	<0.03	<0.03	0.40-0.65	.	3.70-4.20	7.80-8.80	8.00-8.50	3.00-3.30	1.90-2.20	.
M-48	1.50	3.75	9.00	5.25	3.10	10.0	.
M-52	0.90	4.00	.	4.00	2.00	1.25	.
M-61	1.60	4.00	.	6.50	5.00	12.0	.
M-62	1.30	3.75	.	10.5	2.00	6.25	.
O-1	0.85-1.00	1.00-1.40	<0.03	<0.03	<0.50	.	0.40-0.60	.	.	<0.30	0.40-0.60	.
O-2	0.85-0.95	1.40-1.80	<0.03	<0.03	<0.50	.	<0.35	.	<0.30	<0.30	.	.
O-6	1.25-1.55	0.30-1.10	<0.03	<0.03	0.55-1.50	.	<0.30	.	0.20-0.30	.	.	.
O-7	1.10-1.30	<1.00	<0.03	<0.03	<0.60	.	0.35-0.85	.	<0.30	<0.40	1.00-2.00	.
P-20	0.28-0.40	0.60-1.00	<0.03	<0.03	0.20-0.80	.	1.40-2.00	.	0.30-0.55	.	.	.
P-21	0.18-0.22	0.20-0.40	<0.03	<0.03	0.20-0.40	4.00-4.25	0.20-0.30	.	.	0.15-0.25	.	Al: 1.05-1.25
P-6	0.05-0.15	0.35-0.70	<0.03	<0.03	0.10-0.40	3.25-3.75	1.25-1.75
S-1	0.40-0.55	0.10-0.40	<0.03	<0.03	0.15-1.20	.	1.00-1.80	.	<0.50	0.15-0.30	1.50-3.00	.
S-2	0.40-0.55	0.30-0.50	<0.03	<0.03	0.90-1.20	.	.	.	0.30-0.60	<0.50	.	.
S-4	0.50-0.65	0.60-0.95	<0.03	<0.03	1.75-2.25	.	<0.35	.	.	<0.35	.	.
S-5	0.50-0.65	0.60-1.00	<0.03	<0.03	1.75-2.25	.	<0.35	.	0.20-1.35	<0.35	.	.
S-6	0.40-0.50	1.20-1.50	<0.03	<0.03	2.00-2.50	.	1.20-1.50	.	0.30-0.50	0.20-0.40	.	.
S-7	0.45-0.55	0.20-0.80	<0.03	<0.03	0.20-1.00	.	3.00-3.50	.	1.30-1.80	0.20-0.30*	.	.
T-1	0.65-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	.	.	0.90-1.30	17.25-18.25	.
T-15	1.50-1.60	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-5.00	4.75-5.25	<1.00	4.50-5.25	11.75-13.00	.
T-4	0.70-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	0.80-1.20	17.50-19.00	.
T-5	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-5.00	7.00-9.50	0.50-1.25	1.80-2.40	17.50-19.00	.
T-6	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	4.00-4.75	11.00-13.00	0.40-1.00	1.50-2.10	18.50-21.00	.
T-8	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	1.80-2.40	13.25-14.75	.
W-1	0.70-1.50	0.10-0.40	<0.025	<0.025	0.10-0.40	<0.20	<0.15	.	<0.10	<0.10	<0.15	Cu: <0.20
W-2	0.85-1.50	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	<0.15	.	<0.10	0.15-0.35	<0.15	Cu: <0.20
W-5	1.05-1.15	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	0.40-0.60	.	<0.10	<0.10	<0.15	Cu: <0.20

Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other
--------	---	----	---	---	----	----	----	----	----	---	---	-------

These are specifications,
not samples for sale.

STAINLESS AND HIGH ALLOY STEEL SPECIFICATIONS

* notes optional chemistry

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	N	Nb	Other
13-8PH	<0.05	<0.20	<0.01	<0.008	<0.10	.	7.50-8.50	12.25-13.25	2.00-2.50	<0.01	.	Al: 0.90-1.35
15-5PH	<0.07	<1.00	<0.04	<0.03	<1.00	2.50-4.50	3.50-5.50	14.00-15.50	.	.	0.15-0.45	
17-4PH	<0.07	<1.00	<0.04	<0.03	<1.00	3.00-5.00	3.00-5.00	15.00-17.50	.	.	0.15-0.45	
201	<0.15	5.5-7.5	<0.060	<0.03	<1.00	.	3.50-5.50	16.00-18.00	.	<0.25	.	
202	<0.15	7.5-10.0	<0.060	<0.03	<1.00	.	4.00-6.00	17.00-19.00	.	<0.25	.	
301	<0.15	<2.00	<0.045	<0.03	<1.00	.	6.00-8.00	16.00-18.00	.	.	.	
302	<0.15	<2.00	<0.045	<0.03	<1.00	.	8.00-10.00	17.00-19.00	.	.	.	
302B	<0.15	<2.00	<0.045	<0.03	2.00-3.00	.	8.00-10.00	17.00-19.00	.	.	.	
303	<0.15	<2.00	<0.20	>0.15	<1.00	.	8.00-10.00	17.00-19.00	<0.60*	.	.	Zr: <0.60*
304	<0.08	<2.00	<0.045	<0.03	<1.00	.	8.00-10.50	18.00-20.00	.	.	.	
304L	<0.03	<2.00	<0.045	<0.03	<1.00	.	8.00-12.00	18.00-20.00	.	.	.	
305	<0.12	<2.00	<0.045	<0.03	<1.00	.	10.00-13.00	17.00-19.00	.	.	.	
308	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-12.00	19.00-21.00	.	.	.	
309	<0.20	<2.00	<0.045	<0.03	<1.00	.	12.00-15.00	22.00-24.00	.	.	.	
310	<0.25	<2.00	<0.045	<0.03	<1.50	.	19.00-22.00	24.00-26.00	.	.	.	
314	<0.25	<2.00	<0.045	<0.03	1.50-3.00	.	19.00-22.00	23.00-26.00	.	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316L	<0.03	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
321	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-12.00	17.00-19.00	.	.	.	Ti: >5xC
347	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	
348	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	
384	<0.08	<2.00	<0.045	<0.03	<1.00	.	17.00-19.00	15.00-17.00	.	.	.	Ta: <0.10
385	<0.08	<2.00	<0.045	<0.03	<1.00	.	14.00-16.00	11.50-13.50	.	.	.	
403	<0.15	<1.00	<0.04	<0.03	<0.50	.	.	11.50-13.00	.	.	.	
405	<0.08	<1.00	<0.04	<0.03	<1.00	.	.	11.50-14.50	.	.	.	Al: 0.10-0.30
409	<0.08	<1.00	<0.04	<0.01	<1.00	.	<0.50	10.50-11.75	.	.	.	Ti: 6\mtC-0.75
410	<0.15	<1.00	<0.04	<0.03	<1.00	.	.	11.50-13.50	.	.	.	
414	<0.15	<1.00	<0.04	>0.03	<1.00	.	1.25-2.50	11.50-13.50	.	.	.	
416	<0.15	<1.25	<0.06	>0.15	<1.00	.	.	12.00-14.00	<0.60*	.	.	Zr: <0.60*
420	>0.15	<1.00	<0.04	<0.03	<1.00	.	.	12.00-14.00	.	.	.	
422	0.20-0.25	<1.00	<0.04	<0.03	<0.75	<0.50	0.50-1.00	11.00-12.50	0.75-1.25	.	.	V: 0.15-0.30
422	continued											W: 0.75-1.25
430	<0.12	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	.	.	.	
430F	<0.12	<1.25	<0.06	>0.15	<1.00	.	.	16.00-18.00	<0.60*	.	.	Zr: <0.60*
431	<0.20	<1.00	<0.04	<0.03	<1.00	.	1.25-2.50	15.00-17.00	.	.	.	
440A	0.60-0.75	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440B	0.75-0.95	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440C	0.95-1.20	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
450	<0.05	<1.00	<0.03	<0.03	<1.00	1.25-1.75	5.00-7.00	14.00-16.00	0.50-1.00	.	.	8\mtC
455	<0.05	<0.50	<0.04	<0.03	<0.50	1.50-2.50	7.50-9.50	11.00-12.50	<0.50	.	0.10-0.50	Ti: 0.80-1.40
501	>0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
502	<0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
Duplex	<0.05	<3.00	<0.035	<0.03	<1.50	<2.50*	4.00-7.00	18.00-25.00	0.20-5.50	<0.40	.	

These are specifications,
not samples for sale.